3.3 Difference Between Dyeing And Printing

Dyeing	Printing
The process of imparting colour to the fabric is called dyeing.	Pigments or dyes applied locally or discontinuously to produce different designs on the fabric is known as printing.
It is performed on fabric, yarn or fibre in wet condition.	It is performed on fabric in dry condition.
Half bleaching is enough for fabric preparation.	Full-bleaching with optical whitener is essential.
Dyeing can be done on fibre, yarn and fabric.	Printing is done on fabrics only.
Colour is applied in the form of solution.	Colour is applied in form of thick paste.
For dyeing there is no design.	For printing there is a specific design.
Dyes are applied on both the sides of the fabric.	Dyes are applied on single side of the fabric.
Only one colour is generally used for dyeing	One or more colours are used in printing process.
In dyeing process, colour penetrates through the fibre or fabric.	Colour is applied only on the surface.
A particular temperature is maintained in the dyeing process.	Carried out at room temperature.
Thickener is not used.	Thickener must be used.
The density of dye solution is low.	The density of dye solution is high.
Generally after dyeing, steaming, and curing are not required.	After printing, steaming and curing is must for fixing the dye to the fabric.
Dyed fabrics are soft to touch.	Printed fabrics are harsh to touch.
Water consumption is high.	Water consumption is low.
Huge time is required for dye application.	Less time is required for printing process.
Liquor ratio is high.	Liquor ratio is less.

3.4 Styles Of Printing

Fabrics can be printed in three different styles namely direct, discharge and resist styles.

3.4.1 Direct Style of Printing

The most common style of printing textile fabric is direct printing. In this method the dye is directly applied onto the fabric. Dyes are used in paste form. It is the simplest and oldest style of printing. It can be done on a

XII TDD_English version CHAPTER 03.indd 35 1/30/2020 4:55:13 PM