

Figure 3.17 Nail Block in Wax for Batik Printing



Figure 3.18 Batik Printed Fabric

Advantage

- Gives an artistic effect to the fabric

Disadvantages

- Very laborious and time consuming process
- Dye has to be applied at a temperature lower than the melting point of wax

3.5.7 Photo Printing

In this method, the fabric is coated with a chemical that is sensitive to light and photographs are printed on the fabric. The results are similar to the photograph printed on the paper. This is a direct style of printing.



Figure 3.19 Photo Printing

3.6 After Treatment Processes of Printed Fabrics

After printing, the fabrics are dried to retain the printed design. It is an essential step to avoid staining of unprinted areas. It prevents bleeding of print paste from the design areas. Drying is followed by steaming which transfer the pigment from print paste to the fabric.

3.6.1 Steaming

In ageing or steaming process, the dyes and chemicals present superficially on the surface of the fabric is transferred into the fabric. The dried printed fabric has pigments or dyes, thickeners such as starch, gum etc. and printing auxiliaries on its surface. Steaming enhances the absorption of dyes or pigments on the fabric. In steaming or ageing, the dried printed fabric is exposed to steam at atmospheric or higher pressure for different time intervals. Steaming can be carried out continuously or batch-wise. When the printed fabric enters the steam chamber, steam condenses to form water

XII TDD_English version CHAPTER 03.indd 43 1/30/2020 4:55:14 PM