- **Maize Starch**

This starch also gives a viscous solution. But it produces undesirable stiffness which is rough to touch. It is cheap and hence can be used after mixing with other starches.

- **Tapioca Starch**

The starch is obtained from roots of cassava plants. For this purpose the roots are dried, sliced and then crushed into pulp with water. It is then washed several times and then dried when the final starch becomes available in the form of lumps which can be ground.

- **Potato Starch**

This starch has largest grains of all the starches. Potato and sweet potato are used. Potato is ground to pulp washed several times and then water is evaporated. It is not a very suitable laundry stiffening agent.

- **Commercial Starch**

Various types of commercial starches are available in the market. These are made by blending two or more different types of starches.

5.3.3.2 Preparation and Application of Starch Solutions

- **Boiling Water Starch**

Preparation of Standard Starch Jelly

Ingredients

Starch	1 tbsp.
Coldwater	2 tbsp.
Borax	1 1/4 tbsp
Wax	1/4 tbsp.
Boiling water	500 ml

Procedure

Mix the starch in cold water to a smooth paste in a basin. Add borax and wax (The function of borax is to make the starch resistant to atmospheric condition. Wax is added for easy ironing of the fabric). Then pour boiling water till the colour of the solution is transparent. A little formalin can be added to this jelly to avoid microbial spoilage.

Application on Fabrics

The standard starch jelly is diluted with cold water depending upon the amount of stiffness required.

- **Cold Water Starch**

Preparation of Starch Solution

Ingredients

Rice starch	1 tbsp
Borax	1/2 tbsp
Turpentine	3 drops.
Coldwater	250 ml
Boiling water	1 tbsp.

Procedure

Dissolve borax in boiling water and mix with cold water. Pour the mixture over starch followed by turpentine. Stir well till a viscous solution is formed. Strain the starch solution through a muslin cloth and use after half an hour.

Application of Starch

This rice starch is used to provide great stiffness.

For Example the cuff and collars, the fabric should be dry before starching. The article is then kneaded and squeezed in the starch solution. It is then rubbed with a muslin cloth to remove excess starch. The article is then wrung out tightly in cold water.

XII TDD_English version CHAPTER 05.indd 67 1/13/2020 3:02:05 PM