



PERSANG ALLOY INDUSTRIES PVT. LTD.

353, GIDC Estate, Waghodia, Dist. Baroda - 391700 Gujarat. Tel.: +91 2668 262718/719. Fax: +91 2668 262556
Email: sales@persangalloy.com Visit us at: www.persangalloy.com

SM-150G, SM-250G, SM-155P AND SM-255P series products, are single-component type epoxy resin adhesives for electronic applications. They are rapid thermal curing adhesive, especially designed for bonding of surface mount devices to PCB prior to wave soldering in the lead-free conditions. Among these, SM-250G and SM-255P are EU RoHS compliant, and meet the environmental and halogen-free requirements. SM-150G and SM-250G are suitable for dispensing applications. SM-155P and SM-255P are suitable for printing processes. Good stable adhesive profiles with high strength.



Specifications of Products	No.	Item	Specifications
	1	Chemical Type	Epoxy Resin
	2	Composition	One-component - requires no mixing
	3	Curing Type	Rapid Thermal Suring
	4	Application	Adhesion between Electronic Components and PCBs
	5	Applications	SM-150G/SM-250G : dispensing process; SM-155P/SM-255P : printing process
	6	Specific Gravity	1.1
	7	Viscosity (5.0 rpm)	SM-150G/SM-250G: 80,000mPa.s; SM-155P/SM-255P:50,000mPa.s
	8	Thixotropy Index	SM-150G/SM-250G: 6.5; SM-155P/SM-255P: 5.0
	9	Storage	6 months (in refrigerator at 2 - 10°C)

Products Features /



Good Anti-slump

- Single component and solvent-free polymer adhesive
- Good thixotropy before curing: no slump
- Can withstand high temperature thermal shock and has a low defect ratio
- Short curing time, high adhesive strength
- No tailing or stringing problems
- Excellent electric insulation and thermal resistance
- Reliable protection of finished electronic products
- Good preservation stability

Process Applications



Adhesive dispensing



Adhesive printing



Component placement and curing

Use Lead free Alloys.

The proclaimed leader for perfect

solders

Pb Free Solder Paste, Bars, Wires, Spheres, Fluxes, Sac Series Paste, Sn/Pb Bars & Solder Balls



Adhesion Property / Shear Test

Shear strength : Average test values for the adhesion between electronic components 1206R and 0805R and the green-paint PCB were taken Test tool: XYZTEC Condor Shear-Tensile Strength Tester at the cure temperature of 150°C for 1.5 minutes. Note : Average values were obtained under the following conditions.



Printing and component placement



Test tools



1206R



Shear test
Shear force-7Kg



0805R



Shear test
Shear force-2.5Kg



0805R

Heat Resistance to Hot Solder Dip Test /

Electronic components 1206R and 0805R were attached to the substrate and then subjected to the hot solder dip test. Standards : IPC SM-817 TM-650 Method 2.4.4.2.1



Component placement and curing



No components were removed after the solder dip test



Visit us at:



Booth No. M9
Hall No. 10

21 to 23, Feb. 2013, Pragati Maidan, New Delhi