


PRODUCTION REPORT

Production Output

Parameter	Value
Target Production (KG/hr)	10.0
Actual Production (KG/hr)	10.0
Production Efficiency (%)	100.0


Production Trend



Line Performance

Parameter	Value
Speed Set (mpm)	142.4
Speed Actual (mpm)	140.39
Average GSM (g/m ²)	76.71
Layflat Width (mm)	227.59
Density (g/cm ³)	0.923

Line Speed Trend



Production Quality

Parameter	Value
Average Thickness (μm)	18.23
Maximum Thickness (μm)	21.1
Minimum Thickness (μm)	14.6
Thickness Deviation (%)	1.28

Layer Contribution

Layer	Avg Thickness (μm)
Layer 1	6.09
Layer 2	6.09
Layer 3	6.09

Winder Summary

Winder	Roll Length Produced (m)
Winder 1	137.0
Winder 2	137.0