

T=410 C: CNT energy-minimization curves, no strain, 400³, dx=0.1 nm

