

# Soil Side Corrosion Calculation for Asset ID h

## Asset Name/ID

h

#### Soil-side base corrosion rate known?

If the soil-side base corrosion rate not known, CRSB=0.13 mm/yr will be assumed for a typical AST under average conditions defined in Table 2.B.14.3 API 581

No

# Please include measured or estimated soil-side corrosion rate, CRSB

Measured or estimated soil-side corrosion rate in mm/yr

0

## **CRSB** for calculations

0.13

## Soil resistivity

Select soil resistivity (ohm-cm). If not known, then a moderately Corrosive Soil is assumed for an ASTs with RPBs Corrosive, resistivity 500 to 1,000 (ohm-cm)

## **FSR**

The soil-side corrosion rate correction factor for soil conditions

# **AST Pad Type**

Select the type of pad or foundation that the AST rests upon High resistivity low chloride sand

## **FPA**

The soil-side corrosion rate correction factor for AST pad type 0.7

## **AST Drainage**

Select the type of drainage when AST exposed to rainwater or storms Storm water collects at AST base

## **FTD**

The soil-side corrosion rate correction factor for drainage 2

## **CP** at bottom

Select the type of cathodic protection at the AST bottom Yes not per API 651



# Soil Side Corrosion Calculation for Asset ID h

## **FCP**

The soil-side corrosion rate correction factor for CP 0.66

## **Bottom type**

Select the AST Bottom Type RPB per API 650

#### **FTB**

The soil-side corrosion rate correction factor for AST bottom type 1

# **Operating Temperature range**

Selection in (°F) Temp  $\leq 24$ 

#### **FST**

The soil-side corrosion rate correction factor for temperature 1

## Corrosion Rate soil side MM/YR

0.15015

# **Corrosion Rate soil side MPY**

5.9114055

# **Corrosion Damage Morphology**

Localized thinning

# Remaining Life and Next Inspection Date Calculation

# **Corrosion Rate (overwritten)**

Corrosion Rate Overwritten by the user No

## **Material Thickness Units**

Units of the thickness in

#### **T** Actual

Current thickness of the material



# Soil Side Corrosion Calculation for Asset ID h

0.9

# T Required

 $\begin{array}{l} \text{Minimum required thickness for safe operation} \\ \textbf{0.85} \end{array}$ 

# **Selected Date**

Start date of the remaining life Tue Apr 01 2025

# Remaining Life years/Retirement date

8.46 / Sat Sep 17 2033