



PRODUCT DATA SHEET

TECHNOFLUID RUST PREVENTIVE OIL 906

Commercial / Pack Name: RUST PREVENTIVE OIL 906

Product Description

- TECHNOFLUID Rust Preventive Oil 906 is a solvent-based, oil-type rust preventive fluid formulated to provide effective corrosion protection to ferrous metal components.
- Forms a thin, uniform protective film that displaces moisture and shields metal surfaces from rust and oxidation.
- Designed for short- to medium-term indoor and limited outdoor corrosion protection.
- Exhibits excellent water displacement characteristics, ensuring protection even in humid conditions.
- Easy to apply and remove, making it suitable for post-manufacturing and storage protection.

Key Performance Benefits

- Provides reliable protection against rust and corrosion during storage and transportation.
- Excellent water displacement prevents moisture-induced corrosion.
- Thin, non-sticky film ensures clean handling of components.
- Does not stain or attack metal surfaces.
- Easy removal using petroleum solvents or alkaline cleaners.
- Reduces rejection, rework, and maintenance costs.

Applications

- Recommended for rust prevention of:
 - Automotive and engineering components
 - Machined parts and assemblies
 - Gears, bearings, and metal tools
 - Fabricated and finished ferrous components
- Suitable for use in:
 - Manufacturing plants, Warehouses & storage facilities and Inter-process & inter-plant transportation

Typical Uses

- Temporary corrosion protection during storage and shipment.
- Protection of metal components awaiting assembly or dispatch.
- Indoor protection up to several months and short-term outdoor exposure (as per conditions).

Operating Characteristics

- Leaves a uniform, protective oil film with good coverage.
- Compatible with commonly used metals and alloys
- Can be applied by dipping, spraying, or brushing.

Typical Specifications

Characteristics	Test Method	Typical Figures
Appearance	Visual	Clear / Light Brown
Film Type	—	Thin, oily protective film
Base Oil Type	—	Mineral
Solvent Type	—	Hydrocarbon solvent
Density @ 15°C, g/ml	ASTM D4052	0.830 – 0.860
Kinematic Viscosity @ 40°C, cSt	ASTM D445	6 – 10
Flash Point (COC), °C	ASTM D92	≥ 65
Pour Point, °C	ASTM D97	-6
Water Displacement	ASTM D95	Excellent
Rust Prevention (Humidity Cabinet, hrs)	ASTM D1748	≥ 72
Copper Corrosion (3 hrs @ 100°C)	ASTM D130	1a
Neutralization Value, mg KOH/g	ASTM D664	≤ 0.05
Film Thickness, microns	—	2 – 5
Removability	—	Easily removable by solvent/alkaline cleaner
Protection Period (Indoor)	—	Up to 6 months
Protection Period (Outdoor – covered)	—	Up to 3 months

