



PRODUCT DATA SHEET

RUBBER PROCESS OIL

Commercial / Pack Name: RPO 710 / ELASTOL 245 / ELASTOL 541

Product Description

- Premium rubber process oils manufactured from highly refined mineral base oils.
- Developed to improve processing efficiency and compound dispersion in rubber manufacturing.
- Excellent compatibility with natural and synthetic rubber compounds.
- Provides good thermal stability, low volatility and consistent processing performance.
- Available in RPO 710, ELASTOL 245 and ELASTOL 541 grades.

Key Performance Benefits

- Improves filler dispersion and processability.
- Enhances flexibility and finished product quality.
- Excellent oxidation and thermal stability.
- Low aromatic content and consistent viscosity.
- Reduces energy consumption during mixing and processing.

Applications

- Tyre and tube manufacturing.
- Rubber hoses, belts, footwear and moulded rubber goods.
- Automotive rubber components.
- General natural and synthetic rubber compounding.

INDUSTRY PERFORMANCE CHARACTERISTICS

- Excellent compatibility with rubber polymers
- Good thermal stability
- Low volatility
- Consistent processing characteristics
- Improved compound flow

Typical Characteristics

Characteristics	RPO 710	ELASTOL 245	ELASTOL 541
Appearance	Dark green	Yellow clear	Yellow clear
Density @29.5°C	0.940	0.865	0.850
K.V @40°C cSt	70	30-32	18-23
Flash Point (COC) °C	220	210	175
Pour Point °C	-6	-3	-3
Aniline Point °C	90	95	100

RUBBER PROCESS OIL

Commercial / Pack Name: RPO 710 / ELASTOL 245 / ELASTOL 541

Product Description

- Premium rubber process oils manufactured from highly refined mineral base oils.
- Designed to improve processing, filler dispersion and finished rubber properties.
- Excellent compatibility with natural and synthetic rubber compounds.
- Good thermal stability and low volatility for consistent processing.
- Available in RPO 710, ELASTOL 245 and ELASTOL 541 grades.

Key Performance Benefits

- Improves processability and compound flow.
- Enhances filler dispersion and flexibility.

- Consistent viscosity and excellent thermal stability.
- Low aromatic loss during processing.
- Reliable performance for a wide range of rubber products.

Applications

- Tyres and tubes.
- Footwear and conveyor belts.
- Rubber hoses and moulded goods.
- Automotive rubber components.
- General natural and synthetic rubber compounding.

INDUSTRY PERFORMANCE CHARACTERISTICS

- Excellent compatibility with rubber polymers
- Consistent processing performance
- Low volatility
- Good thermal stability
- Improved filler dispersion

Typical Characteristics

Characteristics	RPO 710	ELASTOL 245	ELASTOL 541
Appearance	Brown	Brown	Brown
Density @29.5°C	0.890	0.900	0.905
K.V @40°C (cSt)	70	245	541
Aniline Point (°C)	90	95	100
Copper Corrosion (100°C, 3 h)	1a	1a	1a
Asphaltenes (% wt)	Nil	Nil	Nil
Polar Compounds (% wt)	<10	<10	<10
Aromatics (% wt)	28	22	18
Saturates (% wt)	72	78	82

Flash Point (COC) °C	220	245	260
Pour Point (°C)	-6	-6	-3