



PRODUCT DATA SHEET

PROCESS OIL – TECHNOFLUID PVC OIL

Commercial / Pack Name: PVC OIL

Product Description

- TECHNOFLUID PVC Oil is a high-quality process oil specially formulated for use in PVC compounding and plastic processing applications.
- Manufactured from carefully selected, highly refined base oils to ensure excellent compatibility with PVC resins and additives.
- Provides effective plasticizing action, enhancing processing efficiency and finished product quality.
- Exhibits good thermal stability and low volatility, making it suitable for high-temperature processing operations.
- Designed to deliver consistent performance in both rigid and flexible PVC formulations.

Key Performance Benefits

- Improves processability and flow characteristics during mixing, extrusion, and molding.
- Enhances surface finish and appearance of finished PVC products.
- Provides uniform dispersion of fillers, stabilizers, and pigments.
- Maintains excellent thermal stability, reducing degradation during processing.
- Low odor and light color improve working environment and product aesthetics.
- Helps reduce processing defects such as brittleness and poor finish.

Applications

- Recommended for use in:
 - PVC compounding and processing
 - Extrusion and injection molding of PVC products
 - Manufacturing of PVC pipes, profiles, cables, sheets, and films
 - Footwear, hoses, and flexible PVC products
- Suitable for use in both rigid and plasticized PVC formulations, as per process requirements.

Typical Uses

- As a process aid and extender oil in PVC formulations.
- Applications requiring improved flexibility, surface finish, and processing efficiency.
- Plastic processing operations demanding stable and consistent oil performance.

Operating Characteristics

- Good compatibility with PVC resins, stabilizers, and commonly used additives.
- Maintains stable viscosity during processing cycles.
- Compatible with standard processing equipment and materials.

Typical Specifications

Characteristics	Test Method	Typical Figures
Appearance	Visual	Clear & Bright
Colour	ASTM D1500	≤ 2.0
Base Oil Type	—	Highly Refined Mineral
Aromatic Content	—	Low
Density @ 15°C, g/ml	ASTM D4052	0.870 – 0.890
Kinematic Viscosity @ 40°C, cSt	ASTM D445	80 – 120
Kinematic Viscosity @ 100°C, cSt	ASTM D445	8 – 11
Viscosity Index	ASTM D2270	≥ 95
Flash Point (COC), °C	ASTM D92	≥ 210
Pour Point, °C	ASTM D97	-6
Sulphur Content	ASTM D4294	Nil
Ash Content, % wt	ASTM D482	≤ 0.01
Copper Corrosion (3 hrs @ 100°C)	ASTM D130	1a
Oxidation Stability	ASTM D943	Excellent
Volatility	ASTM D972	Low
Compatibility with PVC	In-house	Excellent
Odour	—	Mild

