



PRODUCT DATA SHEET

GREASE – TECHNOFLUID LITHIUM COMPLEX GREASE

Commercial / Pack Name: LITHIUM COMPLEX GREASE (RED GEL / BLUE GEL / 222)

Product Description

- TECHNOFLUID Lithium Complex Grease is a premium high-temperature, heavy-duty grease formulated with lithium complex thickener and selected base oils.
- Designed to withstand high temperatures, heavy loads, and severe operating conditions.
- Provides superior mechanical stability and resistance to water washout.
- Suitable for demanding automotive and industrial applications requiring extended grease life.

Key Performance Benefits

- High dropping point allows operation at elevated temperatures.
- Excellent load-carrying and extreme pressure properties.
- Superior resistance to water washout and contamination.
- Outstanding oxidation stability minimizes hardening and deposit formation.
- Protects against wear, rust, and corrosion even under severe conditions.
- Extends re-lubrication intervals and component life.

Applications

Recommended for lubrication of:

- Wheel bearings (disc brake equipped vehicles)
- High-speed and high-temperature bearings
- Electric motors and industrial machinery
- Steel, cement, and rolling mill equipment
- Construction and mining machinery

Suitable for both automotive and heavy-duty industrial use.

Typical Uses

- Bearings operating under high temperature and heavy load conditions.
- Equipment exposed to water, vibration, and shock loads.

- Applications requiring long grease life and reduced maintenance.

Operating Characteristics

- Excellent pumpability despite high thickener content.
- Compatible with commonly used seals and elastomers.
- Provides consistent lubrication across wide temperature ranges.

Typical Characteristics

Characteristics	Test Method	RED GEL	BLUE GEL	222 (Blue Gel – Premium)
Appearance	Visual	Smooth, gel type	Smooth, gel type	Smooth, gel type, comparatively softer
Colour	Visual	Red	Blue	Blue
Thickener Type	—	Lithium Complex	Lithium Complex	Lithium Complex
Base Oil Type	—	Mineral	Mineral	Mineral
NLGI Grade	ASTM D217	2	2	2
Worked Penetration (60 strokes), 0.1 mm	ASTM D217	265 – 295	265 – 295	265 – 295
Drop Point, °C (Min)	ASTM D2265	≥ 235	≥ 245	≥ 250
Base Oil Viscosity @ 40°C, cSt	ASTM D445	180 – 220	180 – 220	180 – 220
Four Ball Weld Load, kg (Min)	ASTM D2596	315	320	330
Wear Scar Dia, mm (Max)	ASTM D2266	0.45	0.45	0.40
Copper Corrosion (24 hrs @ 100°C)	ASTM D4048	1a	1a	1a
Water Washout @ 79°C, % loss (Max)	ASTM D1264	≤ 3	≤ 3	≤ 2

Rust Prevention	ASTM D1743	Pass	Pass	Pass
Mechanical Stability (100,000 strokes)	ASTM D217	Excellent	Excellent	Excellent
Operating Temperature Range, °C	—	-20 to 180	-20 to 190	-20 to 200