



PRODUCT DATA SHEET

GREASE – TECHNOFLUID LITHIUM GREASE AP3 & APLR

Commercial / Pack Name: LITHIUM GREASE AP3 / LITHIUM GREASE APLR

Product Description

- TECHNOFLUID Lithium Grease is a high-performance, multi-purpose grease formulated using high-quality mineral base oils and lithium soap thickener.
- Designed to provide excellent lubrication and protection over a wide range of operating temperatures.
- Exhibits good mechanical stability and resistance to oxidation, ensuring consistent performance during extended service.
- Suitable for both automotive and industrial applications requiring reliable bearing lubrication.

Key Performance Benefits

- Excellent anti-wear properties reduce friction and bearing wear.
- Good thermal and oxidation stability extends grease life.
- Provides effective rust and corrosion protection.
- Good water resistance ensures dependable lubrication in moderately wet conditions.
- Maintains consistency under mechanical stress.
- Reduces maintenance frequency and downtime.

Applications

Recommended for lubrication of:

- Wheel bearings
- Electric motor bearings
- Plain and rolling bearings
- Automotive chassis and joints
- Industrial machinery bearings

Suitable for low to moderate speed and load conditions.

Typical Uses

- Automotive and commercial vehicle lubrication.
- General industrial greasing applications.
- Bearings operating under moderate temperatures and loads.

Operating Characteristics

- Good pumpability in centralized lubrication systems.
- Compatible with commonly used bearing materials and seals.
- Stable structure ensures long service intervals

Typical Characteristics

Characteristics	Test Method	TECHNOFLUID AP3	TECHNOFLUID APLR
Appearance	Visual	Smooth, fibrous	Smooth, fibrous
Colour	Visual	Yellowish White	Dark Green
Thickener Type	—	Lithium Soap	Lithium Soap
Base Oil Type	—	Mineral	Mineral
NLGI Grade	ASTM D217	3	3
Worked Penetration (60 strokes), 0.1 mm	ASTM D217	220 – 250	220 – 250
Drop Point, °C (Min)	ASTM D2265	≥ 180	≥ 180
Base Oil Viscosity @ 40°C, cSt	ASTM D445	150 – 220	150 – 220
Four Ball Weld Load, kg (Min)	ASTM D2596	250	250
Wear Scar Dia, mm (Max)	ASTM D2266	0.50	0.50
Copper Corrosion (24 hrs @ 100°C)	ASTM D4048	1a	1a

Water Washout @ 79°C, % loss (Max)	ASTM D1264	≤ 4	≤ 4
Rust Prevention	ASTM D1743	Pass	Pass
Mechanical Stability (Worked, 100k strokes)	ASTM D217	Good	Good
Operating Temperature Range, °C	—	-20 to 140	-20 to 140