



## PRODUCT DATA SHEET

### TECHNOFLUID ROLL PERFECT 22

(NEAT COLD ROLLING OIL)

*Commercial / Pack Name: ROLL PERFECT 22*

#### Product Description

- TECHNOFLUID Roll Perfect 22 is a **premium-quality neat cold rolling oil** specially formulated for **high-speed cold rolling operations**.
- Manufactured using **highly refined mineral base oils** and **selected lubricity-enhancing additives**.
- Designed to provide excellent **lubrication, surface finish, and roll protection** during cold rolling of metals.
- Exhibits **low viscosity and low volatility**, ensuring efficient heat dissipation and reduced oil consumption.
- Suitable for use where **water dilution is not required**.

#### Key Performance Benefits

- Superior **lubricity** improves roll bite and reduces rolling forces.
- Excellent **surface finish** and reduced strip defects.
- Low volatility minimizes oil losses and smoke generation.
- Good **thermal and oxidation stability** ensures longer oil life.
- Protects rolls and workpieces against **wear and corrosion**.
- Ensures clean rolling conditions with minimal residue.

#### Applications

- Recommended for:
  - **Cold rolling of steel strips and sheets**
  - **Precision rolling operations**
- Suitable for **carbon steel, low-alloy steel**, and selected non-ferrous metals.
- Ideal for **high-speed rolling mills** and **recirculating oil systems**.

## Typical Characteristics

| Characteristics                  | Test Method   | Typical Figures        |
|----------------------------------|---------------|------------------------|
| Appearance                       | Visual        | Clear & Bright         |
| Colour                           | ASTM D1500    | $\leq 2.0$             |
| Base Oil Type                    | —             | Highly Refined Mineral |
| Oil Type                         | —             | Neat (Undiluted)       |
| Density @ 15°C, g/ml             | ASTM D4052    | 0.860                  |
| Kinematic Viscosity @ 40°C, cSt  | ASTM D445     | 20 – 24                |
| Kinematic Viscosity @ 100°C, cSt | ASTM D445     | 4.0 – 4.8              |
| Viscosity Index                  | ASTM D2270    | $\geq 95$              |
| Flash Point (COC), °C            | ASTM D92      | $\geq 200$             |
| Pour Point, °C                   | ASTM D97      | -6                     |
| Copper Corrosion (3 hrs @ 100°C) | ASTM D130     | 1a                     |
| Oxidation Stability              | ASTM D943     | Excellent              |
| Volatility                       | ASTM D972     | Low                    |
| Anti-Wear Properties             | ASTM D4172    | Good                   |
| Rust Protection                  | IP / In-house | Pass                   |
| Residue Formation                | In-house      | Minimal                |