

安徽威尔泰克机电设备有限公司
Well-Tanker (Anhui) M&E Equipment Co.,Ltd.

外观及几何尺寸检查报告

Visual/Dimension Inspection Report

产品编号: P-2362-001~P-2362-015

产品图号: 20980145-083-001 Rev.3

Serial NO.

Product Drawing NO.

检查项目 Exam Item		要求尺寸 Design Size	实测尺寸 Actual Size	检查项目 Exam Item		要求尺寸 Design Size	实测尺寸 Actual Size
壳体尺寸 Body Size	内径 I.D	450mm	449~451mm	筒体圆度 Out-Of-Roundness of shell		≤4.5mm	2.1~3.2mm
	长度 Length	1161mm	1160~1162mm	筒体直线度 Straightness of shell		/	/
容积 Volume	130L/23L			纵缝最大允许棱角度 MAX. permitted peaking in longitudinal welds		≤2.6mm	0.5~1.4mm
壳体壁厚 Wall Thickness	封头 Head	≥5.4mm	5.5~5.7mm	焊缝对接错边量 MAX. offset at edges of weld seam	环缝 Circum seam	≤2.5mm	0.6~1.6mm
	筒体 Shell	≥5.75mm	5.8~5.9mm		纵缝 Longi Seam	≤2.5mm	0.3~0.9mm
封头内表面最大间隙 MAX. clearance value of head internal surface	So≤1.25%Di	5.6mm	2.1~3.7mm	焊缝最大咬边深度 MAX. Under Cut Depth Of Welds		≤0.5mm	OK合格
	Si≤0.625%Di	2.8mm	0.9~1.7mm				
封头直边最大纵向褶皱深度 MAX. longitudinal buckling depth of head skirt		无	OK合格	焊缝余高 Reinforcement of weld seam		纵缝 0~2.5mm	0.3~0.9mm
						环缝 0~3.0mm	1.1~2.2mm
罐体内外表面质量 Inside &Outside Surfaces Quality		符合图纸及标准	OK合格	焊缝表面质量 Welds surface quality		符合图纸及标准	OK合格

检验结论:合格

SGS

WITNESSED / REVIEWED

NOTED FOR INFORMATION ONLY

SGS-CHINA STANDARDS TECHNICAL SERVICES CO., LTD.

IND023

检查员: 郑如英
Examiner:

日期: 2024.1.6
Date:

审核: 孙
Reviewed by

日期: 2024.1.6
Date:

安徽威尔泰克机电设备有限公司
Well-Tanker (Anhui) M&E Equipment Co.,Ltd.

外观及几何尺寸检查报告

Visual/Dimension Inspection Report

产品编号: P-2362-016~P-2362-025
Serial NO.

产品图号: 20980145-083-001 Rev.3
Product Drawing NO.

检查项目 Exam Item		要求尺寸 Design Size	实测尺寸 Actual Size	检查项目 Exam Item		要求尺寸 Design Size	实测尺寸 Actual Size
壳体尺寸 Body Size	内径 I.D	450mm	449~451mm	筒体圆度 Out-Of-Roundness of shell		≤4.5mm	3.1~3.7mm
	长度 Length	1161mm	1160~1162mm	筒体直线度 Straightness of shell		/	/
容积 Volume	130L/23L			纵缝最大允许棱角度 MAX. permitted peaking in longitudinal welds		≤2.6mm	0.5~1.3mm
壳体壁厚 Wall Thickness	封头 Head	≥5.4mm	5.5~5.7mm	焊缝对接错边量 MAX. offset at edges of weld seam	环缝 Circum seam	≤2.5mm	0.6~1.7mm
	筒体 Shell	≥5.75mm	5.8~6.0mm		纵缝 Longi Seam	≤2.5mm	0.6~1.6mm
封头内表面最大间隙 MAX. clearance value of head internal surface	So≤1.25%Di	5.6mm	1.1~1.9mm	焊缝最大咬边深度 MAX. Under Cut Depth Of Welds		≤0.5mm	OK合格
	Si≤0.625%Di	2.8mm	0.3~0.8mm				
封头直边最大纵向褶皱深度 MAX. longitudinal buckling depth of head skirt		无	OK合格	焊缝余高 Reinforcement of weld seam		纵缝 0~2.5mm	0.3~1.1mm
						环缝 0~3.0mm	1.2~1.9mm
罐体内外表面质量 Inside &Outside Surfaces Quality		符合图纸及标准	OK合格	焊缝表面质量 Welds surface quality		符合图纸及标准	OK合格
检验结论: OK合格							

SGS

WITNESSED
REVIEWED

NOTED FOR INFORMATION ONLY

SGS-CSI STANDARDS TECHNICAL

652100500-100-11000

检查员: 郑志英
Examiner:

日期: 2024.1.16
Date:

审核: 郑志英
Reviewed by

日期: 2024.1.16
Date: