



No.:SST20001255 Date.:2020-05-05 Page 1 of 4

Applicant: Dongguan Chaosheng Plastic Hardware Co.,Ltd.

Address: 1/F,E Building,Longsheng High-tech Industrial Zone,Lundu Road,Qisha Village,Shatian

Town, Dongguan City, 523997, Guangdong Province, China.

Report on the submitted sample said to be:

Material description: Face Shield

Style/ Model No.: N/A P/O No./ Lot No.: N/A
Order No.: N/A Material: N/A
Color: N/A Test Request Age: N/A

Color: N/A Test Request Age : N/A

Manufactory: Dongguan Chaosheng Plastic Buyer: N/A

Hardware Co.,Ltd.

Country of Origin: Dongguan China Country of Export: N/A

Sample received date: May 4,2020

Sample test period: From May 4,2020 to May 5,2020

SUMMARY OF TEST RESULT(S)

| Test Item(s) | Conclusion | Remark | |
|--------------------|------------|---------------|--|
| Phthalates Content | 25' 45' | See Next Page | |
| Total lead content | | See Next Page | |

******FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)******

Signatories:

John Yue Lab Manager









No.:SST20001255 Date.:2020-05-05 Page 2 of 4

Result:

Phthalates Content

Test Method: With reference to CPSC-CH-C1001-09.4, Sample was extracted with organic solvent, Analysis was performed by Gas Chromatograph Mass Spectrometer(GC-MS).

| Test Item(s) | Unit | Result | |
|-----------------------------------|-------|--------|-----|
| | | 001 | 002 |
| Dibutylphthalate(DBP) | mg/kg | ND | ND |
| Butylbenzylphthalate(BBP) | mg/kg | ND | ND |
| Di-(2-ethylhexyl)-phthalate(DEHP) | mg/kg | ND | ND |
| Di-iso-nonylphthalate(DINP) | mg/kg | ND | ND |
| Di-iso-decylphthalate(DIDP) | mg/kg | ND | ND |
| Di-n-octylphthalate(DNOP) | mg/kg | ND | ND |
| Di-n-hexyl phthalate(DnHP) | mg/kg | ND | ND |
| Di-isobutyl phthalate(DIBP) | mg/kg | ND | ND |

Note:

ND = Not detected(<DL)

% = percent


1000 mg/kg = 0.1 %

mg/kg = milligram(s) per kilogram Detection Limit (mg/kg) : Each 50

Specimen Description:

001: Blue plastic

002: Transparent plastic







No.:SST20001255 Date.:2020-05-05 Page 3 of 4

Result:

Total lead content

Test Method: With reference to CPSC-CH-E1003-09.1(Coatings)/CPSC-CH-E1002-08.3(Nonmetal) /CPSC-CH-E1001-08.3(Metal), Sample digestion by acid, Analysis was performed by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES)/Atomic Absorption Spectrometry (AAS).

| Client's Limit: | 100 mg/kg | | | |
|-----------------|-----------|--|--|--|
|-----------------|-----------|--|--|--|

| Specimen No. | Result[mg/kg] | Conclusion |
|--------------|---------------|------------|
| 001 | ND | - |
| 002 | ND ND | 3 - |

Note:

ND = Not detected(<DL)
mg/kg = milligram(s) per kilogram

Detection Limit (mg/kg): 10

Specimen Description:

001: Blue plastic

002: Transparent plastic





No.:SST20001255 Date.:2020-05-05

Photograph of Sample

Page 4 of 4



*** End of Report ***

The test report is considered invalidated without both signature and specialized stamp, The result(s) shown in this test report refer only to the sample(s) tested. Without written approval of SST, this test report shall not be copied except in full .Detailed description are available at the website http://www.sst-test.com.

