

Test Request Info		
Request Number	R-0015288	Test Purpose RTD neues Umformkonzept - Streifenlänge 1335mm
Request Type	Internal	
Classification	Engineering	
Test Requester	Achim Boos	
Requesting Location	KON - Konigswinter, Germa	

Test Number	Test Type
R-0015288-C-1	Cornering
R-0015288-R-2	Radial
R-0015288-B-3	Biaxial
R-0015288-C-5	Cornering
R-0015288-R-6	Radial

Test Number	Test Type

Test Number	Test Type

Test Number	Test Type

Final Review

Completed By	Martin Schlupek
--------------	-----------------

Completed On	05/08/2023
--------------	------------

	Performance Lab				
	Lab Test Summary				
	Plant:	KON - Königswinter, Germany	Report Number:	R-0015288	

Test Request Info		
Request Number	R-0015288	Test Purpose
Request Type	Internal	
Classification	Engineering	
Test Requester	Achim Boos	
Requesting Location	KON - Königswinter, Germa	

Charts and Pictures
Not Available

Charts and Pictures
Not Available

KON Lab
The information presented in this document refer exclusively to the object it featured not be extended to any other items.
This document may only be reproduced in their entirety, partial reproductions must be previously authorized by the Performance Lab at Maxion Wheels.

Test Request Info		
Request Number	R-0015288	Test Purpose RTD neues Umformkonzept - Streifenlänge 1335mm
Request Type	Internal	
Classification	Engineering	
Test Requester	Achim Boos	
Requesting Location	KON - Konigswinter, Germa	

Test Run Info		Steel Traceability Info		Specification	Specified	Used
Test Number	R-0015288-B-3	Rim Coil Code	-	Collective Load (KN)	-	-
Sample Number	R-0015288-S-3	Rim Thickness (mm)	5.1	Stud	-	-
Sample Received Date	04/06/2023	Disc Coil Code	-	Nut	-	-
Maxion Part Number	292100300001_BT	Disc Thickness (mm)	13.5	Flange	E-0000221	
Customer Part Number		Press Fit (mm)	-	Min. Distance		
Customer	Daimler	Assembly Date	2023-04-05 04:00:00.			
Standard		Production Code	-			

Started Date	04/06/2023	Finished Date	04/18/2023	Duration	12
--------------	------------	---------------	------------	----------	----

Final	Specified	Inspection	Wheel Outside	Wheel Inside
Distance (Km)		4,780		
Min Torque (Nm)	-			
Max Torque (Nm)	-			
Torque Loss (%)	-	-		
Speed (Km/h)	-	-		
Machine Code	M-0000003 Biaxial 21352_ZWARP_02			
Crack Codes	91690-1-25-25			
Inspected by	Tobias Simon			
Remarks	Cracks in welding; airloss			

Remarks
Test failed due to cracks in welding; welding itself with poor quality

	Performance Lab				
	Lab Test Run Cornering				
	Plant:	KON - Konigswinter, Germany	Report Number:	R-0015288	

Test Request Info		
Request Number	R-0015288	Test Purpose RTD neues Umformkonzept - Streifenlänge 1335mm
Request Type	Internal	
Classification	Engineering	
Test Requester	Achim Boos	
Requesting Location	KON - Konigswinter, Germa	

Test Run Info		Steel Traceability Info		Specification	Specified	Used
Test Number	R-0015288-C-1	Rim Coil Code	-	Load (Nm)	32,030	32030
Sample Number	R-0015288-S-1	Rim Thinckness (mm)	5.1	Stud		
Sample Received Date	04/06/2023	Disc Coil Code	-	Nut		
Maxion Part Number	292100300001_BTD	Disc Thinckness (mm)	13.5	Flange	E-0000221	
Customer Part Number		Press Fit (mm)	-	Min. Cycles	250,000	
Customer	Daimler	Assembly Date	2023-04-05 04:00:			
Standard		Production Code	-			

Started Date	04/06/2023	Finished Date	04/12/2023	Duration	6
--------------	------------	---------------	------------	----------	---

Final	Specified	Inspection	Wheel Outside	Wheel Inside
Cycles	250,000	1,150,194		
Min Torque (Nm)	-			
Max Torque (Nm)	-			
Torque Loss (%)	-	-		
Deflection	-	-		
Frequency (RPM)	-			
Machine Code	M-0000016 CFT 8183_CFT_06			
Crack Codes	91200-3-80-100			
Inspected by	Michel Lenzen			
Remarks	No remarks			

Remarks
No remarks

	Performance Lab				
	Lab Test Run Cornering				
	Plant:	KON - Konigswinter, Germany	Report Number:	R-0015288	

Test Request Info		
Request Number	R-0015288	Test Purpose RTD neues Umformkonzept - Streifenlänge 1335mm
Request Type	Internal	
Classification	Engineering	
Test Requester	Achim Boos	
Requesting Location	KON - Konigswinter, Germa	

Test Run Info		Steel Traceability Info		Specification	Specified	Used
Test Number	R-0015288-C-5	Rim Coil Code	-	Load (Nm)	21,350	21350
Sample Number	R-0015288-S-5	Rim Thinckness (mm)	5.1	Stud		
Sample Received Date	04/06/2023	Disc Coil Code	-	Nut		
Maxion Part Number	292100300001_BTD	Disc Thinckness (mm)	13.5	Flange	E-0000221	
Customer Part Number		Press Fit (mm)	-	Min. Cycles	2,000,000	
Customer	Daimler	Assembly Date	2023-04-05 04:00:			
Standard		Production Code	-			

Started Date	04/13/2023	Finished Date	05/03/2023	Duration	20
--------------	------------	---------------	------------	----------	----

Final	Specified	Inspection	Wheel Outside	Wheel Inside
Cycles	2,000,000	12,028,312		
Min Torque (Nm)	-	650		
Max Torque (Nm)	-	650		
Torque Loss (%)	-	-		
Deflection	-	-		
Frequency (RPM)	-	-		
Machine Code	M-0000016 CFT 8183_CFT_06			
Crack Codes	No cracks			
Inspected by	Tobias Boeller			
Remarks	No remarks			

Remarks
No remarks

Test Request Info		
Request Number		Test Purpose
Request Type		
Classification		
Test Requester		
Requesting Location		

Test Run Info				Specification	Specified	Used
Test Number				Screw		
Sample Number				Tire		
Sample Received Date				Pressure (kPa)		
Maxion Part Number				Min Torque (Nm)		
Customer Part Number				Max Torque (Nm)		
Customer				Max Torque (Nm)		

Final	Specified	Inspection	Wheel Outside	Wheel Inside
Angle (°)				
Height (m)				
Drop Mass (kg)				
Pressure Loss?				
Machine Code				
Crack Codes				
Inspected by				
Remarks				

Remarks

	Performance Lab			
	Lab Test Run Radial			
	Plant:	KON - Konigswinter, Germany	Report Number:	

Test Request Info		
Request Number	R-0015288	Test Purpose RTD neues Umformkonzept - Streifenlänge 1335mm
Request Type	Internal	
Classification	Engineering	
Test Requester	Achim Boos	
Requesting Location	KON - Konigswinter, Germa	

Test Run Info		Steel Traceability Info		Specification	Specified	Used
Test Number	R-0015288-R-2	Rim Coil Code		Radial Load (N)	86,300	86300
Sample Number	R-0015288-S-2	Rim Thickness (mm)	5.1	Axial Load (N)	-	-
Sample Received Date	04/06/2023	Disc Coil Code		Stud	-	-
Maxion Part Number	292100300001_BT	Disc Thickness (mm)	13.5	Nut	-	-
Customer Part Number		Press Fit (mm)		Tire	-	-
Customer	Daimler	Assembly Date	04/05/2023	Pressure (kPa)	-	-
Standard		Production Code		Flange	E-0000221	
				Min. Cycles	500,000	

Started Date	04/06/2023	Finished Date	04/12/2023	Duration	6
--------------	------------	---------------	------------	----------	---

Final	Specified	Inspection	Wheel Outside	Wheel Inside
Cycles	500,000	831,300		
Min Torque (Nm)				
Max Torque (Nm)				
Torque Loss (%)	-	-		
Machine Code	M-0000010 RFT 8154_RFT_02			
Crack Codes	91610-2-15-25,91301-6-3-20			
Inspected by	Tobias Simon			
Remarks	No remarks			

Remarks
No remarks

Test Request Info		
Request Number	R-0015288	Test Purpose RTD neues Umformkonzept - Streifenlänge 1335mm
Request Type	Internal	
Classification	Engineering	
Test Requester	Achim Boos	
Requesting Location	KON - Königswinter, Germa	

Test Run Info		Steel Traceability Info		Specification	Specified	Used
Test Number	R-0015288-R-6	Rim Coil Code		Radial Load (N)	86,300	86300
Sample Number	R-0015288-S-6	Rim Thinckness (mm)	5.1	Axial Load (N)	-	-
Sample Received Date	04/21/2023	Disc Coil Code		Stud	-	-
Maxion Part Number	292100300001_BT	Disc Thinckness (mm)	13.5	Nut	-	-
Customer Part Number		Press Fit (mm)		Tire	-	-
Customer	Daimler	Assembly Date	04/05/2023	Pressure (kPa)	-	-
Standard		Production Code		Flange	E-0000221	
				Min. Cycles	500,000	

Started Date	04/21/2023	Finished Date	04/29/2023	Duration	8
--------------	------------	---------------	------------	----------	---

Final	Specified	Inspection	Wheel Outside	Wheel Inside
Cycles	500,000	956,700		
Min Torque (Nm)				
Max Torque (Nm)				
Torque Loss (%)	-	-		
Machine Code	M-0000010 RFT 8154_RFT_02			
Crack Codes	91690-1-25-25			
Inspected by	Tobias Simon			
Remarks	No remarks			

Remarks
No remarks