

Production

Construction exterior material tape	Construction interior material tape	Drawing tape
Tape for process	General surface protection tape	Professional solutions




General **surface protection** tape

스테인리스 스틸, 도장강판, 플라스틱사출물의 표면보호용 테이프로써 청색과 투명의 PE 소재 필름을 사용하였으며 부착성이 우수한 제품입니다. 투명과 청색 테이프는 피착제의 외관을 쉽게 확인할 수 있으며, 판재에 부착하여 공정 및 운송중에 표면순상을 막아줍니다. 다양한 표면에 부착하여 사용이 가능하도록 제조되었으며 작업 후 박리가 용이하고 제거 후 잔류물이 남지 않습니다.



SGE-103



용도 표면 보호용, 드로잉 가공용 - 전자 제품 (가스 레인지, 전기 밥솥, 세탁기)

피착재 스테인리스 스틸 (No.8, BA)

· 테이프구조



[PDF download](#)

SGE-123



용도 표면 보호용, 드로잉 가공용 - 전자 제품 (전자 레인지)

피착재 스테인리스 스틸 (No.8, BA, No.4)

· 테이프구조



[PDF download](#)

점착력 (gf/25mm)	필름종류	폭(mm)	길이(m)	두께(mm)	인장강도 (kgf/cm ²)	신율(%)	점착력 (gf/25mm)	필름종류	폭(mm)	길이(m)	두께(mm)	인장강도 (kgf/cm ²)	신율(%)
10	Transparent PE	1000/1219/ 1524	2000	0.05	MD/TD 200 / 160	MD/TD 200 / 500	100	Blue PE	1000/1219/ 1524	2000	0.05	MD/TD 200 / 160	MD/TC 200 / 5

SGE-113PH

SGE-113



가공성2 - 드로잉 가공



부착성2 - No.4, HL 표면에 부착



SUS - 스테인레스스틸 소재의 강판용

용도 플라스틱 사출물 보호용

피착재 스테인리스 스틸 (No.8, BA, No.4), 플라스틱류



가공성2 - 드로잉 가공



부착성2 - No.4, HL 표면에 부착



SUS - 스테인레스스틸 소재의 강판용

용도 표면 보호용, 드로잉 가공용 - 전자 제품 (가스 레인지, 전기 밥솥, 세탁기)

피착재 스테인리스 스틸 (No.8, BA, No.4)

· 테이프구조

Adhesive (Acrylic)
PE Film

· 테이프구조

Adhesive (Acrylic)
PE Film[PDF download](#)[PDF download](#)

점착력 (gf/25mm)	필름종류	폭(mm)	길이(m)	두께(mm)	인장강도 (kgf/cm ²)	신율(%)
60	Transparent PE	1000/1219/ 1524	2000	0.05	MD/TD 200 / 160	MD/TD 200 / 500

점착력 (gf/25mm)	필름종류	폭(mm)	길이(m)	두께(mm)	인장강도 (kgf/cm ²)	신율(%)
50	Transparent PE Blue PE	1000/1219/ 1524	2000	0.05	MD/TD 200 / 160	MD/TI 200 / 5

SGE-403



가공성2 - 드로잉 가공



부착성1 - BA, No.8 표면에 부착



SUS - 스테인레스스틸 소재의 강판용

용도 표면 보호용, 드로잉 가공용 - 전자 제품 (가스 레인지, 전기 밥솥, 세탁기)

피착재 스테인리스 스틸 (No.8, BA)

· 테이프구조

Adhesive (Acrylic)
PE Film[PDF download](#)

점착력 (gf/25mm)	필름종류	폭(mm)	길이(m)	두께(mm)	인장강도 (kgf/cm ²)	신율(%)
10	Transparent PE	1000/1219/ 1524	2000	0.05	MD/TD 200 / 160	MD/TD 200 / 500

ITEM	피착재						용도					
	No.8	BA	No.4	HL	Dull	Surface protective	Bending	Drawing	Deep drawing	Sink	Roll forming	Construct Exterio
SGE103	◎	◎				○		○				
SGE113	◎	◎	○			○	○	○				
SGE113PH	◎	◎	○			○	○	○				
SGE123	◎	◎	○			○	○	○				
SGE123K	◎	◎	○			○	○	○				
SGE133	◎	◎	○			○	○	○				
SGE116	◎	◎				◎	○					

SGE403

◎

◎

○

◎



Segye chemical industry Co.,Ltd. 331-11, Sanmak-Dong, Yangsan-City, Kyungnam, 62-120, Korea
Tel. 82-55-385-4211~2 Fax.82-55-384-4128
Copyright (c) 2017 SegyeChem. Co.,Ltd All rights reserved / E-mail : sales@sgchem.co.kr