

$^{165}\text{Ho}(^{16}\text{O},x)^{175}\text{W}$

