

$^{158}\text{Gd}(^{45}\text{Sc},x)^{200}\text{Po}$

