

$^{28}\text{Si}(\text{d},\text{p})^{29}\text{Si}$, $E_{\text{lab}}=0$ eV, $\theta_{\text{lab}}=160$ deg

