

$^{82}\text{Se}(\text{h,d})^{83}\text{Br}$, $E_{\text{inc}}=24\text{ MeV}$, $E_{\text{lvl}}=1.809\text{ MeV}$

