

$^{82}\text{Se}(\text{h,d})^{83}\text{Br}$, $E_{\text{inc}}=24\text{ MeV}$, $E_{|\text{V}|}=2.05\text{ MeV}$

