

$^{82}\text{Se}(h,t)^{82}\text{Br}$, $E_{\text{inc}}=420\text{ MeV}$, $E_{|V|}=4.25\text{ MeV}$

