

$^{82}\text{Se}(\text{h,t})^{82}\text{Br}$, $E_{\text{inc}}=420\text{ MeV}$, $E_{|\text{V}|}=764\text{ keV}$

