

$^{60}\text{Ni}(p,\text{el})^{60}\text{Ni}$, $\theta_{\text{lab}}=160$ deg

