

IS 10303 : 1993  
ISO 6749 : 1984

भारतीय मानक

मिट्टी उठाने की मशीनरी — परीक्षण और संग्रहण

( पहला पुनरीक्षण )

*Indian Standard*

EARTH-MOVING MACHINERY — PRESERVATION  
AND STORAGE

*( First Revision )*

UDC 621'878/'879

© BIS 1993

**BUREAU OF INDIAN STANDARDS**

MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI 110002

October 1993

Price Group 3

## NATIONAL FOREWORD

This Indian Standard which is identical with ISO 6749 : 1984 'Earth-moving machinery—Preservation and storage', issued by the International Organization for Standardization ( ISO ) was adopted by the Bureau of Indian Standards on the recommendations of the Bulk Handling Equipment Sectional Committee ( HMD 7 ) and approval of the Heavy Mechanical Engineering Division Council.

This Indian Standard was first published in 1982. Consequent upon the revision of ISO standard, this standard is being revised by adopting the ISO standard under dual number system.

The text of ISO standard has been approved for publication as Indian Standard without deviations. Certain terminology and conventions are however not identical to those used in Indian Standards. Attention is particularly drawn to the following:

- a) Wherever the words 'International Standard' appear, referring to this standard, they should be read as 'Indian Standard'.
- b) Comma ( , ) has been used as a decimal marker while in Indian Standards, the current practice is to use a point ( . ) as a decimal marker.

## ADDITIONAL INFORMATION

IS 10280 : 1993 'Earth-moving machinery — Operation and maintenance — Format and content of manuals' ( *under print* ) is a necessary adjunct to this standard and may cover the information required to be included in the operator's manual in accordance with **4.1.6** of this standard.

In reporting the results of a test or analysis made in accordance with this standard, if the final value, observed or calculated is to be rounded off, it shall be done in accordance with IS 2 : 1960 'Rules for rounding off numerical values ( *revised* )'. The number of significant places retained in the rounded off values should be the same as that of the specified value in this standard.

*Indian Standard*  
**EARTH-MOVING MACHINERY — PRESERVATION  
AND STORAGE**  
*( First Revision )*

## 1 Scope

This International Standard specifies the general methods for preservation and removal of preservation materials from earth-moving machinery and its elements, and the categories of storage and transportation conditions.

## 2 Field of application

This International Standard is applicable to newly-manufactured earth-moving machines as well as to those already in use to be preserved.

## 3 Definitions

For the purpose of this International Standard, the following definitions apply :

**3.1 preservation :** Set of operations to be carried out by the manufacturer, the user and others for the purpose of protecting a machine against the corrosive action of the environment and against minor damage that might occur during handling, transportation and storage.

**3.2 transportation :** Conveyance of a machine by any mode of transport, i.e., rail, road, sea, river and air.

**3.3 storage :** Period during which a machine is kept idle from the moment preservative is applied until the moment the preservative is removed.

**3.4 removal of preservatives :** Set of operations to be carried out by the dealer, the user and/or others prior to putting a machine into service.

## 4 Preservation

### 4.1 General

**4.1.1** Preservation treatment consists of preliminary operations possibly involving some dismantling, marking, preparation for preservation, the preservation proper, and final packaging.

**4.1.2** Preservation of a newly-manufactured machine and its elements, unless otherwise stipulated in the order or the contract of sale, shall be carried out by the manufacturer.

**4.1.3** All materials used for the preservation of a machine and its elements shall conform to the specifications laid down in International Standards or other appropriate technical documents specified in the order or contract of sale, and shall ensure conservation of a machine for the intended period of preservation.

**4.1.4** A machine shall be delivered for preservation treatment without any traces of corrosion on metal surfaces, or damage to paintwork, metallic, or other coatings.

A used machine shall be reconditioned prior to preservation.

**4.1.5** Preservation treatment shall be carried out in suitable conditions (ambient temperature, humidity) and with the correct materials which provide for the required quality of preservation while taking due care to ensure the safety of personnel and protection of the environment.

**4.1.6** Each machine given the preservation treatment shall be provided with instructions for the removal of preservatives.

These instructions may be included as a separate chapter in the operator's manual.

**4.1.7** The instructions for preservation and removal of preservatives shall be packed in a labelled waterproof envelope and attached to the machine in a conspicuous place.

**4.1.8** The instructions for removal of preservatives shall specify the categories of conditions for storage and transportation, the date of preservation, and the duration of validity of preservation.

The instructions shall also specify the methods for the removal of preservatives and reassembly of dismantled elements, a list of tools and appliances needed for these operations.

**4.1.9** Operations of preservation and removal of preservatives shall be carried out with due regard for the general accident prevention measures specified, if necessary, by the national governing body having jurisdiction.

**4.1.10** Full details concerning preservation, packing and transportation shall be specified by the manufacturer in special instructions included with the machine documentation upon request, for example

- a) a method of lifting the machine for loading and/or unloading in order to keep preservatives intact;
- b) particular requirements, such as operations necessary when a machine is to be transferred from one mode of transportation to another which may require unpacking, including a procedure for re-preservation.

**4.1.11** It is important to ensure that tyres, hoses, etc. are protected against damage or deterioration by preservatives, by solvents used near them, and by exposure to the sun, moisture and other natural occurrences.

## **4.2 Preliminary operations**

### **4.2.1 Partial dismantling and marking**

**4.2.1.1** Partial dismantling shall be kept to a minimum and shall be carried out :

- a) to give preservation treatment to inaccessible areas;
- b) to safeguard protruding elements or easily damageable parts against damage or loss; and
- c) to bring down the overall dimensions of a machine within the limits of transportation size specified in International Standards or other documents specified in the order or contract of sale.

**4.2.1.2** When dismantled elements are to be attached to the base machine they shall be so secured that they may not shift or be damaged or lost during handling or transportation.

**4.2.1.3** Fastenings used to attach the dismantled elements shall also be given the preservation treatment, and wherever possible, shall be secured to appropriate mating surfaces to guard against loss.

**4.2.1.4** Dismantled elements and their corresponding mating surfaces on the base machine may be appropriately marked to guide correct reassembly. Tags used for marking dismantled elements should be of waterproof material.

### **4.2.2 Preparation of surfaces for preservation**

**4.2.2.1** Surfaces of a machine and its dismantled elements requiring protection shall be cleaned and be free of corrosion, oil, and other contaminants, and dried.

**4.2.2.2** Aqueous alkali solutions, organic solvents, blasting with abrasives or any other suitable means which ensure the required degree of cleanliness and do not cause damage to the machine can be used for cleaning and degreasing the outer surfaces.

The cleaning method shall be chosen depending on the structural features and degree of soiling and the type of outer coatings present.

**4.2.2.3** Preparation of surfaces by means of alkali solutions shall be carried out in washing installations with such solutions and by such procedures that ensure the required degree of cleanliness and degreasing.

**4.2.2.4** If organic solvents are used, the areas to be preserved shall be wiped with soft rags or brushes wetted with solvent.

**4.2.2.5** If blasting with abrasives is used, the surfaces shall be cleaned by blowing with a high-velocity jet of water or air containing fine abrasive particles.

**4.2.2.6** After cleaning, the surfaces shall be thoroughly dried to remove traces of solvents and moisture by one of the following methods :

- a) blowing with a jet of filtered, dry, compressed air;
- b) heating in a temperature-controlled oven;
- c) wiping with clean rag or paper; or
- d) subjecting to the action of IR rays or any other suitable means that will not damage the surfaces.

## **4.3 Preservation procedures and types of protective coatings**

**4.3.1** The preservation method and the type of protective coating shall be chosen depending on the structural features and the materials of the machine, preservation duration, storage and transportation conditions with due regard for the amount of labour needed and the availability of materials required for removing the preservative coatings.

**4.3.2** Preservative coatings shall be applied to those metallic surfaces which, if corroded, may deteriorate the operational qualities of the machine or detract from its external appearance.

**4.3.3** The surfaces of non-vital parts or those of corrosion-resistant metals such as copper, nickel, chromium, and bronze need not be treated, unless transported by sea.

Special attention should be given to protecting electrical system junction boxes, switches, relays, etc. Permanent protective coatings should be applied during the assembly process.

#### 4.3.4 Recommended preservation methods

##### 4.3.4.1 Inhibitor coatings

Protective inhibitor coatings recommended are inhibitor paper, alcohol or alcohol-aqueous solutions of inhibitors, and powdery or other forms of inhibitors capable of protecting the machine surfaces.

**4.3.4.1.1** Protection by inhibitor paper : constituent parts of machines may be completely wrapped in inhibitor paper with sufficient overlapping at joints.

To protect the elements of heavy machines of complicated configuration with inhibitor paper, an additional outer protective layer such as PVC film, metallic foil, etc. may also be used.

**4.3.4.1.2** Alcohol or aqueous-alcohol solutions of vapour phase inhibitors or powdery inhibitors can be applied to preserve closed cavities which need to be airtight in the course of operation.

After treating with inhibitor solutions, excess solution shall be removed and the machine or its elements dried until the inhibitor crystallizes on the preserved surfaces. All ports and cavities shall be covered with inhibitor paper or glued with an adhesive polymer film and sealed.

##### 4.3.4.2 Preservation with oil or dope coatings

**4.3.4.2.1** Preservation of outer surfaces with an oil coating shall be carried out by dipping, spraying or other suitable method. After the outer surfaces have been treated with oil, excess oil shall be allowed to drain away.

**4.3.4.2.2** Preservation of inner surfaces shall be carried out by pouring oil into the cavities and subsequently rotating the corresponding moving parts of the machine, or by pumping oil into the system to be preserved, or by any other suitable means of applying the preserving oil. In this process, care should be taken that a uniform film of oil is applied to all surfaces being treated. Excess oil shall be allowed to drain away.

**4.3.4.2.3** Inner surfaces of hydraulic systems operating on inhibited hydraulic fluids shall be preserved by filling these systems with the appropriate operating fluids.

**4.3.4.2.4** Preservative dopes in molten state or dissolved in white spirit shall be applied to the machine surfaces by spraying, coating or other suitable means which ensure the required quality of preservation.

**4.3.4.2.5** Any defect detected in the preservative coating shall be eliminated by applying the same oil or dope.

**4.3.4.3** Application of inhibitor polymer dopes on machine surfaces can be carried out by any suitable method which ensures a uniform coating without any discontinuities or inclusions.

**4.3.4.4** To protect against the influence of the sun, rubber elements shall be preserved by coating with light-proof compounds by means of a brush or by spraying or any other suitable method which ensures the required quality of preservation.

**4.3.5** Other suitable preservation methods can also be practised, or a combination of two or more preservation methods applied, provided such a procedure does not cause damage to the machine.

**4.3.6** Preservatives may be removed by one of the methods recommended in table 1 or by any other suitable method which does not cause damage to, or detract from, the external appearance of the machine.

**Table 1 — Methods recommended for removal of preservatives**

Preservation method	Removal method
Inhibitor coating on the surface	Unwrap inhibitor paper, blow the cavities with hot, dry air or wash with soap-soda solution
Oil or dope coating on the surface	Cleanse with hot water, detergent solution or wipe with organic solvents and then wash with hot water or detergent solution
Inhibitor polymer coating on the surface	Peel off polymer film by cutting at a suitable point
Coating of light-proof compound on rubber surface	Wash with detergent

#### 4.4 Packaging

**4.4.1** Packaging is classified into protective and transport packing.

**4.4.2** Protective packing is carried out to prevent or to inhibit penetration of moisture or corrosive gases, to delay diffusion of inhibitor vapours into outer space and to retain the inhibitor oil or dope on the machine surfaces, and to protect the machine against termites and rodents in the course of transportation or during storage.

**4.4.2.1** The material and the type of protective packing shall be chosen depending on the preservative applied, storage duration and transportation conditions. Packing materials recommended are waterproof paper, film, and sealing compounds.

**4.4.2.2** Partial packing can be practised for machine surfaces of complicated configurations.

**4.4.2.3** If a machine is wrapped in paper or in film, the edges shall overlap each other, and the junctions shall be sealed.

**4.4.3** Transport packing is intended to protect the machine against mechanical damage that might occur during handling, transportation and storage.

**4.4.3.1** Transport packing used by the manufacturer shall be in compliance with International Standards or other documents stipulated in the order or contract of sale.

**4.4.3.2** A machine can be shipped without any packing or only with partial packing of vital parts, provided such a packaging does not cause damage to or detract from the external appearance of the machine.

## **5 Storage and transportation**

### **5.1 Storage and transportation conditions**

**5.1.1** Four categories of severity for storage and transportation, depending on the nature of corrosive agents in the atmosphere and on storing conditions, are recognized. The categories are :

- A — light duty,
- B — medium duty,
- C — heavy duty, and
- D — very heavy duty.

The category of storage and transportation conditions shall be specified by the user (see 5.1.3, 5.1.4, and 5.1.5).

**5.1.2** Storage is classified as short-term and long-term.

**5.1.2.1** Short-term storage covers periods up to two months. In short-term storage, the machine shall be held ready for immediate use.

**5.1.2.2** Long-term storage covers periods exceeding two months. Long-term storage is classified as

- a) for periods up to one year,
- b) for periods exceeding one year.

**5.1.3** For machines in short-term storage, the normal category is A (see 5.1.1), but under very severe corrosive conditions a higher category may be necessary.

**5.1.4** The categories of long-term storage conditions are listed in table 2.

**5.1.5** The categories of transportation conditions are listed in table 3.

**5.1.6** The categories of storage and transportation for dismantled elements shall be the same as the categories of storage and transportation of the base machine.

### **5.2 Storage sites and conditions**

**5.2.1** Machines may be stored under cover, in the open air in transport packing, in closed unheated or air-conditioned premises, or under any other storage site conditions equivalent to or better than those recommended by the manufacturer.

**5.2.2** Prior to putting into long-term storage, the machine shall be inspected and the condition of preservation treatment, seals, and components shall be checked.

**5.2.3** The machine shall be set horizontally on supports to prevent warping of the frame or deformation of pneumatic wheels. The clearance between the wheels and the supporting surface shall be not less than 8 cm.

**5.2.4** Access openings, fuel filler openings, exhaust pipes and other openings through which atmospheric precipitations may penetrate into the inner cavities of component units and parts, shall be tightly closed with caps, plugs, water-resistant adhesive tape or other special devices.

**5.2.5** Control levers and pedals shall be set in such positions where there is no danger of the machine being set in operation accidentally.

**5.2.6** Storage batteries shall be disconnected. The level and density of electrolyte shall be in accordance with the recommendations of the manufacturer. When the machine is put into storage for more than one month, storage batteries shall be removed from the machine and put into storage in special premises.

**5.2.7** Fuel, lubricants, hydraulic fluids, coolants and water in tanks shall be filled to the levels recommended by the manufacturer or the national governing body having jurisdiction.

**5.2.8** A machine in long-term storage shall be regularly inspected for its external appearance, the condition of preserved surfaces, and the preservatives.

Preferred inspection intervals for long-term storage are as follows:

- in temperate climatic conditions: every 6 months;
- in tropical, cold, arctic and coastal climatic conditions: every 3 months.

Table 2 — Categories of long-term storage conditions

Atmosphere	Content of corrosive agents in open atmosphere		Storage sites	Storage category in climatic region			
	Sulfur mg/m <sup>3</sup>	Chlorides mg/m <sup>3</sup> per day		Temperate	Cold	Tropical	
						Dry	Humid
Rural, forest, mountain	Not over 0,02	Not over 0,3	Under cover or in open air in transport packing	C	C	B	D
			In closed unheated storehouse	B	B	A	C
			In air-conditioned storehouse	A	A	A	A
Industrial	From 0,02 to 2,0	From 0,3 to 2,0	Under cover or in open air in transport packing	D	D	D	D
			In closed unheated storehouse	B	C	B	C
			In air-conditioned storehouse	A	A	A	A
Coastal	From 0,02 to 0,2	From 2,0 to 2 000	Under cover or in open air in transport packing	D	D	—	D
			In closed unheated storehouse	C	C	—	C
			In air-conditioned storehouse	A	A	—	A

NOTE — The relative humidity in an air-conditioned storehouse should not exceed 70 %.

Table 3 — Categories of transportation conditions

Transport	Transportation condition	Category
Land	On platform car or in open truck	C
	In rail wagon or in closed truck	B
Sea	On ship deck with measures to prevent penetration of water	D
	In ship hold	C
River	In the hold or on deck with measures to prevent penetration of water	B
Air	—	B

NOTES

- 1 In case of transportation by sea or river, if the categories of storage and transportation are different, the more exacting of the two shall be taken.
- 2 In case of land or air transportation, if the categories of storage and transportation are different, a transportation category lesser by one degree shall be taken, provided the transportation duration is not more than 10 % of the storage duration (for example, B for C, or A for B).

### **Standard Mark**

The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.



## Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

### Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

### Revision of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards Monthly Additions'. Comments on this Indian Standard may be sent to BIS giving the following reference:

Doc : No. HMD 7 ( 0174 )

### Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

## BUREAU OF INDIAN STANDARDS

### Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002  
Telephones : 331 01 31, 331 13 75

Telegrams : Manaksanstha  
( Common to all Offices )

### Regional Offices :

	Telephone
Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110002	{ 331 01 31 331 13 75
Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola CALCUTTA 700054	{ 37 84 99, 37 85 61 37 86 26, 37 86 62
Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036	{ 53 38 43, 53 16 40 53 23 84
Southern : C. I. T. Campus, IV Cross Road, MADRAS 600113	{ 235 02 16, 235 04 42 235 15 19, 235 23 15
Western : Manakalaya, E9 MIDC, Marol, Andheri ( East ) BOMBAY 400093	{ 632 92 95, 632 78 58 632 78 91, 632 78 92
Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR. LUCKNOW. PATNA. THIRUVANANTHAPURAM.	