

IS : 2386 (Part VI) - 1963

Indian Standard

METHODS OF TEST
FOR AGGREGATES FOR CONCRETE

PART VI MEASURING MORTAR MAKING PROPERTIES
OF FINE AGGREGATE

(Eighth Reprint APRIL 1997)

UDC 691.322 : 666.97.620.173

© Copyright 1963

BUREAU OF INDIAN STANDARDS

MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Indian Standard

**METHODS OF TEST
FOR AGGREGATES FOR CONCRETE
PART VI MEASURING MORTAR MAKING PROPERTIES
OF FINE AGGREGATE**

Cement and Concrete Sectional Committee, BDC 2*Chairman*

SHRI K. K. NAMBIAR

Representing

The Concrete Association of India, Bombay

*Members*SHRI K. V. THADANEY (*Alternate to*

Shri K. K. Nambiar)

SHRI K. F. ANTIA

M. N. Dastur & Co Private Ltd , Calcutta

SHRI P. S. BHATNAGAR

Bhakra Dam Designs Directorate, New Delhi

DR I C. DOS M. PAIS CUDDOU

Central Water & Power Commission (Ministry of
Irrigation & Power)SHRI Y. K. MURTHY (*Alternate*)

SHRI N. D. DAFTARY

Khira Steel Works Private Ltd , Bombay

SHRI N. G. DEWAN

Central Public Works Department

SUPERINTENDING ENGINEER,

2ND CIRCLE (*Alternate*)

DR R. R. HATTIANGADI

The Associated Cement Companies Ltd , Bombay

SHRI V. N. PAI (*Alternate*)

SHRI P. C. HAZRA

Geological Survey of India, Calcutta

JOINT DIRECTOR STANDARDS

Research, Designs & Standards Organization

(B & S)

(Ministry of Railways)

ASSISTANT DIRECTOR STAND-

ARDS (B & S) (*Alternate*)

SHRI S. B. JOSHI

S. B. Joshi & Co Private Ltd , Bombay

SHRI M. M. LAL

U. P. Government Cement Factory, Churk

SHRI B. N. MAJUMDAR

Directorate General of Supplies & Disposals (Minis-
try of Economic & Defence Co-ordination)SHRI P. L. DAS (*Alternate*)

PROF S. R. MEHRA

Central Road Research Institute (CSIR), New
Delhi

SHRI N. H. MOHILE

The Concrete Association of India, Bombay

SHRI S. N. MUKERJI

Government Test House, Calcutta

SHRI N. C. SEN GUPTA (*Alternate*)

SHRI ERACH A. NADIRSHAH

Institution of Engineers (India), Calcutta

SHRI C. B. PATEL

National Buildings Organisation (Ministry of
Works, Housing & Rehabilitation)SHRI RABINDER SINGH (*Alternate*)

PROF G. S. RAMASWAMY

Central Building Research Institute (CSIR),
RoorkeeSHRI K. SIVA PRASAD (*Alternate*)

SHRI T. N. S. RAO

Gammon India Limited, Bombay

SHRI S. R. PINHEIRO (*Alternate*)(*Continued on page 2*)

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

IS : 2386 (Part VI) - 1963

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
REPRESENTATIVE	Martin Burn Ltd , Calcutta
SHRI NIHAR CHANDRA ROY	Dalmia Cement (Bharat) Ltd , Calcutta
SECRETARY	Central Board of Irrigation & Power (Ministry of Irrigation & Power)
BRIG G. S. SIHOTA	Engineer-in-Chief's Branch, Army Headquarters
SHRI R. S. MEHANDRU (<i>Alternate</i>)	
DR BH. SUBBARAJU	Indian Roads Congress, New Delhi
SHRI J. M. TREHAN	Roads Wing, Ministry of Transport & Communications
SHRI N. H. KESWANI (<i>Alternate</i>)	
DR H. C. VISVESVARAYA,	Director, BIS (<i>Ex-officio Member</i>)
Deputy Director (Bldg)	

Secretary

SHRI A. PRITHIVI RAJ
Extra Assistant Director (Bldg), BIS
Concrete Subcommittee, BDC 2 : 2

Convener

SHRI S. B. JOSHI S. B. Joshi & Co Private Ltd , Bombay

Members

ASSISTANT DIRECTOR STANDARDS (B & S)	Research, Designs & Standards Organization (Ministry of Railways)
SHRI N. H. BHAGWANANI	Engineer-in-Chief's Branch, Army Headquarters
DR I. C. DOS M. PAIS CUDDOU	Central Water & Power Commission (Ministry of Irrigation & Power)
SHRI Y. K. MURTHY (<i>Alternate</i>)	
SHRI P. L. DAS	Directorate General of Supplies & Disposals (Ministry of Economic & Defence Co-ordination)
SHRI B. N. MAJUMDAR (<i>Alternate</i>)	
DIRECTOR	Engineering Research Laboratory, Hyderabad
SHRI V. N. GUNAJI	Maharashtra Public Works Department
SHRI M. A. HAFEEZ	National Buildings Organisation (Ministry of Works, Housing & Rehabilitation)
SHRI B. S. SHIVAMURTHY (<i>Alternate</i>)	
SHRI C. L. HANDA	Central Water & Power Commission (Ministry of Irrigation & Power)
SHRI P. C. HAZRA	Geological Survey of India, Calcutta
SHRI K. K. NAMBLAR	The Concrete Association of India, Bombay
SHRI C. L. N. IYENGAR (<i>Alternate</i>)	
DR M. L. PURI	Central Road Research Institute (CSIR), New Delhi
PROF G. S. RAMASWAMY	Central Building Research Institute (CSIR), Roorkee
SHRI K. SIVA PRASAD (<i>Alternate</i>)	
SHRI T. N. S. RAO	Gammon India Ltd , Bombay
SHRI S. R. PINHEIRO (<i>Alternate</i>)	
SUPERINTENDING ENGINEER,	Central Public Works Department
2ND CIRCLE	
SHRI O. P. GOEL (<i>Alternate</i>)	
SHRI J. M. TREHAN	Roads Wing, Ministry of Transport & Communications
SHRI R. P. SIKKA (<i>Alternate</i>)	
SHRI H. T. YAN	Braithwaite Burn & Jessop Construction Co Ltd , Calcutta

Indian Standard

METHODS OF TEST FOR AGGREGATES FOR CONCRETE

PART VI MEASURING MORTAR MAKING PROPERTIES OF FINE AGGREGATE

0. FOREWORD

0.1 This Indian Standard (Part VI) was adopted by the Indian Standards Institution on 13 September 1963, after the draft finalized by the Cement and Concrete Sectional Committee had been approved by the Building Division Council.

0.2 One of the major contributing factors to the quality of concrete is the quality of aggregates used therein. The test methods given in this standard are intended to assist in assessing the quality of aggregates. In a given situation, for a particular aggregate, it may not be necessary to assess all the qualities and therefore it is necessary to determine beforehand the purpose for which a concrete is being used and the qualities of the aggregate which require to be assessed. Accordingly, the relevant test methods may be chosen from amongst the various tests covered in this standard. For the convenience of the users, the test methods are grouped into the following eight parts of Indian Standard Methods of Test for Aggregates for Concrete (IS : 2386 - 1963):

Part I	Particle Size and Shape
Part II	Estimation of Deleterious Materials and Organic Impurities
Part III	Specific Gravity, Density, Voids, Absorption and Bulking
Part IV	Mechanical Properties
Part V	Soundness
Part VI	Measuring Mortar Making Properties of Fine Aggregate
Part VII	Alkali Aggregate Reactivity
Part VIII	Petrographic Examination

0.3 The Sectional Committee responsible for the preparation of this standard has taken into consideration the views of the concrete specialists, testing authorities, consumers and technologists and has related the standard to the practices followed in this country. Further, the need for international co-ordination among standards prevailing in different countries of the world has also been recognized. These considerations led the Sectional

Committee to derive assistance from C 87.— 62T Tentative Method of Test for Measuring Mortar Making Properties of Fine Aggregate issued by American Society for Testing and Materials.

0.4 Wherever a reference to any Indian Standard appears in this method, it shall be taken as a reference to its latest version.

0.5 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2 - 1960 Rules for Rounding Off Numerical Values (*Revised*). The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

0.6 This standard is intended chiefly to cover the technical provisions relating to testing of aggregates for concrete, and it does not include all the necessary provisions of a contract.

1. SCOPE

1.1 This standard (Part VI) covers the test procedure for measuring the mortar-making properties of fine aggregate for concrete by means of a compression test on specimens made from a mortar of a plastic consistency and gauged to a definite water-cement ratio.

2. APPARATUS

2.1 Flow Table and Flow Mould — These shall conform to the requirements specified in 12 of *IS: 1727 - 1960 Methods of Test for Pozzolanic Materials.

2.2 Tamper — It shall be made of a non-absorptive, non-abrasive material, such as medium-hard rubber or seasoned oak wood rendered non-absorptive by immersion for 15 minutes in paraffin at approximately 200°C and shall have a cross-section of 12.5 × 25 mm and a convenient length from 125 to 150 mm. The tamping face of the tamper shall be flat and at right angles to the length of the tamper.

2.3 Trowel — It shall have a steel blade 100 to 150 mm in length, with straight edges.

2.4 Moulds — These shall be 7.06 cm cube moulds.

2.5 Tamping Rod — It shall be approximately 10 mm in diameter and 100 mm long, with one end rounded to a hemispherical tip 10 mm dia × approx 300 mm long.

2.6 Testing Machine — A compression testing machine of suitable capacity shall be used.

*Since revised.

3. MORTAR

3.1 Place cement and water in quantities that will give a water-cement ratio of 0.6 by weight in an appropriate vessel and permit the cement to absorb water for one minute. Mix the materials into a smooth paste with a spoon. Beat into the mixture a known weight of the sample of sand under test that has been brought to a saturated surface-dry condition. Mix until the material appears to be of the desired consistency (flow 100 ± 5). Continue the mixing for 30 seconds and make a determination of the flow in accordance with 4.

NOTE — For six 7.06 cm cubes 1 650 g of cement and 990 g of water will usually give sufficient mortar. The quantity of sand used with this amount of cement may vary from 3 300 g for fine sand to 5 500 g or more for coarse sand.

4. PROCEDURE

4.1 Carefully wipe the flow-table top clean and dry, and place the flow mould at the centre. Immediately after completing the mixing operation, place a layer of mortar about 25 mm in thickness in the mould and tamp 20 times with the tamper. The tamping pressure shall be just sufficient to insure uniform filling of the mould. Fill the mould with mortar and tamp as specified for the first layer. Cut off the mortar to a plane surface, flush with the top of the mould, by drawing the straight edge of a trowel (held nearly perpendicular to the mould) with a sawing motion across the top of the mould. Wipe the table top clean and dry, being especially careful to remove any water from around the edge of the flow mould. Lift the mould away from the mortar one minute after completing the mixing operation. Immediately, drop the table through a height of 12.5 mm ten times in 6 seconds. The flow is the resulting increase in average diameter of the mortar mass, measured on at least four diameters at approximately equal angles, expressed as a percentage of the original diameter. Should the flow be too great, return the mortar to the mixing vessel, add additional sand, and make another determination of the flow. If more than two trials need be made to obtain a flow of 100 ± 5 , consider the mortar as a trial mortar, and prepare test specimens from a new batch. If the mortar is too dry, discard the batch. Determine the quantity of sand used by subtracting the weight of the portion remaining after mixing from the weight of the initial sample.

5. MOULDING TEST SPECIMENS

5.1 Immediately following completion of the flow test, place the mortar in 7.06 cm cube moulds in two layers. Rod each layer in place with 25 strokes of the tamping rod. After the rodding has been completed, fill the moulds to overflowing. Place the specimens in a moist closet for curing. Three to four hours after moulding, strike off the specimens to a smooth surface. Remove the specimens from the moulds 20 to 24 hours after moulding and store in water until tested.

5.2 The temperature of the mixing water, moist closet, and storage tank shall be maintained at $27 \pm 2^{\circ}\text{C}$.

6. TESTING OF SPECIMENS

6.1 Test the specimens for compressive strength as given in **6.1.1** to **6.1.3**.

6.1.1 Test the specimens immediately after their removal from the moist closet in the case of 24-hour specimens, and from storage water in the case of all other specimens. If more than one specimen at a time is removed from the moist closet for the 24-hour tests, keep these specimens covered with a damp cloth until time of testing. If more than one specimen at a time is removed from the storage water for testing, keep these specimens in water at a temperature of $27 \pm 2^{\circ}\text{C}$ and of sufficient depth to immerse completely each specimen until time of testing.

6.1.2 Surface-dry each specimen, and remove any loose sand grains or incrustations from the faces that will be in contact with the bearing blocks of the testing machine. Check these faces by applying a straight edge (see Note). If there is appreciable curvature, grind the face or faces to plane surfaces or discard the specimen.

NOTE — Results much lower than the true strength will be obtained by loading faces of the specimen that are not truly plane surfaces. Therefore, it is essential that specimen moulds be kept scrupulously clean, as otherwise large irregularities in the surfaces will occur. Instruments for cleaning of moulds should always be softer than the metal in the moulds to prevent wear. In case grinding of specimen faces is necessary, it can be accomplished best by rubbing the specimen on a sheet of fine emery paper or cloth glued to a plane surface, using only a moderate pressure. Such grinding is tedious for more than a few hundredths of a millimetre; where more than this is found necessary, it is recommended that the specimen be discarded.

6.1.3 Apply the load to specimen faces that were in contact with the true plane surfaces of the mould. Carefully place the specimen in the testing machine below the centre of the upper bearing block. Use no cushioning or bedding materials. An initial loading up to one-half of the expected maximum load for specimens having expected maximum loads of more than 2 500 kg may be applied at any convenient rate. Adjust the rate of load application so that the remainder of the load (or the entire load in the case of expected maximum loads of less than 2 500 kg) is applied, without interruption, to failure at such a rate that the maximum load will be reached in not less than 20 nor more than 80 seconds. Make no adjustment in the controls of the testing machine while a specimen is yielding rapidly immediately before failure.

7. REPORTING OF RESULT

7.1 Report the average crushing strength of not less than three specimens and also the age of test.

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones: 323 0131, 323 3375, 323 9402

Fax: 91 11 3234062, 91 11 3239399, 91 11 3239382

Telegrams : Manaksanstha
(Common to all Offices)

Telephone

Central Laboratory:

Plot No. 20/9, Site IV, Sahibabad Industrial Area, Sahibabad 201010

8-77 00 32

Regional Offices:

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002 323 76 17

*Eastern : 1/14 CIT Scheme VII M, V.I.P. Road, Maniktola, CALCUTTA 700054 337 86 62

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022 60 38 43

Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113 235 23 15

†Western : Manakalaya, E9, Behind Marol Telephone Exchange, Andheri (East),
MUMBAI 400093 832 92 95

Branch Offices::

'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMEDABAD 380001 550 13 48

‡Peenya Industrial Area, 1st Stage, Bangalore-Tumkur Road,
BANGALORE 560058 839 49 55

Gangotri Complex, 5th Floor, Bhadbhada Road, T.T. Nagar, BHOPAL 462003 55 40 21

Plot No. 62-63, Unit VI, Ganga Nagar, BHUBANESHWAR 751001 40 36 27

Kalaikathir Buildings, 670 Avinashi Road, COIMBATORE 641037 21 01 41

Plot No. 43, Sector 16 A, Mathura Road, FARIDABAD 121001 8-28 88 01

Savitri Complex, 116 G.T. Road, GHAZIABAD 201001 8-71 19 96

53/5 Ward No.29, R.G. Barua Road, 5th By-lane, GUWAHATI 781003 54 11 37

5-8-56C, L.N. Gupta Marg, Nampally Station Road, HYDERABAD 500001 20 10 83

E-52, Chitaranjan Marg, C-Scheme, JAIPUR 302001 37 29 25

117/418 B, Sarvodaya Nagar, KANPUR 208005 21 68 76

Seth Bhawan, 2nd Floor, Behind Leela Cinema, Naval Kishore Road,
LUCKNOW 226001 23 89 23

NIT Building, Second Floor, Gokulpat Market, NAGPUR 440010 52 51 71

Patiputra Industrial Estate, PATNA 800013 26 23 05

Institution of Engineers (India) Building 1332 Shivaji Nagar, PUNE 411005 32 36 35

T.C. No. 14/1421, University P. O. Palayam, THIRUVANANTHAPURAM 695034 6 21 17

*Sales Office is at 5 Chowringhee Approach, P.O. Princep Street,
CALCUTTA 700072 27 10 85

†Sales Office is at Novelty Chambers, Grant Road, MUMBAI 400007 309 65 28

‡Sales Office is at 'F' Block, Unity Building, Narashimaraja Square,
BANGALORE 560002 222 39 71

AMENDMENT NO. 1 FEBRUARY 1982

TO

IS:2386(Part VI)-1963 METHODS OF TEST FOR
AGGREGATES FOR CONCRETE

Part VI MEASURING MORTAR MAKING PROPERTIES
OF FINE AGGREGATE

Alteration

[Page 8, clauses 7 and 7.1 (renumbered as 3 and 8.1)] - Substitute the following for the existing clauses:

'8. REPORTING OF RESULT

8.1 Calculate the average crushing strength of not less than three specimens containing untreated sand. Similarly calculate the average crushing strength of the corresponding number of specimens containing treated sand. Report the average crushing strength of specimens containing untreated sand as a percentage of the average crushing strength of the specimens containing treated sand.'

Addendum

(Page 4, clause 1.1) - Add the following new clauses after 1.1 and renumber the clauses '2 to 7' as '3 to 8':

"2. BASIS FOR COMPARISON

2.1 The fine aggregate shall be compared in mortar, as described in this method, with a sample of the same aggregate that has been washed in a 3 percent solution of sodium hydroxide followed by thorough rinsing in water. The treatment shall be repeated till the washed material produces a colour lighter than that of

the standard solution described in 6.2.2 of IS:2386(Part II)-1963 'Methods of test for aggregates for concrete : Part II Estimation of deleterious materials and organic impurities'. However, it shall be ensured that no fines are lost while washing with sodium hydroxide. The washed and rinsed aggregate shall be checked with a suitable indicator such as phenolphthalein or litmus to assure that all traces of sodium hydroxide are removed from the aggregate before being used for making control mortar."

(EDC 2)

AMENDMENT NO. 2 OCTOBER 1991
TO
IS 2386 (Part 6) : 1963 METHODS OF TEST FOR
AGGREGATES FOR CONCRETE

PART 6 MEASURING MORTAR MAKING PROPERTIES OF FINE
AGGREGATE

(*Page 4, clause 2.2*) — Substitute the following for the existing clause :

2.2 Tamping Bar — The tamping bar shall be made of non-absorbent, abrasion resistant, non-brittle material such as a rubber compound having a Shore A durometer hardness of 80 ± 10 or seasoned teak wood rendered non-absorbent by immersion for 15 minutes in paraffin at approximately 200°C and shall have a cross-section of 12.5×25 mm and a convenient length of 125 to 150 mm. The tamping face shall be flat and at right angles to the length of the bar.'

(*Page 4, clause 2.4*) — Substitute the following for the existing clause :

"2.4 Moulds — These shall be 50 mm cube moulds and shall conform to the requirements laid down in IS 10036 : 1982 'Specification for moulds for use in tests of cement and concrete'."

(*Page 5, clause 3.1, Note*) — Delete.

(*Page 5, clause 5.1, line 2*) — Substitute '50 mm' for '7.06 cm'.

(CED 2)

Printed at Simco Printing Press, Delhi