

IS 12600 : 1989

*Indian Standard*

**PORTLAND CEMENT, LOW HEAT —  
SPECIFICATION**

**भारतीय मानक**

**पोर्टलैंड सीमेंट, अल्प ताप — विशिष्ट**

UDC 666.942.33

© BIS 1990

**BUREAU OF INDIAN STANDARDS**  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI 110002

*January 1990*

**Price Group 4**

## FOREWORD

This Indian Standard was adopted by the Bureau of Indian Standards on 20 June 1989, after the draft finalized by the Cement and Concrete Sectional Committee had been approved by the Civil Engineering Division Council.

The requirements of low heat Portland cement were earlier covered in IS 269 : 1976 'Specification for ordinary and low heat Portland cement ( *third revision* )' which in addition, covered the requirements of ordinary Portland cement. Since the Sectional Committee decided to bifurcate the standard, the requirements of low heat Portland cement have now been covered in a separate specification.

This specification covers the requirements of low heat Portland cement as was given in IS 269 : 1976 with the various amendments published from time to time.

Low heat cement is particularly suited for making concrete for dams and many other types of water-retaining structures, bridge abutments, massive retaining walls, piers and slabs, etc. In mass concreting, there is often considerable rise in temperature because of the heat evolved as the cement sets and hardens, and the slow rate at which it is dissipated from the surface. The shrinkage which occurs on subsequent cooling sets up tensile stresses in the concrete which may result in cracking. The use of low heat cement is advantageous since it evolves less heat than ordinary Portland cement.

Mass of cement packed in bags and the tolerance requirements for the mass of cement packed in bags shall be in accordance with the relevant provisions of the *Standards of Weights and Measures ( Packaged Commodities ) Rules, 1977* and B-1.2 ( *see Annex B for information* ). Any modification in these rules in respect of tolerance on mass of cement would apply automatically to this standard.

This standard contains clause 11.4.1 which gives option to the purchaser and clauses 6.5, 9.2.1 and 9.3 which call for agreement between the purchaser and the supplier.

In the formulation of this standard, considerable assistance has been rendered by the National Council for Cement and Building Materials, New Delhi as many of the changes are based on the studies carried out by them.

The composition of the technical committee responsible for the formulation of this standard is given in Annex C.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values ( *revised* )'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

# Indian Standard

## PORTLAND CEMENT, LOW HEAT — SPECIFICATION

### 1 SCOPE

**1.1** This standard covers the manufacture and chemical and physical requirements of low heat Portland cement for use where low heat of hydration is required, as in mass concrete for dams.

### 2 REFERENCES

**2.1** The Indian Standards listed in Annex A are necessary adjuncts to this standard.

### 3 TERMINOLOGY

**3.1** For the purpose of this standard, the definitions given in IS 4845 : 1968 shall apply.

### 4 MANUFACTURE

**4.1** Low heat Portland cement shall be manufactured by intimately mixing together calcareous and argillaceous and/or other silica, alumina or iron oxide bearing materials, burning them at a clinkering temperature and grinding the resultant clinker so as to produce a cement capable of complying with this specification. No material shall be added after burning, other than gypsum

( natural or chemical ) or water or both, and not more than one percent of air-entraining agents or other agents which have proved not to be harmful.

NOTE — Chemical gypsum shall be added provided that the performance requirements of the final product as specified in this standard are met with.

### 5 CHEMICAL REQUIREMENTS

**5.1** When tested in accordance with the methods given in IS 4032 : 1985, low heat Portland cement shall comply with the chemical requirements given in Table 1 and 5.2.

**5.2** The percentage of lime, after deduction of that necessary to combine with sulphuric anhydride percent, shall be:

a) not more than  $2.4 ( \text{SiO}_2 ) + 1.2 ( \text{Al}_2\text{O}_3 ) + 0.65 ( \text{Fe}_2\text{O}_3 )$ , and

b) not less than  $1.9 ( \text{SiO}_2 ) + 1.2 ( \text{Al}_2\text{O}_3 ) + 0.65 ( \text{Fe}_2\text{O}_3 )$ .

NOTE — Each symbol in brackets refers to the percentage ( by mass of total cement ) of the oxide excluding any contained in the insoluble residue referred to at SI No. (ii) of Table 1.

**Table 1 Chemical Requirements for Low Heat Portland Cement**  
( *Clauses 5.1 and 5.2* )

| SI No. | Characteristic   | Requirement  |
|--------|--|--|
| i)     | Ratio of percentage of alumina to that of iron oxide                                       | Not less than 0.66   |
| ii)    | Insoluble residue, percent by mass   | Not more than 4 percent  |
| iii)   | Magnesia, percent by mass  | Not more than 6 percent  |
| iv)    | Total sulphur content calculated as sulphuric anhydride ( $\text{SO}_3$ ), percent by mass | Not more than 2.5 and 3.0 when tricalcium aluminate ( <i>see</i> Note 1 ) percent by mass is 5 or less and greater than 5 respectively |
| v)     | Total loss on ignition   | Not more than 5 percent  |

#### NOTES

**1** The tri-calcium aluminate content (  $\text{C}_3\text{A}$  ) is calculated by the formula:

$$\text{C}_3\text{A} = 2.65 ( \text{Al}_2\text{O}_3 ) - 1.69 ( \text{Fe}_2\text{O}_3 )$$

where each symbol in brackets refers to the percentage ( by mass of total cement ) of the oxide, excluding any contained in the insoluble residue referred to at SI No. (ii).

**2** Alkali aggregate reactions have been noticed in aggregates in some parts of the country. On large and important jobs where the concrete is likely to be exposed to humid atmosphere or wetting action, it is advisable that the aggregate be tested for alkali aggregate reaction. In the case of reactive aggregates, the use of cement with alkali content below 0.6 percent expressed as sodium oxide (  $\text{Na}_2\text{O}$  ), is recommended. Where, however, such cements are not available, use of Portland pozzolana cement or cement pozzolanic admixture is recommended.

**3** The limit of total chloride content in cement for use in plain and other reinforced concrete structures is being reviewed. Till that time, the limit may be mutually agreed to between the purchaser and the manufacturer.

## 6 PHYSICAL REQUIREMENTS

### 6.1 Fineness

When tested for fineness by Blaine's air permeability method as described in IS 4031 ( Part 2 ) : 1988, the specific surface of cement shall be not less than 320 m<sup>2</sup>/kg.

### 6.2 Soundness

**6.2.1** When tested by 'Le Chatelier' method and autoclave test described in IS 4031 ( Part 3 ) : 1988, unaerated cement shall not have an expansion of more than 10 mm and 0.8 percent, respectively.

**6.2.1.1** In the event of cements failing to comply with any one or both the requirements specified in **6.2.1**, further tests in respect of each failure shall be made as described in IS 4031 ( Part 3 ) : 1988 from another portion of the same sample after aeration. The aeration shall be done by spreading out the sample to a depth of 75 mm at a relative humidity of 50 to 80 percent for a total period of 7 days. The expansion of cements so aerated shall be not more than 5 mm and 0.6 percent when tested by 'Le Chatelier' method and autoclave test respectively.

### 6.3 Setting Time

The setting time of the cements, when tested by the Vicat apparatus method described in IS 4031 ( Part 5 ) : 1988, shall conform to the following requirements:

- a) Initial setting time in minutes not less than 60, and
- b) Final setting time in minutes not more than 600.

**6.3.1** If cement exhibits false set, the ratio of final penetration measured after 5 minutes of completion of mixing period to the initial penetration measured exactly after 20 seconds of completion of mixing period, expressed as percent, shall be not less than 50. In the event of cement exhibiting false set, the initial and final setting time of cement when tested by the method described in IS 4031 ( Part 5 ) : 1988 after breaking the false set, shall conform to **6.3**.

### 6.4 Compressive Strength

The average compressive strength of at least three mortar cubes ( area of face 50 cm<sup>2</sup> ) composed of one part of cement, three parts of standard sand ( conforming to IS 650 : 1966 ) by mass and  $\left( \frac{P}{4} + 3.0 \right)$  percent ( of combined mass of cement plus sand ) water and prepared, stored and tested

in the manner described in IS 4031 ( Part 6 ) : 1988 shall be as follows:

- a) 72 ± 1 hour not less than 10 MPa,
- b) 168 ± 2 hours not less than 16 MPa, and
- c) 672 ± 4 hours not less than 35 MPa.

NOTE — *P* is the percentage of water required to produce a paste of standard consistency ( see 11.3 ).

**6.5** By agreement between the purchaser and the manufacturer, transverse strength test of plastic mortar in accordance with the method described in IS 4031 ( Part 8 ) : 1988 may be specified in addition to the test specified in **6.4**. The permissible values of the transverse strength shall be mutually agreed to between the purchaser and the supplier at the time of placing the order.

**6.6** Notwithstanding the strength requirements specified in **6.4** and **6.5**, the cement shall show a progressive increase in strength from the strength at 72 hours.

### 6.7 Heat of Hydration

When tested by the method described in IS 4031 ( Part 9 ) : 1988, the heat of hydration of cement shall be as follows:

- a) 7 days : not more than 272 kJ/kg, and
- b) 28 days : not more than 314 kJ/kg.

## 7 STORAGE

**7.1** The cement shall be stored in such a manner as to permit easy access for proper inspection and identification, and in a suitable weather-tight building to protect the cement from dampness and to minimize warehouse deterioration.

## 8 MANUFACTURER'S CERTIFICATE

**8.1** The manufacturer shall satisfy himself that the cement conforms to the requirements of this standard and, if requested, shall furnish a certificate to this effect to the purchaser or his representative, within ten days of despatch of the cement.

**8.2** The manufacturer shall furnish a certificate, within ten days of despatch of the cement, indicating the total chloride content in percent by mass of cement.

## 9 DELIVERY

**9.1** The cement shall be packed in bags [ jute sacking bag conforming to IS 2580 : 1982, double hessian bituminized ( CRI type ), multi-wall paper conforming to IS 11761 : 1986, polyethylene lined ( CRI type ) jute, light weight jute conforming to IS 12154 : 1987, woven HDPE conforming to IS 11652 : 1986, woven polypropylene conforming to IS 11653 : 1986, jute synthetic union conforming

to IS 12174 : 1987 or any other approved composite bag ] bearing the manufacturer's name or his registered trade-mark, if any. The words 'low heat Portland cement' and the number of bags ( net mass ) to the tonne or the nominal average net mass of the cement shall be legibly and indelibly marked on each bag. Bags shall be in good condition at the time of inspection.

**9.1.1** Similar information shall be provided in the delivery advices accompanying the shipment of packed or bulk cement ( *see* 9.3 ).

**9.2** The average net mass of cement per bag shall be 50 kg ( *see* Annex B ).

**9.2.1** The average net mass of cement per bag may also be 25 kg subject to tolerances as given in 9.2.1.1 and packed in suitable bags as agreed to between the purchaser and the manufacturer.

**9.2.1.1** The number of bags in a sample taken from weighment showing a minus error greater than 2 percent of the specified net mass shall be not more than 5 percent of the bags in the sample. Also the minus error in none of such bags in the sample shall exceed 4 percent of the specified net mass of cement in the bag. However, the average net mass of cement in a sample shall be equal to or more than 25 kg.

**9.3** Supplies of cement in bulk may be made by arrangement between the purchaser and the supplier ( manufacturer or stockist ).

**NOTE**—A single bag or container containing 1 000 kg and more net mass of cement shall be considered as bulk supply of cement. Supplies of cement may also be made in intermediate containers, for example, drums of 200 kg, by agreement between the purchaser and the manufacturer.

## 10 SAMPLING

### 10.1 Samples for Testing

A sample or samples for testing may be taken by the purchaser or his representative, or by any person appointed to superintend the work for purpose of which the cement is required or by the latter's representative.

**10.1.1** The samples shall be taken within three weeks of the delivery and all the tests shall be commenced within one week of sampling.

**10.1.2** When it is not possible to test the samples within one week, the samples shall be packed and stored in air-tight containers till such time that they are tested.

**10.2** In addition to the requirements of 10.1, the methods and procedure of sampling shall be in accordance with IS 3535 : 1986.

### 10.3 Facilities for Sampling and Identifying

The manufacturer or supplier shall afford every facility and shall provide all labour and materials

for taking and packing the samples for testing the cement and for subsequent identification of cement sampled.

## 11 TESTS

**11.1** The sample or samples of cement for test shall be taken as described in 10 and shall be tested in the manner described in the relevant clauses.

### 11.2 Temperature for Testing

The temperature range within which physical tests may be carried out shall, as far as possible, be  $27 \pm 2^\circ\text{C}$ . The actual temperature during the testing shall be recorded.

### 11.3 Consistency of Standard Cement Paste

The quantity of water required to produce a paste of standard consistency, to be used for the determination of the water content of mortar for compressive strength tests and for the determination of soundness and setting time, shall be obtained by the method described in IS 4031 ( Part 4 ) : 1988.

### 11.4 Independent Testing

**11.4.1** If the purchaser or his representative requires independent tests, the samples shall be taken before or immediately after delivery at the option of the purchaser or his representative and the tests shall be carried out in accordance with this standard on the written instructions of the purchaser or his representative.

### 11.4.2 Cost of testing

The manufacturer shall supply, free of charge, the cement required for testing. Unless otherwise specified in the enquiry and order, the cost of the tests shall be borne as follows:

- a) By the manufacturer if the results show that the cement does not comply with the requirements of this standard, and
- b) By the purchaser if the results show that the cement complies with the requirements of this standard.

**11.4.3** After a representative sample has been drawn, tests on the sample shall be carried out as expeditiously as possible.

## 12 REJECTION

**12.1** Cement may be rejected if it does not comply with any of the requirements of this specification.

**12.2** Cement remaining in bulk storage at the mill, prior to shipment, for more than six months, or cement in bags in local storage in the hands of a vendor for more than 3 months after the completion of tests, may be retested before use and may be rejected if it fails to conform to any of the requirements of this specification.

## ANNEX A

( Clause 2.1 )

## LIST OF REFERRED INDIAN STANDARDS

| IS No.                       | Title   | IS No.          | Title   |
|------------------------------|---|-----------------|---|
| IS 650 : 1966                | Standard sand for testing of cement ( <i>first revision</i> )             | IS 4905 : 1968  | Methods for random sampling                                       |
| IS 2580 : 1982               | Jute sacking bags for packing cement ( <i>second revision</i> )           | IS 11652 : 1986 | High density polyethylene ( HDPE ) woven sacks for packing cement |
| IS 3535 : 1986               | Methods of sampling hydraulic cement ( <i>first revision</i> )            | IS 11653 : 1986 | Polypropylene ( PP ) woven sacks for packing cement               |
| IS 4031<br>( Parts 1 to 13 ) | Methods of physical tests for hydraulic cement                            | IS 11761 : 1986 | Multi-wall paper sacks for cement, valved-sewn-gusseted type      |
| IS 4032 : 1985               | Method of chemical analysis of hydraulic cement ( <i>first revision</i> ) | IS 12154 : 1987 | Light weight jute bags for packing cement                         |
| IS 4845 : 1968               | Definitions and terminology relating to hydraulic cement                  | IS 12174 : 1987 | Jute synthetic union bag for packing cement                       |

## ANNEX B

( Clause 9.2 and Foreword )

## TOLERANCE REQUIREMENTS FOR THE MASS OF CEMENT PACKED IN BAGS

**B-1** The average net mass of cement packed in bags at the plant in a sample shall be equal to or more than 50 kg. The number of bags in a sample shall be as given below:

| Batch Size     | Sample Size |
|----------------|-------------|
| 100 to 150     | 20          |
| 151 to 280     | 32          |
| 281 to 500     | 50          |
| 501 to 1 200   | 80          |
| 1 201 to 3 200 | 125         |
| 3 201 and over | 200         |

The bags in a sample shall be selected at random. For methods of random sampling, IS 4905 : 1968 may be referred to.

**B-1.1** The number of bags in a sample showing a minus error greater than 2 percent of the specified net mass ( 50 kg ) shall be not more

than 5 percent of the bags in the sample. Also the minus error in none of such bags in the sample shall exceed 4 percent of the specified net mass of cement in the bag.

NOTE — The matter given in **B-1** and **B-1.1** are extracts based on the *Standards of Weights and Measures ( Packaged Commodities ) Rules, 1977* to which reference shall be made for full details. Any modification made in these Rules and other related Acts and Rules would apply automatically.

**B-1.2** In case of a wagon/truck load of 20 to 25 tonnes, the overall tolerance on net mass of cement shall be 0 to +0.5 percent.

NOTE — The mass of a jute sacking bag conforming to IS 2580 : 1982 to hold 50 kg of cement is 531 g, the mass of a double hessian bituminized ( CRI type ) bag to hold 50 kg of cement is 630 g, the mass of a 6-ply paper bag to hold 50 kg of cement is approximately 400 g and the mass of a polyethylene lined ( CRI Type ) jute bag to hold 50 kg of cement is approximately 480 g.

## ANNEX C

## COMPOSITION OF THE TECHNICAL COMMITTEE

## Cement and Concrete Sectional Committee, CED 2

*Chairman*

DR H. C. VISVESVARAYA

*Members*

SHRI K. P. BANERJEE

SHRI HARISH N. MALANI ( *Alternate* )

SHRI S. K. BANERJEE

CHIEF ENGINEER ( BD )

SHRI J. C. BASUR ( *Alternate* )

CHIEF ENGINEER ( DESIGNS )

SUPERINTENDING ENGINEER ( S & S )  
( *Alternate* )

CHIEF ENGINEER ( RESEARCH-CUM-DIRECTOR )

RESEARCH OFFICER ( CONCRETE TECHNOLOGY ) ( *Alternate* )

DIRECTOR

JOINT DIRECTOR ( *Alternate* )

DIRECTOR

CHIEF RESEARCH OFFICER ( *Alternate* )

DIRECTOR ( C &amp; MDD-II )

DEPUTY DIRECTOR ( C & MDD-II )  
( *Alternate* )

SHRI V. K. GHANEKAR

SHRI S. GOPINATH

SHRI A. K. GUPTA

SHRI J. SEN GUPTA

SHRI P. J. JAGUS

DR A. K. CHATTERJEE ( *Alternate* )

JOINT DIRECTOR STANDARDS ( B &amp; S )/CB-I

JOINT DIRECTOR STANDARDS ( B & S )/CB-II  
( *Alternate* )

SHRI N. G. JOSHI

SHRI R. L. KAPOOR

SHRI R. K. SAXENA ( *Alternate* )

DR A. K. MULLICK

SHRI G. K. MAJUMDAR

SHRI P. N. MEHTA

SHRI S. K. MATHUR ( *Alternate* )

SHRI NIRMAL SINGH

SHRI S. S. MIGLANI ( *Alternate* )

SHRI S. N. PAL

SHRI BIMAN DASGUPTA ( *Alternate* )

SHRI R. C. PARATE

LT-COL R. K. SINGH ( *Alternate* )

SHRI H. S. PASRICHA

SHRI Y. R. PHULL

SHRI S. S. SEEHRA ( *Alternate* )

DR MOHAN RAI

DR S. S. REHSI ( *Alternate* )

SHRI A. V. RAMANA

DR K. C. NARANG ( *Alternate* )

SHRI G. RAMDAS

SHRI T. N. SUBBA RAO

SHRI S. A. REDDI ( *Alternate* )*Representing*

National Council for Cement and Building Materials, New Delhi

Larsen and Toubro Limited, Bombay

National Test House, Calcutta

Bhakra Beas Management Board, Nangal Township

Central Public Works Department, New Delhi

Irrigation Department, Government of Punjab

A. P. Engineering Research Laboratories, Hyderabad

Central Soil and Materials Research Station, New Delhi

Central Water Commission, New Delhi

Structural Engineering Research Centre ( CSIR ), Ghaziabad

The India Cements Limited, Madras

Hyderabad Industries Limited, Hyderabad

National Buildings Organization, New Delhi

The Associated Cement Companies Ltd, Bombay

Research, Designs and Standards Organization ( Ministry of Railways ), Lucknow

Indian Hume Pipes Co Limited, Bombay

Roads Wing ( Ministry of Transport ), Department of Surface Transport, New Delhi

National Council for Cement and Building Materials, New Delhi  
Hospital Services Consultancy Corporation ( India ) Ltd,  
New Delhi

Geological Survey of India, Calcutta

Development Commissioner for Cement Industry ( Ministry of Industry ), New Delhi

M.N. Dastur and Company Private Limited, Calcutta

Engineer-in-Chief's Branch, Army Headquarters

Hindustan Prefab Limited, New Delhi

Indian Roads Congress, New Delhi; and Central Road Research Institute ( CSIR ), New Delhi

Central Road Research Institute ( CSIR ), New Delhi

Central Building Research Institute ( CSIR ), Roorkee

Dalmia Cement ( Bharat ) Limited, New Delhi

Directorate General of Supplies and Disposals, New Delhi

Gammon India Limited, Bombay

*Members*

DR M. RAMAIAH  
DR A. G. MADHAVA RAO ( *Alternate* )  
SHRI A. U. RIJHSINGHANI  
SHRI C. S. SHARMA ( *Alternate* )  
SECRETARY  
SHRI K. R. SAXENA ( *Alternate* )  
SUPERINTENDING ENGINEER ( DESIGNS )  
EXECUTIVE ENGINEER ( SMD DIVISION )  
( *Alternate* )  
SHRI L. SWAROOP  
SHRI H. BHATTACHARYYA  
( *Alternate* )  
SHRI S. K. GUHA THAKURTA  
SHRI S.P. SANKARNARAYANAN  
( *Alternate* )  
DR H. C. VISVESVARAYA  
SHRI D. C. CHATURVEDI ( *Alternate* )  
SHRI G. RAMAN,  
Director ( Civ Engg )

*Representing*

Structural Engineering Research Centre ( CSIR ), Madras  
Cement Corporation of India, New Delhi  
Central Board of Irrigation and Power, New Delhi  
Public Works Department, Government of Tamil Nadu  
Orissa Cement Limited, New Delhi  
Gannon Dunkerly & Co Ltd, Bombay  
The Institution of Engineers ( India ), Calcutta  
Director General, BIS ( *Ex-officio Member* )

*Secretary*

SHRI N. C. BANDYOPADHYAY  
Joint Director ( Civ Engg ), BIS

**Cement, Pozzolana and Cement Additives Subcommittee, CED 2 : 1**

*Convener*

DR H. C. VISVESVARAYA

National Council for Cement and Building Materials,  
New Delhi

*Members*

|   |  |   |
|---|--|---|
| DR A. K. MULLICK<br>DR ( SMT ) S. LAXMI   | } ( <i>Alternates to Dr H. C. Visvesvaraya</i> ) |   |
| SHRI S. K. BANERJEE<br>SHRI N. G. BASAK<br>SHRI T. MADHESHWAR ( <i>Alternate</i> )<br>SHRI SOMNATH BANERJEE<br>CHIEF ENGINEER ( RESEARCH-CUM-DIRECTOR )<br>RESEARCH OFFICER ( CT ) ( <i>Alternate</i> )<br>SHRI N. B. DESAI<br>SHRI J. K. PATEL ( <i>Alternate</i> )<br>DIRECTOR<br>RESEARCH OFFICER ( <i>Alternate</i> )<br>DIRECTOR ( C & MDD II )<br>DEPUTY DIRECTOR ( C & MDD II )<br>( <i>Alternate</i> )<br>SHRI R. K. GATTANI<br>SHRI R. K. VAISHNAVI ( <i>Alternate</i> )<br>SHRI J. SEN GUPTA<br>SHRI P. J. JAGUS<br>DR A. K. CHATTERJEE ( <i>Alternate</i> )<br>JOINT DIRECTOR, STANDARDS<br>( B & S ) CB-I<br>JOINT DIRECTOR STANDARDS<br>( B & S )/CB-II ( <i>Alternate</i> )<br>SHRI R. L. KAPOOR<br>SHRI R. K. DATTA ( <i>Alternate</i> )<br>SHRI W. N. KARODE<br>SHRI R. KUNJITHAPATTAM<br>SHRI G. K. MAJUMDAR |  |   |
|   |  | National Test House, Calcutta<br>Directorate General of Technical Development, New Delhi<br>Cement Manufacturers Association, Bombay<br>Irrigation Department, Government of Punjab<br>Gujarat Engineering Research Institute, Vadodara<br>Maharashtra Engineering Research Institute, Nasik<br>Central Water Commission, New Delhi<br>Shree Digvijay Cement Co Ltd, Bombay<br>National Buildings Organization, New Delhi<br>The Associated Cement Companies Ltd, Bombay<br>Research, Designs and Standards Organization, Lucknow<br>Roads Wing ( Ministry of Transport ) ( Department of Surface Transport ), New Delhi<br>The Hindustan Construction Co Ltd, Bombay<br>Chettinad Cement Corporation Ltd, Poliyur, Tamil Nadu<br>Hospital Services Consultancy Corporation ( India ) Ltd,<br>New Delhi |



*Members*

SHRI K. P. MOHIDEEN  
 SHRI NIRMAL SINGH  
     SHRI S. S. MIGLANI ( *Alternate* )  
 SHRI Y. R. PHULL  
     SHRI S. S. SEEHRA ( *Alternate* )  
 SHRI A. V. RAMANA  
     DR K. C. NARANG ( *Alternate* )  
 COL V. K. RAO  
     SHRI N. S. GALANDE ( *Alternate* )  
 SHRI S. A. REDDI  
 DR S. S. REHSI  
     DR IRSHAD MASOOD ( *Alternate* )  
 SHRI A. U. RUHSINGHANI  
     SHRI M. P. SINGH  
 SUPERINTENDING ENGINEER (D)  
     SENIOR DEPUTY CHIEF ENGINEER  
     ( GENERAL ) ( *Alternate* )  
 SHRI L. SWAROOP  
     SHRI H. BHATTACHARYYA ( *Alternate* )  
 SHRI V. M. WAD

*Representing*

Central Warehousing Corporation, New Delhi  
 Development Commissioner for Cement Industry ( Ministry of  
     Industry )  
 Central Road Research Institute ( CSIR ), New Delhi  
 Dalmia Cement ( Bharat ) Ltd, New Delhi  
 Engineer-in-Chief's Branch, Army Headquarters  
 Gammon India Ltd, Bombay  
 Central Building Research Institute ( CSIR ), Roorkee  
 Cement Corporation of India Ltd, New Delhi  
 Federation of Mini Cement Plants, New Delhi  
 Public Works Department, Government of Tamil Nadu  
 Orissa Cement Ltd, New Delhi  
 Bhilai Steel Plant, Bhilai

### **Standard Mark**

The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

## Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

### Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

### Revision of Indian Standards

Indian Standards are reviewed periodically and revised, when necessary and amendments, if any, are issued from time to time. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition. Comments on this Indian Standard may be sent to BIS giving the following reference:

Doc : No. BDC 2 ( 4668 )

### Amendments Issued Since Publication

| Amend No. | Date of Issue | Text Affected |
|-----------|---------------|---------------|
|           |               |               |
|           |               |               |
|           |               |               |
|           |               |               |

## BUREAU OF INDIAN STANDARDS

### Headquarters :

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002  
Telephones : 331 01 31, 331 13 75

Telegrams : Manaksanstha  
( Common to all Offices )

### Regional Offices :

|  | Telephone                          |
|--|------------------------------------|
| Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg<br>NEW DELHI 110002  | { 331 01 31<br>331 13 75           |
| Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola<br>CALCUTTA 700054                                    | 36 24 99                           |
| Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036   | { 2 18 43<br>3 16 41               |
| Southern : C. I. T. Campus, IV Cross Road, MADRAS 600113   | { 41 24 42<br>41 25 19<br>41 29 16 |
| Western : Manakalaya, E9 MIDC, Marol, Andheri ( East )<br>BOMBAY 400093  | 6 32 92 95                         |
| Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR.<br>GUWAHATI. HYDERABAD. JAIPUR. KANPUR. PATNA.<br>TRIVANDRUM. |                                    |

**AMENDMENT NO. 1 JUNE 1991**  
**TO**  
**IS 12600 : 1989 PORTLAND CEMENT, LOW**  
**HEAT — SPECIFICATION**

( Page 3, clause 9.2.1.1 ) — Insert the following new clauses after 9.2.1.1:

“9.2.2 When cement is intended for export and if the purchaser so requires, packing of cement may be done in bags other than those given in 9.2 and 9.2.1 with an average net mass of cement per bag as agreed to between the purchaser and the manufacturer.

9.2.2.1 For this purpose the permission of the certifying authority shall be obtained in advance for each export order.

9.2.2.2 The words ‘FOR EXPORT’ and the average net mass of cement per bag shall be clearly marked in indelible ink on each bag.

9.2.2.3 The packing material shall be as agreed to between the supplier and the purchaser.

9.2.2.4 The tolerance requirements for the mass of cement packed in bags shall be as given in 9.2.1.1 except the average net mass which shall be equal to or more than quantity in 9.2.2.”

( CED 2 )

**AMENDMENT NO. 2 NOVEMBER 1991**  
**TO**  
**IS 12600 : 1989 PORTLAND CEMENT, LOW HEAT —**  
**SPECIFICATION**

*( Page 4, clause B-1.2 )* — Substitute 'up to 25 tonnes' for ' of 20 to 25 tonnes'.

( CED 2 )

---

Reprography Unit, BIS, New Delhi, India

**AMENDMENT NO. 3 JUNE 1993**  
**TO**  
**IS 12600 : 1989 PORTLAND CEMENT, LOW HEAT —**  
**SPECIFICATION**

[ *Page 3, clause 9.2.1.1 ( see also Amendment No. 1 )* ] — Substitute the following for the existing clauses 9.2.2 to 9.2.2.4:

**“9.2.2** When cement is intended for export and if the purchaser so requires, packing of cement may be done in bags or in drums with an average net mass of cement per bag or drum as agreed to between the purchaser and the manufacturer.

**9.2.2.1** For this purpose the permission of the certifying authority shall be obtained in advance for each export order.

**9.2.2.2** The words ‘FOR EXPORT’ and the average net mass of cement per bag/drum shall be clearly marked in indelible ink on each bag/drum.

**9.2.2.3** The packing material shall be as agreed to between the manufacturer and the purchaser.

**9.2.2.4** The tolerance requirements for the mass of cement packed in bags/drum shall be as given in 9.2.1.1 except the average net mass which shall be equal to or more than the quantity in 9.2.2.”

( CED 2 )

---

Reprography Unit, BIS, New Delhi, India

**AMENDMENT NO. 4   APRIL 2000**  
**TO**  
**IS 12600 : 1989   PORTLAND CEMENT, LOW**  
**HEAT — SPECIFICATION**

Substitute 'net mass' *for* 'average net mass' wherever it appears in the standard.

( CED 2 )

---

Reprography Unit, BIS, New Delhi, India

**AMENDMENT NO. 5   APRIL 2002**  
**TO**  
**IS 12600 : 1989   PORTLAND CEMENT, LOW HEAT —**  
**SPECIFICATION**

*( Page 2, clause 6.3.1, line 6 )* — Substitute 'less than' for 'not less than'.

( CED 2 )

---

Reprography Unit, BIS, New Delhi, India