

Indian Standard

**ORDINARY PORTLAND CEMENT, 33 GRADE —
SPECIFICATION**

(Fourth Revision)

भारतीय मानक

साधारण पोर्टलैंड सीमेंट, 33 ग्रेड — विशिष्ट

(चौथा पुनरीक्षण)

Second Reprint JULY 1993

UDC 666.942

© BIS 1990

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

FOREWORD

This Indian Standard (Fourth Revision) was adopted by the Bureau of Indian Standards on 20 June 1989, after the draft finalized by the Cement and Concrete Sectional Committee had been approved by the Civil Engineering Division Council.

This standard was first published in 1951 and subsequently revised in 1958, 1967 and 1976. This fourth revision incorporates the experience gained with the use of this specification and brings the standard in line with the present practices followed in the production and testing of cement.

Since the third revision of this standard was published, a large number of amendments have been issued from time to time in order to modify various requirements based on experience gained with the use of the standard and the requirements of the users, and also keeping in view the raw materials and fuels available in the country for the manufacture of cement. The important amendments include increase in insoluble residue from 2 to 4 percent, incorporating 33 MPa as the 28-day compressive strength, making autoclave soundness test compulsory irrespective of magnesia content, incorporating a provision for retest in respect of autoclave soundness test after aeration of the cement, incorporating a clause on false set and permitting packaging of cement in 25-kg bags. In view of these large number of amendments, the Sectional Committee decided to bring out this fourth revision of the standard incorporating all these amendments so as to make it more convenient for the users.

The Sectional Committee also decided that ordinary Portland cement should be designated by its 28-day compressive strength and, therefore, the title of this standard has been modified in this revision, after taking out the provisions relating to low heat Portland cement for covering in a separate standard.

Mass of cement packed in bags and the tolerance requirements for the mass of cement packed in bags shall be in accordance with the relevant provisions of the *Standards of Weights and Measures (Packaged Commodities) Rules, 1977* and B-1.2 (see Annex B). Any modification in these rules in respect of tolerance on mass of cement would apply automatically to this standard.

This standard contains clause 11.4.1 which gives option to the purchaser and clauses 6.5 and 9.3 which call for agreement between the purchaser and the supplier.

In the formulation of this standard, considerable assistance has been rendered by the National Council for Cement and Building Materials, New Delhi as many of the revisions are based on the studies carried out by them.

The composition of the technical committee responsible for the formulation of this standard is given in Annex C.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (revised)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

ORDINARY PORTLAND CEMENT, 33 GRADE — SPECIFICATION

(Fourth Revision)

1 SCOPE

1.1 This standard covers the manufacture and chemical and physical requirements of 33 grade ordinary Portland cement.

2 REFERENCES

2.1 The Indian Standards listed in Annex A are necessary adjuncts to this standard.

3 TERMINOLOGY

3.1 For the purpose of this standard, the definitions given in IS 4845 : 1968 shall apply.

4 MANUFACTURE

4.1 33 grade ordinary Portland cement shall be manufactured by intimately mixing together

calcareous and argillaceous and/or other silica, alumina or iron oxide bearing materials, burning them at a clinkering temperature and grinding the resultant clinker so as to produce a cement capable of complying with this specification. No material shall be added after burning, other than gypsum (natural or chemical) or water or both, and not more than one percent of air-entraining agents or other agents, which have proved not to be harmful.

NOTE — Chemical gypsum shall be added provided that the performance requirements of the final product as specified in this standard are met with.

5 CHEMICAL REQUIREMENTS

5.1 When tested in accordance with the methods given in IS 4032 : 1985, 33 grade ordinary Portland cement shall comply with the chemical requirements given in Table 1.

Table 1 Chemical Requirements for 33 Grade Ordinary Portland Cement

Sl No. (1)	Characteristic (2)	Requirement (3)
i)	Ratio of percentage of lime to percentages of silica, alumina and iron oxide, when calculated by the formula $\frac{\text{CaO} - 0.7 \text{ SO}_3}{2.8 \text{ SiO}_2 + 1.2 \text{ Al}_2\text{O}_3 + 0.65 \text{ Fe}_2\text{O}_3}$	Not greater than 1.02 and not less than 0.66
ii)	Ratio of percentage of alumina to that of iron oxide	Not less than 0.66
iii)	Insoluble residue, percent by mass	Not more than 4 percent
iv)	Magnesia, percent by mass	Not more than 6 percent
v)	Total sulphur content calculated as sulphuric anhydride (SO ₃), percent by mass	Not more than 2.5 and 3.0 when tri-calcium aluminate (see Note 1) percent by mass is 5 or less and greater than 5 respectively
vi)	Total loss on ignition	Not more than 5 percent

NOTES

1 The tri-calcium aluminate content (C₃A) is calculated by the formula:

$$C_3A = 2.65 (\text{Al}_2\text{O}_3) - 1.69 (\text{Fe}_2\text{O}_3)$$

Where each symbol in brackets refers to the percentage (by mass of total cement) of the oxide, excluding any contained in the insoluble residue referred at Sl No. (iii).

2 Alkali aggregate reactions have been noticed in aggregates in some parts of the country. On large and important jobs where the concrete is likely to be exposed to humid atmosphere or wetting action, it is advisable that the aggregate be tested for alkali aggregate reaction. In the case of reactive aggregates, the use of cement with alkali content below 0.6 percent expressed as sodium oxide (Na₂O), is recommended. Where, however, such cements are not available, use of Portland pozzolana cement or cement pozzolanic admixture is recommended.

3 Total chloride content in cement shall not exceed 0.05 percent by mass for cement used in prestressed concrete structures and long span reinforced concrete structures (Method of test for determination of chloride content in cement is given in IS 12423 : 1988).

4 The limit of total chloride content in cement for use in plain and other reinforced concrete structures is being reviewed. Till that time, the limit may be mutually agreed to between the purchaser and the manufacturer.

6 PHYSICAL REQUIREMENTS

6.1 Fineness

When tested for fineness by Blaine's air permeability method as described in IS 4031 (Part 2) : 1988, the specific surface of cement shall not be less than 225 m²/kg.

6.2 Soundness

6.2.1 When tested by 'Le Chatelier' method and autoclave test described in IS 4031 (Part 3) : 1988, unaerated cement shall not have an expansion of more than 10 mm and 0.8 percent, respectively.

6.2.1.1 In the event of cements failing to comply with any one or both the requirements specified in **6.2.1**, further tests in respect of each failure shall be made as described in IS 4031 (Part 3) : 1988 from another portion of the same sample after aeration. The aeration shall be done by spreading out the sample to a depth of 75 mm at a relative humidity of 50 to 80 percent for a total period of 7 days. The expansion of cements so aerated shall be not more than 5 mm and 0.6 percent when tested by 'Le Chatelier' method and autoclave test respectively.

6.3 Setting Time

The setting time of the cements, when tested by the Vicat apparatus method described in IS 4031 (Part 5) : 1988 shall conform to the following requirements:

- a) Initial setting time in minutes, not less than 30; and
- b) Final setting time in minutes, not more than 600.

6.3.1 If cement exhibits false set, the ratio of final penetration measured after 5 minutes of completion of mixing period to the initial penetration measured exactly after 20 seconds of completion of mixing period, expressed as percent, shall be not less than 50. In the event of cement exhibiting false set, the initial and final setting time of cement when tested by the method described in IS 4031 (Part 5) : 1988 after breaking the false set, shall conform to **6.3**.

6.4 Compressive Strength

The average compressive strength of at least three mortar cubes (area of face 50 cm²) composed of one part of cement, three parts of standard sand (conforming to IS 650 : 1966) by mass and $\left(\frac{P}{4} + 3.0 \right)$ percent (of combined mass of cement plus sand) water and prepared, stored and tested

in the manner described in IS 4031 (Part 6) : 1988 shall be as follows:

- a) 72±1 hour : not less than 16 MPa,
- b) 168±2 hours : not less than 22 MPa, and
- c) 672±4 hours : not less than 33 MPa.

NOTE — *P* is the percentage of water required to produce a paste of standard consistency (see 11.3).

6.5 By agreement between the purchaser and the manufacturer, transverse strength test of plastic mortar in accordance with the method described in IS 4031 (Part 8) : 1988 may be specified in addition to the test specified in **6.4**. The permissible values of the transverse strength shall be mutually agreed to between the purchaser and the supplier at the time of placing the order.

6.6 Notwithstanding the strength requirements specified in **6.4** and **6.5**, the cement shall show a progressive increase in strength from the strength at 72 hours.

7 STORAGE

7.1 The cement shall be stored in such a manner as to permit easy access for proper inspection and identification, and in a suitable weather-tight building to protect the cement from dampness and to minimize warehouse deterioration.

8 MANUFACTURER'S CERTIFICATE

8.1 The manufacturer shall satisfy himself that the cement conforms to the requirements of this standard and, if requested, shall furnish a certificate to this effect to the purchaser or his representative, within ten days of despatch of the cement.

8.2 The manufacturer shall furnish a certificate, within ten days of despatch of the cement, indicating the total chloride content in percent by mass of cement.

9 DELIVERY

9.1 The cement shall be packed in bags [jute sacking bag conforming to IS 2580 : 1982, double hessian bituminized (CRI type), multi-wall paper conforming to IS 11761 : 1986, polyethylene lined (CRI type) jute, light weight jute conforming to IS 12154 : 1987, woven HDPE conforming to IS 11652 : 1986, woven polypropylene conforming to IS 11653 : 1986, jute synthetic union conforming to IS 12174 : 1987 or any other approved composite bag] bearing the manufacturer's name or his registered trade-mark, if any. The words '33 grade ordinary Portland cement', and the number of bags (net mass) to the tonne or the nominal average net mass of the cement shall be legibly

and indelibly marked on each bag. Bags shall be in good condition at the time of inspection.

9.1.1 Similar information shall be provided in the delivery advices accompanying the shipment of packed or bulk cement (*see* 9.3).

9.2 The average net mass of cement per bag shall be 50 kg (*see* Annex B).

9.2.1 The average net mass of cement per bag may also be 25 kg subject to tolerances as given in 9.2.1.1 and packed in suitable bags as agreed to between the purchaser and the manufacturer.

9.2.1.1 The number of bags in a sample taken for weighment showing a minus error greater than 2 percent of the specified net mass shall be not more than 5 percent of the bags in the sample. Also the minus error in none of such bags in the sample shall exceed 4 percent of the specified net mass of cement in the bag. However, the average net mass of cement in a sample shall be equal to or more than 25 kg.

9.3 Supplies of cement in bulk may be made by arrangement between the purchaser and the supplier (manufacturer or stockist).

NOTE — A single bag or container containing 1 000 kg and more, net mass of cement shall be considered as the bulk supply of cement. Supplies of cement may also be made in intermediate containers, for example, drums of 200 kg, by agreement between the purchaser and the manufacturer.

10 SAMPLING

10.1 A sample or samples for testing may be taken by the purchaser or his representative, or by any person appointed to superintend the work for purpose of which the cement is required or by the latter's representative.

10.1.1 The samples shall be taken within three weeks of the delivery and all the tests shall be commenced within one week of sampling.

10.1.2 When it is not possible to test the samples within one week, the samples shall be packed and stored in air-tight containers till such time that they are tested.

10.2 In addition to the requirements of 10.1, the methods and procedure of sampling shall be in accordance with IS 3535 : 1986.

10.3 Facilities for Sampling and Identification

The manufacturer or the supplier shall afford every facility, and shall provide all labour and materials for taking and packing the samples for testing the cement and for subsequent identification of cement sampled.

11 TESTS

11.1 The sample or samples of cement for test shall be taken as described in 10 and shall be tested in the manner described in the relevant clauses.

11.2 Temperature for Testing

The temperature range within which physical tests may be carried out shall, as far as possible, be $27 \pm 2^\circ\text{C}$. The actual temperature during the testing shall be recorded.

11.3 Consistency of Standard Cement Paste

The quantity of water required to produce a paste of standard consistency, to be used for the determination of water content of mortar for compressive strength tests and for the determination of soundness and setting time, shall be obtained by the method described in IS 4031 (Part 4) : 1988.

11.4 Independent Testing

11.4.1 If the purchaser or his representative requires independent tests, the samples shall be taken before or immediately after delivery at the option of the purchaser or his representative, and the tests shall be carried out in accordance with this standard on the written instructions of the purchaser or his representative.

11.4.2 Cost of Testing

The manufacturer shall supply, free of charge, the cement required for testing. Unless otherwise specified in the enquiry and order, the cost of the tests shall be borne as follows:

- a) By the manufacturer if the results show that the cement does not comply with the requirements of this standard, and
- b) By the purchaser if the results show that the cement complies with the requirement of this standard.

11.4.3 After a representative sample has been drawn, tests on the sample shall be carried out as expeditiously as possible.

12 REJECTION

12.1 Cement may be rejected if it does not comply with any of the requirements of this specification.

12.2 Cement remaining in bulk storage at the mill, prior to shipment, for more than six months, or cement in bags, in local storage in the hands of a vendor for more than 3 months after completion of tests, may be retested before use and may be rejected if it fails to conform to any of the requirements of this specification.

ANNEX A

(Clause 2.1)

LIST OF REFERRED INDIAN STANDARDS

IS No.	Title	IS No.	Title
IS 650 : 1966	Standard sand for testing of cement (<i>first revision</i>)	IS 11652 : 1986	High density polyethylene (HDPE) woven sacks for packing cement
IS 2580 : 1982	Jute sacking bags for packing cement (<i>second revision</i>)	IS 11653 : 1986	Polypropylene (PP) woven sacks for packing cement
IS 3535 : 1986	Methods of sampling hydraulic cements (<i>first revision</i>)	IS 11761 : 1986	Multi wall paper sacks for cement, valved-sewn-gusseted type
IS 4031	Methods of physical tests for (Parts I to 13) hydraulic cement	IS 12154 : 1987	Light weight jute bags for packing cement
IS 4032 : 1985	Method of chemical analysis of hydraulic cement (<i>first revision</i>)	IS 12174 : 1987	Jute synthetic union bags for packing cement
IS 4845 : 1968	Definitions and terminology relating to hydraulic cement	IS 12423-1988	Method for colorimetric analysis of hydraulic cement
IS 4905 : 1968	Methods for random sampling		

ANNEX B

(Clause 9.2 and Foreword)

TOLERANCE REQUIREMENTS FOR THE MASS OF CEMENT PACKED IN BAGS

B-1 The average net mass of cement packed in bags at the plant in a sample shall be equal to or more than 50 kg. The number of bags in a sample shall be as given below:

Batch Size	Sample Size
100 to 150	20
151 to 280	32
281 to 500	50
501 to 1 200	80
1 201 to 3 200	125
3 201 and over	200

The bags in a sample shall be selected at random. For methods of random sampling, IS 4905 : 1968 may be referred to.

B-1.1 The number of bags in a sample showing a minus error greater than 2 percent of the specified net mass (50 kg) shall be not more than 5 percent

of the bags in the sample. Also the minus error in none of such bags in the sample shall exceed 4 percent of the specified net mass of cement in the bag.

NOTE — The matter given in **B-1** and **B-1.1** are extracts based on the *Standards of Weights and Measures (Packaged Commodities) Rules, 1977* to which reference shall be made for full details. Any modification made in these Rules and other related Acts and Rules would apply automatically.

B-1.2 In case of a wagon/truck load of 20 to 25 tonnes, the overall tolerance on net mass of cement shall be 0 to +0.5 percent.

NOTE — The mass of a jute sacking bag conforming to IS 2580 : 1982 to hold 50 kg of cement is 531 g, the mass of a double hessian bituminized (CRI type) bag to hold 50 kg of cement is 630 g, the mass of a 6-ply paper bag to hold 50 kg of cement is approximately 400 g and the mass of a polyethylene lined (CRI type) jute bag to hold 50 kg of cement is approximately 480 g.

ANNEX C**COMPOSITION OF THE TECHNICAL COMMITTEE****Cement and Concrete Sectional Committee, CED 2***Chairman*

DR H. C. VISVESVARAYA

Members

SHRI K. P. BANERJEE

SHRI HARISH N. MALANI (*Alternate*)

SHRI S. K. BANERJEE

CHIEF ENGINEER (BD)

SHRI J. C. BASUR (*Alternate*)

CHIEF ENGINEER (DESIGNS)

SUPERINTENDING ENGINEER (S & S)
(*Alternate*)

CHIEF ENGINEER (RESEARCH-CUM-DIRECTOR)

RESEARCH OFFICER (CONCRETE TECHNOLOGY) (*Alternate*)

DIRECTOR

JOINT DIRECTOR (*Alternate*)

DIRECTOR

CHIEF RESEARCH OFFICER (*Alternate*)

DIRECTOR (C & MDD-II)

DEPUTY DIRECTOR (C & MDD-II)
(*Alternate*)

SHRI V. K. GHANEKAR

SHRI S. GOPINATH

SHRI A. K. GUPTA

SHRI J. SEN GUPTA

SHRI P. J. JAGUS

DR A. K. CHATTERJEE (*Alternate*)

JOINT DIRECTOR STANDARDS (B & S)/CB-I

JOINT DIRECTOR STANDARDS (B & S)/CB-II
(*Alternate*)

SHRI N. G. JOSHI

SHRI R. L. KAPOOR

SHRI R. K. SAXENA (*Alternate*)

DR A. K. MULICK

SHRI G. K. MAJUMDAR

SHRI P. N. MEHTA

SHRI S. K. MATHUR (*Alternate*)

SHRI NIRMAL SINGH

SHRI S. S. MIGLANI (*Alternate*)

SHRI S. N. PAL

SHRI BIMAN DASGUPTA (*Alternate*)

SHRI R. C. PARATE

LT-COL R. K. SINGH (*Alternate*)

SHRI H. S. PASRICHA

SHRI Y. R. PHULL

SHRI S. S. SEEHRA (*Alternate*)

DR MOHAN RAI

DR S. S. REHSI (*Alternate*)

SHRI A. V. RAMANA

DR K. C. NARANG (*Alternate*)

SHRI G. RAMDAS

SHRI T. N. SUBBA RAO

SHRI S. A. REDDI (*Alternate*)*Representing*

National Council for Cement and Building Materials, New Delhi

Larsen and Toubro Limited, Bombay

National Test House, Calcutta

Bhakra Beas Management Board, Nangal Township

Central Public Works Department, New Delhi

Irrigation Department, Government of Punjab

A. P. Engineering Research Laboratories, Hyderabad

Central Soil and Materials Research Station, New Delhi

Central Water Commission, New Delhi

Structural Engineering Research Centre (CSIR), Ghaziabad

The India Cements Limited, Madras

Hyderabad Industries Limited, Hyderabad

National Buildings Organization, New Delhi

The Associated Cement Companies Ltd, Bombay

Research, Designs and Standards Organization (Ministry of Railways), Lucknow

Indian Hume Pipes Co Limited, Bombay

Roads Wing (Ministry of Transport), Department of Surface Transport, New Delhi

National Council for Cement and Building Materials, New Delhi
Hospital Services Consultancy Corporation (India) Ltd,
New Delhi

Geological Survey of India, Calcutta

Development Commissioner for Cement Industry (Ministry of Industry), New Delhi

M.N. Dastur and Company Private Limited, Calcutta

Engineer-in-Chief's Branch, Army Headquarters

Hindustan Prefab Limited, New Delhi

Indian Roads Congress, New Delhi; and Central Road Research Institute (CSIR), New Delhi

Central Road Research Institute (CSIR), New Delhi

Central Building Research Institute (CSIR), Roorkee

Dalmia Cement (Bharat) Limited, New Delhi

Directorate General of Supplies and Disposals, New Delhi

Gammon India Limited, Bombay

Members

DR M. RAMAIAH
DR A. G. MADHAVA RAO (*Alternate*)
SHRI A. U. RIJHSINGHANI
SHRI C. S. SHARMA (*Alternate*)
SECRETARY
SHRI K. R. SAXENA (*Alternate*)
SUPERINTENDING ENGINEER (DESIGNS)
EXECUTIVE ENGINEER (SMD DIVISION)
(*Alternate*)
SHRI L. SWAROOP
SHRI H. BHATTACHARYYA
(*Alternate*)
SHRI S. K. GUHA THAKURTA
SHRI S. P. SANKARNARAYANAN
(*Alternate*)
DR H. C. VISVESVARAYA
SHRI D. C. CHATURVEDI (*Alternate*)
SHRI G. RAMAN,
Director (Civ Engg)

Representing

Structural Engineering Research Centre (CSIR), Madras
Cement Corporation of India, New Delhi
Central Board of Irrigation and Power, New Delhi
Public Works Department, Government of Tamil Nadu
Orissa Cement Limited, New Delhi
Gannon Dunkerly & Co Ltd, Bombay
The Institution of Engineers (India), Calcutta
Director General, BIS (*Ex-officio Member*)

Secretary

SHRI N. C. BANDYOPADHYAY
Joint Director (Civ Engg), BIS

Cement, Pozzolana and Cement Additives Subcommittee, CED 2 : I

Convener

DR H. C. VISVESVARAYA

National Council for Cement and Building Materials,
New Delhi

Members

DR A. K. MULLICK DR (SMT) S. LAXMI	} (<i>Alternates to Dr H. C. Visvesvaraya</i>)	
SHRI S. K. BANERJEE SHRI N. G. BASAK SHRI T. MADHESHWAR (<i>Alternate</i>) SHRI SOMNATH BANERJEE CHIEF ENGINEER (RESEARCH-CUM-DIRECTOR) RESEARCH OFFICER (CT) (<i>Alternate</i>) SHRI N. B. DESAI SHRI J. K. PATEL (<i>Alternate</i>) DIRECTOR RESEARCH OFFICER (<i>Alternate</i>) DIRECTOR (C & MDD II) DEPUTY DIRECTOR (C & MDD II) (<i>Alternate</i>) SHRI R. K. GATTANI SHRI R. K. VAISHNAVI (<i>Alternate</i>) SHRI J. SEN GUPTA SHRI P. J. JAGUS DR A. K. CHATTERJEE (<i>Alternate</i>) JOINT DIRECTOR, STANDARDS (B & S) CB-I JOINT DIRECTOR STANDARDS (B & S)/CB-II (<i>Alternate</i>) SHRI R. L. KAPOOR SHRI R. K. DATTA (<i>Alternate</i>) SHRI W. N. KARODE SHRI R. KUNITHAPATTAM SHRI G. K. MAJUMDAR		National Test House, Calcutta Directorate General of Technical Development, New Delhi Cement Manufacturers Association, Bombay Irrigation Department, Government of Punjab Gujarat Engineering Research Institute, Vadodara Maharashtra Engineering Research Institute, Nasik Central Water Commission, New Delhi Shree Digvijay Cement Co Ltd, Bombay National Buildings Organization, New Delhi The Associated Cement Companies Ltd, Bombay Research, Designs and Standards Organization, Lucknow Roads Wing (Ministry of Transport) (Department of Surface Transport), New Delhi The Hindustan Construction Co Ltd, Bombay Chattinad Cement Corporation Ltd, Poliyur, Tamil Nadu Hospital Services Consultancy Corporation (India) Ltd, New Delhi

Members

SHRI K. P. MOHIDEEN
 SHRI NIRMAL SINGH
 SHRI S. S. MIGLANI (*Alternate*)
 SHRI Y. R. PHULL
 SHRI S. S. SEEHRA (*Alternate*)
 SHRI A. V. RAMANA
 DR K. C. NARANG (*Alternate*)
 COL V. K. RAO
 SHRI N. S. GALANDE (*Alternate*)
 SHRI S. A. REDDI
 DR S. S. REHSI
 DR IRSHAD MASOOD (*Alternate*)
 SHRI A. U. RIJHSINGHANI
 SHRI M. P. SINGH
 SUPERINTENDING ENGINEER (D)
 SENIOR DEPUTY CHIEF ENGINEER
 (GENERAL) (*Alternate*)
 SHRI L. SWAROOP
 SHRI H. BHATTACHARYYA (*Alternate*)
 SHRI V. M. WAD

Representing

Central Warehousing Corporation, New Delhi
 Development Commissioner for Cement Industry (Ministry of Industry)
 Central Road Research Institute (CSIR), New Delhi
 Dalmia Cement (Bharat) Ltd, New Delhi
 Engineer-in-Chief's Branch, Army Headquarters
 Gammon India Ltd, Bombay
 Central Building Research Institute (CSIR), Roorkee
 Cement Corporation of India Ltd, New Delhi
 Federation of Mini Cement Plants, New Delhi
 Public Works Department, Government of Tamil Nadu
 Orissa Cement Ltd, New Delhi
 Bhilai Steel Plant, Bhilai

Standard Mark

The use of the Standard Mark is governed by the provisions of the *Bureau of the Indian Standards, Act, 1986* and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

Bureau of Indian Standard

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designation. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Revision of Indian Standards

Indian Standards are reviewed periodically and revised, when necessary and amendments, if any, are issued from time to time. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition. Comments on this Indian Standard may be sent to BIS giving the following reference:

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones : 331 01 31, 331 13 75

Telegrams : Manaksanstha
(Common to all Offices)

Regional Offices :

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg
NEW DELHI 110002

Telephone

{ 331 01 31
{ 331 13 75

Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola
CALCUTTA 700054

{ 37 84 99, 37 85 61,
{ 37 86 26, 37 85 62

Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036

{ 53 38 43, 53 16 40,
{ 53 23 84

Southern : C. I. T. Campus, IV Cross Road, MADRAS 600113

{ 41 24 42, 41 25 19,
{ 41 23 15, 41 29 16

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)
BOMBAY 400093

{ 632 92 95, 63 27 80,
{ 632 78 92

Branches : AHMADABAD, BANGALORE, BHOPAL, BHUBANESHWAR, COIMBATORE,
FARIDABAD, GHAZIABAD, GUWAHATI, HYDERABAD, JAIPUR, KANPUR,
LUCKNOW, PATNA, THIRUVANANTHAPURAM.

AMENDMENT NO. 1 JULY 1990
TO
IS : 269 - 1989 ORDINARY PORTLAND CEMENT,
33 GRADE — SPECIFICATION

(Fourth Revision)

(Page 3, clause 9.2.1.1) — Insert the following new clauses after 9.2.1.1:

9.2.2 When cement is intended for export and if the purchaser so requires, packing of cement may be done in bags other than those given in 9.2 and 9.2.1 with an average net mass of cement per bag as agreed to between the purchaser and the manufacturer.

9.2.2.1 For this purpose the permission of the certifying authority shall be obtained in advance for each export order.

9.2.2.2 The words 'FOR EXPORT' and the average net mass of cement per bag shall be clearly marked in indelible ink on each bag.

9.2.2.3 The packing material shall be as agreed to between the supplier and the purchaser.

9.2.2.4 The tolerance requirements for the mass of cement packed in bags shall be as given in 9.2.1.1 except the average net mass which shall be equal to or more than the quantity in 9.2.2.'

(CED 2)

AMENDMENT NO. 2 NOVEMBER 1991
TO
IS 269 : 1989 ORDINARY PORTLAND CEMENT, 33
GRADE — SPECIFICATION

(Fourth Revision)

(Page 4, clause B-1.2) — Substitute 'up to 25 tonnes' for 'of 20 to 25 tonnes'.

(CED 2)

Reprography Unit, BIS, New Delhi, India

AMENDMENT NO. 3 JUNE 1993
TO
IS 269 : 1989 ORDINARY PORTLAND CEMENT, 33
GRADE — SPECIFICATION

(Fourth Revision)

[Page 3, clause 9.2.1.1 (see also Amendment No. 1)] — Substitute the following for the existing clauses 9.2.2 to 9.2.2.4:

“9.2.2 When cement is intended for export and if the purchaser so requires, packing of cement may be done in bags or in drums with an average net mass of cement per bag or drum as agreed to between the purchaser and the manufacturer.

9.2.2.1 For this purpose the permission of the certifying authority shall be obtained in advance for each export order.

9.2.2.2 The words ‘FOR EXPORT’ and the average net mass of cement per bag/drum shall be clearly marked in indelible ink on each bag/drum.

9.2.2.3 The packing material shall be as agreed to between the manufacturer and the purchaser.

9.2.2.4 The tolerance requirements for the mass of cement packed in bags/drum shall be as given in 9.2.1.1 except the average net mass which shall be equal to or more than the quantity in 9.2.2.”

AMENDMENT NO. 4 NOVEMBER 1998
TO
IS 269 : 1989 ORDINARY PORTLAND CEMENT,
33 GRADE — SPECIFICATION

(Fourth Revision)

(Page 3, clause 9.2.1) — Substitute the following for the existing clause:

9.2.1 The average net mass of cement per bag may also be 25 kg, 10 kg, 5 kg, 2 kg or 1 kg subject to tolerances as given in 9.2.1.1 and packed in suitable bag as agreed to between the purchaser and the manufacturer.'

(Page 3, clause 9.2.1.1) — Substitute the following for the existing clause:

9.2.1.1 The number of bags in a sample taken for weighment showing a minus error greater than 2 percent of the specified net mass shall not be more than 5 percent of the bags in the sample. Also the minus error in none of such bags in the sample shall exceed 4 percent of the specified net mass of cement in the bag. However, the average mass of the cement in a sample shall be equal to or more than 25 kg, 10 kg, 5 kg, 2 kg or 1 kg, as the case may be.'

(Page 4, clause B-1.2) — Substitute 'up to 25 tonnes' for '20 to 25 tonnes'.

(CED 2)

AMENDMENT NO. 5 OCTOBER 1999
TO
IS 269 : 1989 ORDINARY PORTLAND CEMENT,
33 GRADE — SPECIFICATION

(Fourth Revision)

[*Page 1, Table 1, Sl No. (iii), col 3*] — Substitute '4.0' for '4'.

[*Page 1, Table 1, Sl No. (iv), col 3*] — Substitute '6.0' for '6'.

(*Page 1, Table 1, Notes 3 and 4*) — Delete.

(*Page 1, clause 5.1*) — Insert the following after the clause:

'5.2 Total chloride content in cement shall not exceed 0.1 percent by mass for cement used in structures other than prestressed concrete. For determination of chloride content in cement, IS 12423 may be referred.

NOTE — For use in special structures like prestressed concrete, where chloride is a critical parameter, the limit of chloride content shall be 0.05 percent and shall be required to be measured if desired by the purchaser.'

(CED 2)

**AMENDMENT NO. 6 MAY 2000
TO
IS 269 : 1989 ORDINARY PORTLAND CEMENT,
33 GRADE — SPECIFICATION**

(Fourth Revision)

Substitute 'net mass' for 'nominal average net mass', 'average net mass' and 'average mass' wherever these appear in the standard.

(CED 2)

Reprography Unit, BIS, New Delhi, India

AMENDMENT NO. 7 DECEMBER 2003 TO IS 269 : 1989 ORDINARY PORTLAND CEMENT, 33 GRADE — SPECIFICATION

(*Fourth Revision*)

(*Page 1, clause 4.1, last sentence*) — Substitute the following for the existing sentence:

'No material shall be added after burning, other than gypsum (natural or chemical) or water or both; performance improvers; and not more than one percent of air-entraining agents or other agents including colouring agents, which have proved not to be harmful. Limit of addition of performance improvers shall be as follows and shall be inclusive of one percent additives as mentioned above:

<i>Performance Improver</i>	<i>Percentage Addition, Max</i>	<i>Requirement</i>
Fly ash	5	As per IS 3812 (Part 1)
Granulated slag	5	As per IS 12089
Silica fume	5	As per IS 15388
Limestone	5	CaCO ₃ content calculated from CaO content shall not be less than 75 percent when tested as per IS 1760 (Part 3)
Rice husk ash	5	a) Reactive silica shall not be less than 85 percent when tested as per IS 3812 (Part 1) b) Pozzolanic activity index shall not be less than 90 percent when tested as per 10 of IS 1727 c) Loss on ignition shall not be more than 8 percent when tested as per IS 1727
Metakaoline	5	a) Silicon dioxide (SiO ₂) plus aluminium oxide (Al ₂ O ₃) plus iron oxide (Fe ₂ O ₃) in percent by mass shall not be less than 95 percent when tested as per IS 1727 b) Loss on ignition shall not be more than 1 percent when tested as per IS 1727 c) Total alkalis as sodium oxide (Na ₂ O) in percent by mass shall not be more than 0.6 percent when tested as per IS 4032 d) Particles retained on 45 micron IS sieve (wet sieving) shall not be more than 1 percent when test as per IS 1727

Amend No. 7 to IS 269 : 1989

If a combination of above performance improvers is added, the maximum limit of addition shall be 5 percent.

[Page 1, Table 1, Sl No. (iii) (see also Amendment No. 5)] — Substitute the following for the existing matter:

Sl No. (1)	Characteristic (2)	Requirement (3)
iii)	Insoluble residue, percent by mass	a) In case no fly ash, silica fume, rice husk ash and metakaoline is added — Not more than 4.0 b) In case of addition of fly ash and/or silica fume and/or rice husk ash and/or metakaoline — Not more than 5.0

(Page 2, clause 6.3.1, line 6) — Substitute 'less than' for 'not less than'.

(Page 3, clause 9.1, last sentence) — Insert the following sentence before the existing sentence:

'Bags shall also be marked with the type and the percentage of performance improvers added.'

(Page 4, Annex A) — Insert the following matter:

IS No.	Title
1727 : 1967	Methods of test for pozzolanic materials (<i>first revision</i>)
1760 (Part 3): 1992	Methods of chemical analysis of limestone, dolomite and allied materials : Part 3 Determination of iron oxide, alumina, calcium oxide and magnesia (<i>first revision</i>)
3812 (Part 1) : 2003	Pulverized fuel ash — Specification : Part 1 For use as pozzolana in cement, cement mortar and concrete (<i>second revision</i>)
12089 : 1987	Granulated slag for the manufacture of Portland slag cement — Specification
15388 : 2003	Silica fume — Specification

(CED 2)