

भारतीय मानक

जल विरोधी पोर्टलैंड सीमेंट — विशिष्ट

(दूसरा पुनरीक्षण)

Indian Standard

**HYDROPHOBIC PORTLAND CEMENT —
SPECIFICATION**

(Second Revision)

(Second Reprint MAY 1998)

UDC 666.942.4/.7

© BIS 1991

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

July 1991

Price Group 3

FOREWORD

This Indian Standard (Second Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Cement and Concrete Sectional Committee had been approved by the Civil Engineering Division Council.

Hydrophobic cement deteriorates very little during prolonged storage under unfavourable conditions. This cement is obtained by intergrinding 33 grade ordinary Portland cement clinker with certain hydrophobic agents which will impart to the cement a water repelling property. The hydrophobic properties are due to the formation of a water repellant film around each particle of cement. This film is broken during the mixing of the concrete, and normal hydration takes place. Hydrophobic cement shall not be confused with waterproofing cements. A test on hydrophobicity is also included in this standard.

This standard was first issued as an emergency standard in 1976 and subsequently revised in 1978. Since publication of the first revision of this standard, amendments have been issued from time to time in order to modify various requirements based on the requirements of the users and also keeping in view the raw materials and fuel available in the country for manufacture of cement. The important amendments include modification in the tolerance requirements for the mass of cement packed in bags, permitting packaging of cement in 25 kg bags, making compulsory provision for issuing a certificate indicating the total chloride content in percent by mass of cement, permitting different bags for packing of cement, incorporating details for considering of supply of cement as bulk supply, etc. In view of these large number of amendments, the Committee decided to bring out the second revision of this standard incorporating all these amendments so as to make it convenient for the users.

Mass of cement packed in bags and the tolerance requirements for the mass of cement packed in bags shall be in accordance with the relevant provisions of the Standards of Weights and Measures (Packaged Commodities) Rules, 1977 and C-1.2 (see Annex C for information). Any modification in these rules in respect of tolerance on mass of cement would apply automatically to this standard.

The composition of the Technical Committee responsible for the formulation of this standard is given at Annex D.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (revised)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

HYDROPHOBIC PORTLAND CEMENT — SPECIFICATION

(Second Revision)

1 SCOPE

This standard covers the manufacture and chemical and physical requirements of hydrophobic Portland cement.

2 REFERENCES

The Indian Standards listed in Annex A are necessary adjuncts to this standard.

3 TERMINOLOGY

3.1 For the purpose of this standard, the definitions given in IS 4845 : 1968 and the following shall apply.

3.1.1 *Hydrophobic Cement*

Cement obtained by grinding 33 grade ordinary Portland cement clinker with an additive which will impart to ground cement, a water repelling property which shall be destroyed only by wet attrition, such as in concrete mixer. The hydrophobic quality of cement would facilitate its storage for longer periods in extremely wet climatic conditions.

4 MANUFACTURE

4.1 Hydrophobic cement shall be manufactured by intimately mixing together calcareous and argillaceous and/or other silica, alumina or iron oxide bearing materials, burning them at clinkering temperature and grinding the resultant clinker with natural or chemical gypsum and small quantities (0.1 to 0.5 percent by mass of clinker) of a hydrophobic agent.

NOTE — Some of the hydrophobic agents used in the manufacture of hydrophobic cement are oleic acid, naphthenic acid, stearic acid, pentachlorophenol, etc.

5 CHEMICAL REQUIREMENTS

5.1 The chemical requirements of hydrophobic cement shall be as laid in IS 269 : 1989.

6 PHYSICAL REQUIREMENTS

6.1 Fineness

When tested for fineness in terms of specific surface by Blaine's air permeability method as described in IS 4031 (Part 2) : 1988, the specific surface of the hydrophobic cement shall be not less than 350 m²/kg.

6.2 The physical requirements, such as soundness and setting time shall be as laid down in IS 269 : 1989.

6.3 Compressive Strength

The average compressive strength of at least three mortar cubes (area of face 50 cm²) composed of one part of cement, three parts of standard sand (conforming to IS 650 : 1966) by mass and $P/4 + 3.0$ percent (of combined mass of cement and sand) water, and prepared, stored and tested in the manner described in IS 4031 (Part 6) : 1988 shall be as follows:

- | | |
|------------------|-------------------------|
| a) 72 ± 1 hours | Not less than 15.69 MPa |
| b) 168 ± 2 hours | Not less than 21.57 MPa |
| c) 672 ± 4 hours | Not less than 30.40 MPa |

NOTE — P is the percentage of water required to produce a paste of standard consistency.

6.4 By agreement between the purchaser and the manufacturer, transverse strength test of plastic mortar in accordance with the method described in IS 4031 (Part 8) : 1988 may be specified in addition to the test specified in 6.3. The permissible value of the transverse strength for hydrophobic Portland cement shall be mutually agreed to between the purchaser and the supplier at the time of placing order.

6.5 Notwithstanding the strength requirements specified in 6.3 and 6.4, the cement shall show a progressive increase in strength from the strength at 72 hours.

6.6 Hydrophobicity of the cement shall be tested and accepted in accordance with Annex B.

7 STORAGE, SAMPLING, TESTS AND REJECTION

7.1 Storage, sampling, tests and rejection of hydrophobic cement shall be as laid down in IS 269 : 1989.

8 MANUFACTURER'S CERTIFICATE

8.1 The manufacturer shall satisfy himself that the cement conforms to the requirements of this standard, and if requested, shall furnish a certificate to this effect to the purchaser or his representative within ten days of despatch of the cement.

8.2 The manufacturer shall furnish a certificate, within ten days of despatch of cement, indicating the total chloride content in percent by mass of cement.

9 DELIVERY

9.1 The cement shall be packed in bags [jute sacking bag conforming to IS 2580 : 1982, double hessian bituminized (CRI type), multiwall paper conforming to IS 11761 : 1986, polyethylene lined (CRI type), jute, light weight jute conforming to IS 12154 : 1987, woven HDPE conforming to IS 11652 : 1986, woven polypropylene conforming to IS 11653 : 1986, jute synthetic union conforming to IS 12174 : 1987 or any other approved composite bags] bearing the manufacturer's name or his registered trade-mark, if any. The words 'Hydrophobic Cement' and the number of bags to a tonne or the nominal average net mass (*see* 9.2) of the cement shall be marked legibly and indelibly on each bag. Bags shall be in good condition at the time of inspection.

9.1.1 The bags or packages may also be marked with the Standard Mark.

9.2 The average net mass of cement per bag shall be 50 kg (*see* Annex C).

9.2.1 The average net mass of cement per bag may also be 25 kg subject to tolerances as given in 9.2.1.1 and packed in suitable bags as agreed to between the purchaser and the manufacturer.

9.2.1.1 The number of bags in a sample taken for weighment showing a minus error greater than 2 percent of the specified net mass shall be not

more than 5 percent of the bags in the sample. Also the minus error in none of such bags in the sample shall exceed 4 percent of the specified net mass of cement in the bag. However, the average net mass of cement in a sample shall be equal to or more than 25 kg.

9.2.2 When cement is intended for export and if the purchaser so requires, packing of cement may be done in bags with an average net mass per bag as agreed to between the purchaser and the manufacturer.

9.2.2.1 For this purpose the permission of the certifying authority shall be obtained in advance for each export order.

9.2.2.2 The words "FOR EXPORT" and the average net mass of cement per bag shall be clearly marked in indelible ink on each bag.

9.2.2.3 The packing material shall be as agreed to between the supplier and the purchaser.

9.2.2.4 The tolerance requirements for the mass of cement packed in bags shall be as given in 9.2.1.1 except the average net mass which shall be equal to or more than quantity in 9.2.2.

9.3 Supplies of cement in bulk may be made by arrangement between the purchaser and the supplier (manufacturer or stockist).

NOTE — A single bag or container containing 1 000 kg or more net mass of cement shall be considered as bulk supply of cement. Supplies of cement may also be made in intermediate containers, for example, drums of 200 kg, by agreement between the purchaser and the manufacturer.

ANNEX A

(Clause 2.1)

LIST OF REFERRED INDIAN STANDARDS

IS No.	Title	IS No.	Title
269 : 1989	Specification for 33 grade ordinary Portland cement (<i>fourth revision</i>)	11652 : 1986	Specification for high density polyethylene (HDPE) woven sacks for packing cement
650 : 1966	Specification for standard sand for testing of cement (<i>first revision</i>)	11653 : 1986	Specification for polypropylene (PP) woven sacks for packing cement
2580 : 1982	Specification for jute sacking bags for packing cement (<i>second revision</i>)	11761 : 1986	Specification for multi-wall paper sacks for cement valved-sewn gusseted type
3535 : 1986	Methods of sampling hydraulic cements (<i>first revision</i>)	12089 : 1987	Specification for granulated slag for the manufacture of Portland slag cement
4031 (Part 1 to 13) : 1988	Methods of Physical tests for hydraulic cement (<i>first revision</i>)	12154 : 1987	Specification for light weight jute bags for packing cement
4845 : 1968	Definitions and terminology relating to hydraulic cement	12174 : 1987	Specification for jute synthetic union bag for packing cement
4905 : 1968	Methods of random sampling		

ANNEX B

(Clause 6.6)

HYDROPHOBICITY TEST**B-1 QUANTITATIVE TEST**

B-1.1 Take 5 g each of fresh and free flowing 33 grade ordinary Portland cement and the hydrophobic cement under test and spread each of the samples evenly in a thin layer in 15 cm (dia) petri dish. Expose it to a relative humidity of not less than 99.9 percent at $27 \pm 2^\circ\text{C}$ for 24 hours. Determine the mass loss at 550°C for the two

samples. Hydrophobic cement shall not show loss on ignition more than 30 percent of the value for the 33 grade ordinary Portland cement.

B-2 QUALITATIVE TEST (FLOATATION)

B-2.1 Sprinkle a small quantity of hydrophobic cement on water in a container. The cement shall float on the water for a period of not less than 24 hours.

ANNEX C

(Clause 9.2)

TOLERANCE REQUIREMENTS FOR THE MASS OF CEMENT PACKED IN BAGS

C-1 The average net mass of cement packed in bags at the plant in a sample shall be equal to or more than 50 kg. The number of bags in a sample shall be as given below:

Batch Size	Sample Size
100 to 150	20
151 to 280	32
281 to 500	50
501 to 1 200	80
1 201 to 3 200	125
3 201 and over	200

The bags in a sample shall be selected at random (see IS 4905 : 1968).

C-1.1 The number of bags in a sample showing a minus error greater than 2 percent of the specified net mass (50 kg) shall be not more than 5 percent of the bags in the sample. Also the minus

error in none of such bags in the sample shall exceed 4 percent of the specified net mass of cement in the bag.

NOTE — The matter given in C-1 and C-1.1 are extracts based on the Standards of Weights and Measures (Packaged Commodities) Rules, 1977 to which reference shall be made for full details. Any modification made in these Rules and other related Acts and Rules would apply automatically.

C-1.2 In case of a wagon/truck load of 20 to 25 tonnes, the overall tolerance on net mass of cement shall be 0 to + 0.5 percent.

NOTE — The mass of a jute sacking bag conforming to IS 2580 : 1982 to hold 50 kg of cement is 531 g, the mass of a double hessian bituminized (CRI type) bag to hold 50 kg of cement is 630 g, the mass of a 6-ply paper bag to hold 50 kg of cement is approximately 400 g and the mass of a polyethylene lined (CRI type) jute bag to hold 50 kg of cement is approximately 480 g.

ANNEX D

(Foreword)

COMPOSITION OF THE TECHNICAL COMMITTEE

Cement and Concrete Sectional Committee, CED 2

<i>Chairman</i>	<i>Representing</i>
DR H. C. VISVESVARAYA	In personal capacity (<i>University of Roorkee, Roorkee 247667</i>)
<i>Members</i>	
SHRI H. BHATTACHARYA	Orissa Cement Limited, New Delhi
DR A. K. CHATTERJEE	The Associated Cement Companies Ltd, Bombay
SHRI S. H. SUBRAMANIAN (<i>Alternate</i>)	Central Public Works Department, New Delhi
CHIEF ENGINEER (DESIGNS)	
SUPERINTENDING ENGINEER (S & S)	
(<i>Alternate</i>)	
CHIEF ENGINEER, NAVAGAM DAM	Sardar Sarovar Narmada Nigam Ltd, Gandhinagar
SUPERINTENDING ENGINEER, OCC	
(<i>Alternate</i>)	
CHIEF ENGINEER (RESEARCH-CUM-DIRECTOR)	Irrigation and Power Research Institute, Amritsar
RESEARCH OFFICER (CONCRETE TECHNOLOGY) (<i>Alternate</i>)	
DIRECTOR	A. P. Engineering Research Laboratories, Hyderabad
JOINT DIRECTOR (<i>Alternate</i>)	
DIRECTOR (C & MDD) (N & W)	Central Water Commission, New Delhi
DEPUTY DIRECTOR (C & MDD)	
(NW & S) (<i>Alternate</i>)	
SHRI K. H. GANGWAL	Hyderabad Industries Limited, Hyderabad
SHRI V. PATTABHI (<i>Alternate</i>)	
SHRI V. K. GHANEKAR	Structural Engineering Research Centre (CSIR), Ghaziabad
SHRI S. GOPINATH	The India Cements Limited, Madras
SHRI R. TAAMILAKARAN (<i>Alternate</i>)	
SHRI S. K. GUHA THAKURTA	Gannon Dunkerley & Company Limited, Bombay
SHRI S. P. SHANKARANARAYANAN	
(<i>Alternate</i>)	
DR IRSHAD MASOOD	Central Building Research Institute (CSIR), Roorkee
DR MD KHALID (<i>Alternate</i>)	
JOINT DIRECTOR, STANDARDS (B & S) (CB-I)	Research, Designs and Standards Organization (Ministry of Railways), Lucknow
JOINT DIRECTOR STANDARDS (B & S) (CB-II) (<i>Alternate</i>)	
SHRI N. G. JOSHI	Indian Hume Pipes Co Limited, Bombay
SHRI P. D. KELKAR (<i>Alternate</i>)	
SHRI D. K. KANUNGO	National Test House, Calcutta
SHRI B. R. MEENA (<i>Alternate</i>)	
SHRI P. KRISHNAMURTHY	Larsen and Toubro Limited, Bombay
SHRI S. CHAKRAVARTHY (<i>Alternate</i>)	
SHRI G. K. MAJUMDAR	Hospital Services Consultancy Corporation (India) Ltd, New Delhi
SHRI S. O. RANGARI (<i>Alternate</i>)	
SHRI P. N. MEHTA	Geological Survey of India, Calcutta
SHRI J. S. SANGANERIA (<i>Alternate</i>)	
MEMBER SECRETARY	Central Board of Irrigation and Power, New Delhi
DIRECTOR (CIVIL) (<i>Alternate</i>)	
SHRI M. K. MUKHERJEE	Roads Wing Department of Surface Transport (Ministry of Transport), New Delhi
SHRI M. K. GHOSH (<i>Alternate</i>)	
DR A. K. MULLICK	National Council for Cement and Building Materials, New Delhi
DR S. C. AHLUWALIA (<i>Alternate</i>)	
SHRI NIRMAL SINGH	Development Commissioner for Cement Industry (Ministry of Industry)
SHRI S. S. MIGLANI (<i>Alternate</i>)	
SHRI R. C. PARATE	Engineer-in-Chief's Branch, Army Headquarters
LT-COL R. K. SINGH (<i>Alternate</i>)	

Members

SHRI H. S. PASRICHA
 SHRI Y. R. PHULL
 SHRI S. S. SEEHRA (*Alternate*)
 SHRI Y. R. PHULL
 SHRI K. B. THANDEVAN (*Alternate*)
 DR M. RAMAIAH
 DR A. G. MADHAVA RAO (*Alternate*)
 SHRI G. RAMDAS
 REPRESENTATIVE
 SHRI A. U. RIJHSINGHANI
 SHRI C. S. SHARMA (*Alternate*)
 SHRI J. SEN GUPTA
 SHRI A. K. LAL (*Alternate*)
 SHRI T. N. SUBBA RAO
 SHRI S. A. REDDI (*Alternate*)
 SUPT. ENGINEER (DESIGNS)
 EXECUTIVE ENGINEER (S.M.R. DIVISION)
 (*Alternate*)
 SHRI S. B. SURI
 SHRI N. CHANDRASEKARAN (*Alternate*)
 DR H. C. VISVESVARAYA
 SHRI D. C. CHATURVEDI (*Alternate*)
 SHRI G. RAMAN,
 Director (Civil Engg)

Representing

Hindustan Prefab Ltd, New Delhi
 Central Road Research Institute (CSIR), New Delhi
 Indian Roads Congress, New Delhi
 Structural Engineering Research Centre (CSIR), Madras
 Directorate General of Supplies and Disposals, New Delhi
 Builders' Association of India, Bombay
 Cement Corporation of India, New Delhi
 National Buildings Organization, New Delhi
 Gammon India Limited, Bombay
 Public Works Department, Government of Tamil Nadu
 Central Soil and Materials Research Station, New Delhi
 The Institution of Engineers (India), Calcutta
 Director General, BIS (*Ex-officio Member*)

Secretary

SHRI N. C. BANDYOPADHYAY
 Joint Director (Civil Engg), BIS

Cement, Pozzolana and Cement Additives Subcommittee, CED 2 : 1*Convener*

DR H. C. VISVESVARAYA

In personal capacity (*University of Roorkee, Roorkee 247667*)

Members

SHRI S. K. BANERJEE
 SHRI N. G. BASAK
 SHRI T. MADNESHWAR (*Alternate*)
 SHRI SOMNATH BANERJEE
 CHIEF ENGINEER (RESEARCH-CUM-DIRECTOR)
 RESEARCH OFFICER (CT) (*Alternate*)
 SHRI N. B. DESAI
 SHRI J. K. PATEL (*Alternate*)
 DIRECTOR
 RESEARCH OFFICER (*Alternate*)
 DIRECTOR (C & MDD II)
 DEPUTY DIRECTOR (C & MDD II)
 (*Alternate*)
 SHRI R. K. GATTANI
 SHRI R. K. VAISHNAVI (*Alternate*)
 SHRI P. J. JAGUS
 DR A. K. CHATTERJEE (*Alternate*)
 JOINT DIRECTOR (MATERIALS)
 ASSTT DIRECTOR (PLASTIC) (*Alternate*)
 JOINT DIRECTOR STANDARDS (B & S) (CB-I)
 JOINT DIRECTOR, STANDARDS (B & S)
 (CB-II) (*Alternate*)
 SHRI R. L. KAPOOR
 SHRI R. K. DATTA (*Alternate*)
 SHRI W. N. KARODE
 SHRI R. KUNJITHAPATTAM

National Test House, Calcutta
 Directorate General of Technical Development, New Delhi
 Cement Manufacturers Association, Bombay
 Irrigation Department, Government of Punjab
 Gujarat Engineering Research Institute, Vadodara
 Maharashtra Engineering Research Institute, Nasik
 Central Water Commission, New Delhi
 Shree Digvijay Cement Co Ltd, Bombay
 The Associated Cement Companies Ltd, Bombay
 National Buildings Organization, New Delhi
 Research, Designs and Standards Organization (Ministry of
 Railways), Lucknow
 Roads Wing, Department of Surface Transport, Ministry of
 Transport, New Delhi
 The Hindustan Construction Co Ltd, Bombay
 Chettinad Cement Corporation Ltd, Poliyur, Tamil Nadu

Members

SHRI G. K. MAJUMDAR
DR IRSHAD MASOOD
SHRI K. P. MOHIDEEN
DR A. K. MULLICK
DR (SMT) S. LAXMI (*Alternate*)
SHRI K. NARANAPPA
SHRI D. P. KEWALRAMANI (*Alternate*)
SHRI NIRMAL SINGH
SHRI S. S. MIGLANI (*Alternate*)
SHRI Y. R. PHULL
SHRI S. S. SEEHRA (*Alternate*)
SHRI A. V. RAMANA
DR K. C. NARANG (*Alternate*)
COL V. K. RAO
SHRI N. S. GALANDE (*Alternate*)
SHRI S. A. REDDI
SHRI A. U. RIJHSINGHANI
SHRI M. P. SINGH
SUPERINTENDING ENGINEER (D)
SENIOR DEPUTY CHIEF ENGINEER
(GENERAL) (*Alternate*)
SHRI S. B. SURI
SHRI N. CHANDRASEKARAN (*Alternate*)
SHRI L. SWAROOP
SHRI H. BHATTACHARYA (*Alternate*)
SHRI V. M. WAD

Representing

Hospital Services Consultancy Corporation (India) Ltd,
New Delhi
Central Building Research Institute (CSIR), Roorkee
Central Warehousing Corporation, New Delhi
National Council for Cement and Building Materials, New Delhi
Central Electricity Authority, New Delhi
Development Commissioner for Cement Industry (Ministry of
Industry)
Central Road Research Institute (CSIR), New Delhi
Dalmia Cement (Bharat) Ltd, New Delhi
Engineer-in-Chief's Branch, Army Headquarters
Gammon India Ltd, Bombay
Cement Corporation of India Ltd, New Delhi
Federation of Mini Cement Plants, New Delhi
Public Works Department, Govt of Tamil Nadu
Central Soil and Materials Research Station, New Delhi
Orissa Cement Ltd, New Delhi
Bhilai Steel Plant, Bhilai

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act*, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publication), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards Monthly Additions'.

This Indian Standard has been developed from Doc: No. **CED 2 (4796)**

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones: 323 01 31, 323 33 75, 323 94 02

Telegrams: Manaksanstha
(Common to all offices)

Regional Offices:

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg
NEW DELHI 110002

Telephone
323 76 17, 323 38 41

Eastern : 1/14 C.I.T. Scheme VII M, V.I.P. Road, Maniktola
CALCUTTA 700054

{ 337 84 99, 337 85 61
{ 337 86 26, 337 91 20

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022

{ 60 38 43
{ 60 20 25

Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113

{ 235 02 16, 235 04 42
{ 235 15 19, 235 23 15

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)
MUMBAI 400093

{ 832 92 95, 832 78 58
{ 832 78 91, 832 78 92

Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR.
COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI.
HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR.
PATNA. PUNE. THIRUVANANTHAPURAM.

AMENDMENT NO. 1 NOVEMBER 1991
TO
IS 8043 : 1991 HYDROPHOBIC PORTLAND CEMENT —
SPECIFICATION

(Second Revision)

(Page 3, clause C-1.2) — Substitute 'up to 25 tonnes' for 'of 20 to 25 tonnes'.

(CED 2)

Reprography Unit, BIS, New Delhi, India

AMENDMENT NO. 2 NOVEMBER 1993
TO
IS 8043 : 1991 HYDROPHOBIC PORTLAND CEMENT —
SPECIFICATION

(Second Revision)

(Page 2, clause 9.2.2) — Substitute the following for the existing matter:

‘9.2.2 When cement is intended for export and if the purchaser so requires, packing of cement may be done in bags or in drums with an average net mass of cement per bag or drum as agreed to between the purchaser and the manufacturer.

9.2.2.1 For this purpose the permission of the certifying authority shall be obtained in advance for each export order.

9.2.2.2 The words **‘FOR EXPORT’** and the average net mass of cement per bag/drum shall be clearly marked in indelible ink on each bag/drum.

9.2.2.3 The packing material shall be as agreed to between the manufacturer and the purchaser.

9.2.2.4 The tolerance requirements for the mass of cement packed in bags/drum shall be as given in **9.2.1.1** except the average net mass which shall be equal to or more than the quantity in **9.2.2.**

AMENDMENT NO. 3 APRIL 2000
TO
IS 8043 : 1991 HYDROPHOBIC PORTLAND
CEMENT — SPECIFICATION
(Second Revision)

Substitute 'net mass' *for* 'average net mass' wherever it appears in the standard.

(CED 2)

Reprography Unit, BIS, New Delhi, India