

“भारतीय मानक”
“RE-AFFIRMED 1996”
IS:8419 (Part I) - 1977

Indian Standard “भारतीय मानक”
REQUIREMENTS FOR “RE-AFFIRMED 1996”
FILTRATION EQUIPMENT

PART I FILTRATION MEDIA — SAND AND GRAVEL

(Fourth Reprint SEPTEMBER 1993)

UDC 628.16.067.1:553.623/.624

© Copyright 1977

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Indian Standard

REQUIREMENTS FOR FILTRATION EQUIPMENT

PART I FILTRATION MEDIA—SAND AND GRAVEL

Public Health Engineering Equipment Sectional Committee, BDC 40

Chairman

SHRI T. S. SWAMY

Representing

Central Public Health and Environmental Engineering Organization, (Ministry of Works & Housing), New Delhi

Members

SHRI B. B. RAU (*Alternate to*
Shri T. S. Swamy)

DR B. V. BHOOTA
SHRI N. BISWAS

All India Manufacturers Organization, Bombay
Directorate General of Technical Development,
New Delhi

SHRI R. C. P. CHAUDHARY
SHRI K. RUDRAPPA (*Alternate*)
CHIEF ENGINEER

Engineers India Ltd, New Delhi
Public Health Engineering Department, Government of Jammu & Kashmir

SUPERINTENDING ENGINEER (*Alternate*)

CHIEF ENGINEER

Uttar Pradesh Jal Nigam, Lucknow

SUPERINTENDING ENGINEER (*Alternate*)

CHIEF ENGINEER (WATER)

Municipal Corporation of Delhi

SHRI V. D. DESAI

Municipal Corporation of Greater Bombay

SHRI M. Y. MADAN

The Hindustan Construction Co Ltd, Bombay

SHRI C. E. S. RAO (*Alternate*)

PROF N. MAJUMDER

National Environmental Engineering- Research
Institute (CSIR), Nagpur

SHRI J. M. DAVE (*Alternate*)

SHRI S. R. MAJUMDER

Paterson Engineering Co (India) Ltd, Calcutta

SHRI A. M. LAHIRI (*Alternate*)

SHRI K. GOVINDA MENON

Tamil Nadu Water Supply & Drainage Board,
Madras

SUPERINTENDING ENGINEER
(EXECUTION) (*Alternate*)

SHRI R. N. MUKHJEE

Calcutta Metropolitan Planning Organization,
Calcutta

SHRI S. S. NAIK

SHRI H. D. PATEL (*Alternate*)

Hydraulic & General Engineers Pvt Ltd, Bombay

(Continued on page 2)

© Copyright 1977

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 8419 (Part I) - 1977

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
SHRI D. APPUKUTTAN NAIR	Public Health Engineering Department, Government of Kerala
SHRI S. K. NEOGI	Institution of Public Health Engineers India, Calcutta
SHRI D. K. GHOSH (<i>Alternate</i>)	
COL RAJ KUMAR	Engineer-in-Chief's Branch, Army Headquarters
SHRI I. S. BEDI (<i>Alternate</i>)	
SHRI K. RAMANNA	Corporation of Madras
SHRI D. R. JAGANNATH RAO	Public Health Engineering Department, Government of Madhya Pradesh, Bhopal
SHRI M. G. VAIDYA (<i>Alternate</i>)	
PROF S. SUBBA RAO	All India Institute of Hygiene & Public Health, Calcutta
SHRI A. V. RAO (<i>Alternate</i>)	
SHRI B. N. SEN	Department of Health, Government of West Bengal, Calcutta
SHRI T. N. CHATTERJEE (<i>Alternate</i>)	
SHRI J. L. SETHI	Public Health Engineering Department, Government of Haryana, Chandigarh
SHRI L. M. CHAUDHARI (<i>Alternate</i>)	
SHRI M. L. SHAH	Dorr Oliver India Ltd, Bombay
SHRI M. J. SHETTY	Geo-Miller & Co, Calcutta
SHRI D. K. CHOUDHURY (<i>Alternate</i>)	
SHRI D. R. SINGAL	Public Health Engineering Department, Government of Punjab, Chandigarh
SHRI S. A. SWAMY	The Institution of Engineers (India), Calcutta
SHRI P. S. TENDOLKAR	Candy Filters (India) Ltd, Bombay
SHRI C. L. SASTRI (<i>Alternate</i>)	
SHRI C. VISWESWARIAH	Public Health Engineering Department, Government of Karnataka, Bangalore
SHRI D. AJITHA SIMHA, Director (Civ Engg)	Director General, BIS (<i>Ex-officio Member</i>)

Secretary

SHRI VINOD KUMAR
Deputy Director (Civ Engg), BIS

Water Treatment Equipment Subcommittee, BDC 40 : 1

Convener

SHRI A. C. CHATURVEDI Uttar Pradesh Jal Nigam, Lucknow

Members

SHRI R. R. BAGRI Institution of Public Health Engineers (India), Calcutta

SHRI S. K. NEOGI (*Alternate*)

DR R. N. CHAKRABARTY Engineers India Limited, New Delhi

SHRI S. N. CHAKRABORTY (*Alternate*)

SHRI D. K. CHAUDHARY Geo-Miller & Co Pvt Ltd, Calcutta

SHRI A. K. MAZUMDER (*Alternate*)

SHRI S. N. GOSWAMI DCM Chemical Works, New Delhi

SHRI SURINDER KUMAR (*Alternate*)

(Continued on page 8)

Indian Standard

REQUIREMENTS FOR FILTRATION EQUIPMENT

PART I FILTRATION MEDIA—SAND AND GRAVEL

0. FOREWORD

0.1 This Indian Standard (Part I) was adopted by the Indian Standards Institution on 16 April 1977, after the draft finalized by the Public Health Engineering Equipment Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 Sand and gravel are often employed as filter media for filtration of water. For their proper functioning it is necessary that they should satisfy certain physical and chemical requirements. This standard provides the necessary guidelines in selecting the appropriate type of sand and gravel for filtration. Other media which are also used for filtration of water are not covered under this standard.

0.3 In the formulation of this standard due weightage has been given to international co-ordination among the standards and practices prevailing in different countries in addition to relating it to the practices in the field in this country.

0.4 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard (Part I) lays down the requirements for filter sand and for gravel used in filtration of water.

2. TERMINOLOGY

2.0 For the purpose of this standard, the following definitions shall apply.

*Rules for rounding off numerical values (revised).

IS : 8419 (Part I) - 1977

2.1 Effective Size (E. S.)— Particle diameter corresponding to 10 percent finer on the grain size curve [determined according to IS : 2720 (Part IV)-1975*].

2.2 Uniformity Coefficient — The ratio D_{60}/D_{10} where D_{60} is the particle diameter corresponding to 60 percent finer on the grain size curve, and D_{10} is the particle diameter corresponding to 10 percent finer on the grain size curve.

3. FILTER SAND

3.1 Quality Requirements

3.1.1 Filter sand shall consist of hard, durable grains of silica and shall have a specific gravity of not less than 2.5. All grains of sand shall preferably be water worn. The minimum silica content in sand as determined by method given in 7 of IS : 2000-1962† shall be 90 percent.

3.1.2 Any sample of filter sand shall not contain more than 5 percent by volume of impurities, such as clay, loam, silt, etc, in one hour settlement after shaking in water in accordance with procedure described in Appendix A.

3.1.3 The sand shall not contain more than 5 percent of acid soluble matter as determined by solubility test described in Appendix B.

3.1.4 The loss on ignition, which is a measure of the organic matter present in sand, and determined by the procedure given in Appendix C shall not be more than 0.7 percent.

3.2 Grain Shape and Shape Variation

3.2.1 Shape of filter grains is important from the hydraulic and turbidity removal points of view. Rounded grains are preferable to angular ones.

3.2.2 Filter sand shall meet the requirements of effective size and uniformity coefficient as specified by the purchaser.

3.3 Sampling — Sampling and criteria for conformity for filter sand may be in accordance with 3.3.1 to 3.3.4.

3.3.1 Lot — The quantity of sand received in a consignment from a single source shall be divided into a convenient number of lots of approximately equal size not exceeding 10 m^3 .

*Methods of test for soils : Part IV Grain size analysis (*first revision*).

†Methods of chemical analysis of bauxite.

3.3.2 From each lot, 10 increments each weighing about 2 kg shall be collected. The increment shall be taken at regular intervals during loading or unloading. From a stationary lot, 2 increments shall be taken from the top and 2 each from the four sides. The increment in all cases shall be taken from a depth of at least 150 mm.

3.3.3 All the increments taken from the same lot shall be mixed thoroughly and reduced by the process of coning and quartering to yield a laboratory sample of required mass (about 2 kg).

3.3.4 Criteria for Conformity — The laboratory sample as obtained in **3.3.3** shall be tested for all the requirements and if it passes in respect of them the lot shall be considered as conforming to this standard.

4. GRAVEL

4.1 Quality Requirements

4.1.1 Filter gravel shall consist of hard, preferably rounded stones with an average specific gravity of not less than 2.5 and shall be free from clay, sand, loam and organic impurities of any kind.

4.1.2 The gravel shall contain not more than 2 percent by mass of thin, flat or elongated pieces (in which the largest dimension exceeds three times the smallest dimension) determined by hand picking.

4.1.3 Gravel should be free from excessive amount of limestone or shells and acid solubility determined in accordance with procedure given in Appendix B should not exceed the following limits:

- a) For gravel sizes 10 mm or larger 10 percent solubility
- b) For sizes smaller than 10 mm 5 percent solubility

4.2 Sampling — Sampling and criteria for conformity for gravel shall be in accordance with **4.2.1** to **4.2.4**.

4.2.1 Lot — The quantity of gravel received in a consignment from a single source shall be divided into a convenient number of lots of approximately equal size not exceeding 25 m³.

4.2.2 From each lot 25 increments each weighing about 5 kg shall be collected. The increments shall be taken at regular intervals during loading or unloading. From a stationary lot the increment shall be taken by a suitable method so as to represent the material in various locations of the lot.

4.2.3 All the increments taken from the same lot shall be mixed thoroughly and then reduced by the process of coning and quartering to yield a laboratory sample of about 5 kg.

4.2.4 Criteria for Conformity—The laboratory sample as obtained in **4.2.3** shall be tested for all the requirements. If it passes in respect of all of them, the lot shall be considered as conforming to this standard.

A P P E N D I X A

(Clause 3.1.2)

TEST FOR DETERMINING IMPURITIES, SUCH AS CLAY, LOAM, SILT, ETC

A-1. PROCEDURE

A-1.1 Fill a 1 000 ml calibrated measuring cylinder with filter sand to be tested to half its volume and add water until the cylinder is three-fourths full. Shake up the mixture vigorously and allow it to settle for one hour.

A-2. REPORTING OF RESULT

A-2.1 Report the volume of impurities standing over the sand as percentage of volume of sand.

A P P E N D I X B

(Clauses 3.1.3 and 4.1.3)

ACID SOLUBILITY TEST

B-1. PROCEDURE

B-1.1 Rinse a minimum of 10 g of sample with distilled water to remove all dust and fine material, dry at 103°C in hot air-oven for one hour, cool and weigh. Immerse in 40 percent (*v/v*) hydrochloric acid for a period of 24 hours at room temperature. After 24 hours of immersion, wash the sample thoroughly with distilled water, dry at 103°C in hot air for one hour, cool and weigh.

B-1.2 The percentage of solubility is given by the formula:

$$\text{Solubility percentage} = \frac{\text{Loss in weight}}{\text{Original weight}} \times 100$$

A P P E N D I X C*(Clause 3.1.4)***LOSS ON IGNITION TEST****C-1. PROCEDURE**

C-1.1 Rinse a minimum of 10 g of the sample with distilled water to remove dust and fine material, dry at 103°C in hot air-oven for one hour, cool and weigh. Ignite the sample at 550°C in an electric muffle furnace for one hour, cool and weigh.

C-2. CALCULATION

C-2.1 Calculate percent loss on ignition using the following formula:

$$\text{Loss on ignition} = \frac{\text{Loss in weight}}{\text{Original weight of sample}} \times 100$$

(Continued from page 2)

Members

PROF B. L. MAHABAL
SHRI N. W. MIRCHANDANI
SHRI H. N. MISRA
SHRI S. S. NAIK
SHRI H. D. PATEL (*Alternate*)
SHRI JAI NARAIN
SHRI K. R. SAHU (*Alternate*)
DR S. V. PATWARDHAN
DR S. RAMACHANDRA

SHRI S. NATARAJAN (*Alternate*)
SHRI N. RAMACHANDRAN
SHRI A. M. JOSHI (*Alternate*)
SHRI V. RAMAN

SHRI S. R. KSHIRSAGAR (*Alternate*)
PROF S. SUBBA RAO

SHRI K. J. NATH (*Alternate*)
SHRI M. L. SHAH
SHRI S. B. SHUKLA
DR M. S. VAIDYA (*Alternate*)
SHRI S. P. UNVALA
SHRI P. S. WADIA

Representing

Victoria Jubilee Technical Institute, Bombay
Municipal Corporation of Greater Bombay
EIMCO — KCP Ltd, Madras
Hydraulic & General Engineers (P) Ltd, Bombay

Indian Water Works Association, Bombay

University of Roorkee, Roorkee
Central Mechanical Engineering Research Institute
(CSIR), Durgapur

Ion Exchange (India) Ltd, Bombay

National Environmental Engineering Research
Institute (CSIR), Nagpur

All India Institute of Hygiene & Public Health,
Calcutta

Dorr Oliver (India) Ltd, Bombay
The Dharmji Morarji Chemicals Co Ltd, Bombay

Candy Filters (India) Ltd, Bombay
The Hindustan Construction Co Ltd, Bombay

BUREAU OF INDIAN STANDARDS

Headquarters :

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones : 331 01 31

331 13 75

Telegrams : Manaksanstha

(Common to all Offices)

Regional Offices :

Telephone

Central	: Manak Bhavan, 9, Bahadur Shah Zafar Marg. NEW DELHI 110002	{ 331 01 31 331 13 75
* Eastern	: 1/14 C.I.T. Scheme VII M, V.I.P. Road, Maniktola, CALCUTTA 700054	37 86 62
Northern	: SCO 445-446, Sector 35-C, CHANDIGARH 160036	2 18 43
Southern	: C.I.T. Campus, IV Cross Road, MADRAS 600113	41 29 16
† Western	: Manakalaya, E9 MIDC, Marol, Andheri (East), BOMBAY 400093	6 32 92 95

Branch Offices :

'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMADABAD 380001	2 63 48
† Peenya Industrial Area, 1st Stage, Bangalore-Tumkur Road, BANGALORE 560058	39 49 55
Gangotri Complex, 5th Floor, Bhadbhada Road, T.T. Nagar, BHOPAL 462003	55 40 21
Plot No. 82/83, Lewis Road, BHUBANESHWAR 751002	5 36 27
Kalai Kathir Building, 6/48-A, Avanesi Road, COIMBATORE 641037	2 67 05
Quality Marking Centre, N.H. IV, N.I.T., FARIDABAD 121001	—
Savitri Complex, 116 G. T. Road, GHAZIABAD 201001	8-71 19 96
53/5 Ward No. 29, R.G. Barua Road, 5th By-lane, GUWAHATI 781003	3 31 77
5-8-56C L. N. Gupta Marg, (Nampally Station Road) HYDERABAD 500001	23 10 83
R14 Yudhister Marg, C Scheme, JAIPUR 302005	6 34 71
117/418 B Sarvodaya Nagar, KANPUR 208005	21 68 76
Plot No. A-9, House No. 561/63, Sindhu Nagar, Kanpur Road, LUCKNOW 226005	5 55 07
Patliputra Industrial Estate, PATNA 800013	6 23 05
District Industries Centre Complex, Bagh-e-Ali Maidan, SRINAGAR 190011	—
T. C. No. 14/1421, University P. O., Palayam, THIRUVANANTHAPURAM 695034	6 21 04
Inspection Offices (With Sale Point) :	
Pushpanjali, First Floor, 205-A West High Court Road, Shankar Nagar Square, NAGPUR 440010	52 51 71
Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005	5 24 35
*Sales Office Calcutta is at 5 Chowringhee Approach, P. O. Princep Street, CALCUTTA	27 68 00
† Sales Office is at Novelty Chambers, Grant Road, BOMBAY	89 65 28
‡ Sales Office is at Unity Building, Narasimharaja Square, BANGALORE	22 39 71