

*Indian Standard*

43 GRADE ORDINARY PORTLAND  
CEMENT — SPECIFICATION

*( First Revision )*

भारतीय मानक

43 ग्रेड साधारण पोर्टलैंड सीमेंट — विशिष्ट

( पहला पुनरीक्षण )

---

Fourth Reprint JULY 1997

UDC 666.942.2

© BIS 1990

BUREAU OF INDIAN STANDARDS  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI 110002

May 1990

Price Group 4

## FOREWORD

This Indian Standard ( First Revision ) was adopted by the Bureau of Indian Standards on 30 October 1989, after the draft finalized by the Cement and Concrete Sectional Committee had been approved by the Civil Engineering Division Council.

This standard was first published in 1976 under the title 'Specification for high strength ordinary Portland cement'. Since publication of this standard, large number of amendments have been issued from time to time in order to modify various requirements based on experience gained with the use of the standard and the requirements of the users and also keeping in view the raw materials and fuel available in the country for manufacture of cement. The important amendments include increasing the value of total loss on ignition from 4 to 5 percent, modifying the requirement of total sulphur content calculated as sulphuric anhydride (  $\text{SO}_3$  ) reducing the fineness by specific surface of cement from  $350 \text{ m}^2/\text{kg}$  to  $225 \text{ m}^2/\text{kg}$ , making autoclave soundness test compulsory irrespective of magnesia content, incorporating a provision for retest in respect of autoclave soundness test after aeration of the cement, incorporating a clause on false set of cement, permitting packaging of cement in 25 kg bags and making compulsory provision for issuing a certificate indicating the total chloride content in cement. Further, in view of the decision to designate ordinary Portland cement by its 28-day compressive strength, the title of this standard was modified as '43 grade ordinary Portland cement — Specification'. In view of these large number of amendments, the Sectional Committee decided to bring out the first revision of the standard incorporating all these amendments, so as to make it more convenient for the users.

This specification intends to cover the requirements of ordinary Portland cement used for the manufacture of prestressed concrete sleepers also. Some requirements of 43 grade ordinary Portland cement for uses, such as, manufacture of railway sleepers and precast products may be agreed to between the purchaser and the supplier.

Mass of cement packed in bags and the tolerance requirements shall be in accordance with the relevant provisions of the *Standards of Weights and Measures ( Packaged Commodities ) Rules, 1977* and **B-1.2** ( see Annex B for information ). Any modification in these rules in respect of tolerance on mass of cement would apply automatically to this standard.

This standard contains **11.4.1** which permits the purchaser to use his option for testing and **6.1, 6.5, 9.2.1** and **9.3** which call for agreement between the purchaser and the manufacturer.

In the formulation of this standard considerable assistance has been rendered by National Council for Cement and Building Materials, New Delhi as many of these modifications are based on studies carried out by them.

The composition of the committee responsible for the formulation of this standard is given in Annex C.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values ( revised )'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

# Indian Standard

## 43 GRADE ORDINARY PORTLAND CEMENT — SPECIFICATION

( First Revision )

### 1 SCOPE

1.1 This standard covers the manufacture, chemical and physical requirements of 43 grade ordinary Portland cement.

### 2 REFERENCES

2.1 The Indian Standards listed in Annex A are necessary adjuncts to this standard.

### 3 TERMINOLOGY

3.1 For the purpose of this standard, the definitions given in IS 4845 : 1968 shall apply.

### 4 MANUFACTURE

4.1 43 grade ordinary Portland cement shall be manufactured by intimately mixing together calcareous and agrillaceous and/or other silica, alumina or iron oxide bearing materials, burning them at a clinkering temperature and grinding the resultant clinker so as to produce a cement capable of complying with this specification. No material shall be added after burning other than gypsum ( natural or chemical ) or water or both, and not more than one percent of air-entraining agents or other agents, which have proved not to be harmful.

### 5 CHEMICAL REQUIREMENTS

5.1 When tested in accordance with the methods given in IS 4032 : 1985, 43 grade ordinary Portland cement shall comply with the chemical requirements given in Table 1.

### 6 PHYSICAL REQUIREMENTS

#### 6.1 Fineness

When tested for fineness by Blaine's air permeability method as described in IS 4031 ( Part 2 ) : 1988, the specific surface of cement shall not be less than 225 m<sup>2</sup>/kg.

NOTE — A higher fineness of cement, when specifically required, may be agreed to by mutual agreement between the purchaser and the manufacturer.

**Table 1 Chemical Requirements for High Strength Portland Cement**  
( Clause 5.1 )

Sl No. (1)	Characteristic (2)	Requirement (3)
i)	Ratio of percentage of lime to percentages of silica, alumina and iron oxide, when calculated by the formula: $\frac{\text{CaO} - 0.7 \text{ SO}_3}{2.8 \text{ SiO}_2 + 1.2 \text{ Al}_2\text{O}_3 + 0.65 \text{ Fe}_2\text{O}_3}$	Not greater than 1.02 and not less than 0.66
ii)	Ratio of percentage of alumina to that of iron oxide	Not less than 0.66
iii)	Insoluble residue, percent by mass	Not more than 2
iv)	Magnesia, percent by mass	Not more than 6
v)	Total sulphur content calculated as sulphuric anhydride ( SO <sub>3</sub> ), percent by mass	Not more than 2.5 and 3.0 when tricalcium aluminate ( see Note 1 ), percent by mass is 5 or less and greater than 5 respectively
vi)	Total loss on ignition	Not more than 5 percent

#### NOTES

1 The tricalcium aluminate content ( C<sub>3</sub>A ) is calculated by the formula:

$$C_3A = 2.65 ( Al_2O_3 ) - 1.69 ( Fe_2O_3 ),$$

where each symbol in brackets refers to the percent ( by mass of total cement ) of the oxide, excluding any contained in insoluble residue referred to at Sl No. ( iii ).

2 Alkali aggregate reactions have been noticed in aggregates in some parts of the country. On large and important jobs where the concrete is likely to be exposed to humid atmosphere or wetting action it is advisable that the aggregate be tested for alkali aggregate reaction. In the case of reactive aggregates, the use of cement with alkali content below 0.6 percent expressed as sodium oxide ( Na<sub>2</sub>O ) is recommended.

3 Total chloride content in cement shall not exceed 0.05 percent by mass for cement used in prestressed concrete structures and long span reinforced concrete structures. Method of test for determination of chloride content in cement is given in IS 12423 : 1988.

4 The limit of total chloride content in cement for use in plain and other reinforced concrete structures is being reviewed. Till that time, the limit may be mutually agreed to between the purchaser and the manufacturer.

## 6.2 Soundness

**6.2.1** When tested by the 'Le-Chatelier' method and autoclave test described in IS 4031 ( Part 3 ): 1988, unaerated cement shall not have an expansion of more than 10 mm and 0.8 percent respectively.

**6.2.1.1** In the event of cements failing to comply with any one or both the requirements specified in 6.2.1, further tests in respect of each failure shall be made as described in IS 4031 ( Part 3 ): 1988 from another portion of the same sample after aeration. The aeration shall be done by spreading out the sample to a depth of 75 mm at a relative humidity of 50 to 80 percent for a total period of 7 days. The expansion of cements so aerated shall be not more than 5 mm and 0.6 percent when tested by 'Le-Chatelier' method and autoclave test respectively.

## 6.3 Setting Time

The setting time of cement, when tested by the Vicat apparatus method described in IS 4031 ( Part 5 ): 1988 shall conform to the following requirements:

- a) Initial setting time in minutes — not less than 30
- b) Final setting time in minutes — not more than 600

**6.3.1** If cement exhibits false set, the ratio of final penetration measured after 5 minutes of completion of mixing period to the initial penetration measured exactly after 20 seconds of completion of mixing period, expressed as percent, shall be not less than 50. In the event of cement exhibiting false set, the initial and final setting time of cement when tested by the method described in IS 4031 ( Part 5 ): 1988 after breaking the false set, shall conform to 6.3.

## 6.4 Compressive Strength

The average compressive strength of at least three mortar cubes ( area of face 50 cm<sup>2</sup> ) composed of one part of cement, three parts of standard sand ( conforming to IS 650 : 1966 ) by mass and P/4 + 3.0 percent ( of combined mass of cement plus sand ) water, and prepared, stored and tested in the manner described in IS 4031 ( Part 6 ): 1988, shall be as follows:

- a) 72 ± 1 hour not less than 23 MPa
- b) 168 ± 2 hours not less than 33 MPa
- c) 672 ± 4 hours not less than 43 MPa

NOTE — P is the percentage of water required to produce a paste of standard consistency ( see 11.3 ).

**6.5** By agreement between the purchaser and the manufacturer, transverse strength test of plastic mortar in accordance with the method described in IS 4031 ( Part 8 ): 1988 may be specified in addition to the test specified in 6.4. The permissible values of the transverse strength shall be mutually agreed to between the purchaser and the supplier at the time of placing order.

**6.6** Notwithstanding the strength requirements specified in 6.4 and 6.5, cement shall show a progressive increase in strength from the strength at 72 hours.

## 7 STORAGE

**7.1** The cement shall be stored in such a manner as to permit easy access for proper inspection and in a suitable weather-tight building to protect the cement from dampness and to minimize warehouse deterioration.

## 8 MANUFACTURER'S CERTIFICATE

**8.1** The manufacturer shall satisfy himself that the cement conforms to the requirements of this standard, and if requested, shall furnish a certificate to this effect to the purchaser or his representative, within ten days of despatch of the cement.

**8.2** The manufacturer shall furnish a certificate, within ten days of despatch of cement, indicating the total chloride content in percent by mass of cement.

## 9 DELIVERY

**9.1** The cement shall be packed in bags [ jute sacking bag conforming to IS 2580 : 1982, double hessian bituminized ( CRI type ), multiwall paper conforming to IS 11761 : 1986, polyethylene lined ( CRI type ) jute, light weight jute conforming to IS 12154 : 1987, woven HDPE conforming to IS 11652 : 1986, woven polypropylene conforming to IS 11653 : 1986, jute synthetic union conforming to IS 12174 : 1987 or any other approved composite bags ] bearing the manufacturer's name or his registered trade-mark, if any, and the words '43 Grade Ordinary Portland Cement'. The number of bags ( net mass ) to the tonne or the average net mass of the cement shall be legibly and indelibly marked on each bag. Bags shall be in good condition at the time of inspection.

**9.1.1** Similar information shall be provided in the delivery advices accompanying the shipment of packed or bulk cement ( see 9.3 ).

**9.2** The average net mass of cement per bag shall be 50 kg ( see Annex B ).

**9.2.1** The average net mass of cement per bag may also be 25 kg subject to tolerances as given in 9.2.1.1 and packed in suitable bags as agreed to between the purchaser and the manufacturer.

**9.2.1.1** The number of bags in a sample taken for weighment showing a minus error greater than 2 percent of the specified net mass shall be not more than 5 percent of the bags in the sample. Also the minus error in none of such bags in the sample shall exceed 4 percent of the specified net mass of cement in the bag. However, the average net mass of cement in a sample shall be equal to or more than 25 kg.

**9.3** Supplies of cement in bulk may be made by arrangement between the purchaser and the supplier ( manufacturer or stockist ).

**NOTE** — A single bag or container containing 1 000 kg or more net mass of cement shall be considered as bulk supply of cement. Supplies of cement may also be made in intermediate containers, for example, drums of 200 kg, by agreement between the purchaser and the manufacturer.

## 10 SAMPLING

### 10.1 Samples for Testing and by Whom to be Taken

A sample or samples for testing may be taken by the purchaser or his representative, or by any person appointed to superintend the work for purpose of which the cement is required or by latter's representative.

**10.1.1** The samples shall be taken within three weeks of the delivery and all the tests shall be commenced within one week of sampling.

**10.1.2** When it is not possible to test the samples within one week, the samples shall be packed and stored in air-tight containers till such time that they are tested.

**10.2** In addition to the requirements of 10.1, the methods and procedure of sampling shall be in accordance with IS 3535 : 1986.

### 10.3 Facilities for Sampling and Identification

The manufacturer or supplier shall afford every facility, and shall provide all labour and materials for taking and packing the samples for testing the cement and for subsequent identification of the cement sampled.

## 11 TESTS

**11.1** The sample or samples of cement for test shall be taken as described in 10 and shall be

tested in the manner described in the relevant clauses.

### 11.2 Temperature for Testing

The temperature range within which physical tests may be carried out shall, as far as possible, be  $27 \pm 2^\circ\text{C}$ . The actual temperature during the testing shall be recorded.

### 11.3 Consistency of Standard Cement Paste

The quantity of water required to produce a paste of standard consistency, to be used for the determination of the water content of mortar for the compressive strength tests and for the determination of soundness and setting time, shall be obtained by the method described in IS 4031 ( Part 4 ) : 1988.

### 11.4 Independent Testing

**11.4.1** If the purchaser or his representative requires independent tests, the samples shall be taken before or immediately after delivery at the option of the purchaser or his representative, and the tests shall be carried out in accordance with this standard on the written instruction of the purchaser or his representative.

### 11.4.2 Cost of Testing

The manufacturer shall supply, free of charge, the cement required for testing. Unless otherwise specified in the enquiry and order, the cost of the tests shall be borne as follows:

- a) by the manufacturer if the results show that the cement does not comply with this standard, and
- b) by the purchaser if the results show that the cement complies with this standard.

**11.4.3** After a representative sample has been drawn, tests on the sample shall be carried out as expeditiously as possible.

## 12 REJECTION

**12.1** Cement may be rejected if it does not comply with any of the requirements of this specification.

**12.2** Cement remaining in bulk storage at the mill, prior to shipment, for more than six months, or cement in bags in local storage in the hands of a vendor for more than 3 months after completion of tests, may be retested before use and may be rejected, if it fails to conform to any of the requirements of this specification.

## ANNEX A

( Clause 2.1 )

## LIST OF REFERRED INDIAN STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
650 : 1966	Specification for standard sand for testing of cement ( <i>first revision</i> )	11652 : 1986	Specification for high density polyethylene (HDPE) woven sacks for packing cement
2580 : 1982	Specification for jute sacking bags for packing cement ( <i>second revision</i> )	11653 : 1986	Specification for polypropylene (PP) woven sacks for packing cement
3535 : 1986	Methods of sampling hydraulic cements ( <i>first revision</i> )	11761 : 1986	Specification for multi wall paper sacks for cement, valved-sewn-gusseted type
4031	Methods of physical test for ( Parts 1 to 13 ) hydraulic cement ( <i>first revision</i> )	12154 : 1987	Specification for light weight jute bags for packing cement
4032 : 1985	Method of Chemical analysis of hydraulic cement ( <i>first revision</i> )	12174 : 1987	Specification for jute synthetic union bag for packing cement
4845 : 1968	Definitions and terminology relating to hydraulic cement	12423 : 1988	Method for colorimetric analysis of hydraulic cement
4905 : 1968	Methods for random sampling		

## ANNEX B

( Clause 9.2 )

TOLERANCE REQUIREMENTS FOR THE MASS OF CEMENT  
PACKED IN BAGS

**B-1** The average net mass of cement packed in bags at the plant in a sample shall be equal to or more than 50 kg. The number of bags in a sample shall be as given below:

<i>Batch Size</i>	<i>Sample Size</i>
100 to 150	20
151 to 280	32
281 to 500	50
501 to 1 200	80
1 201 to 3 200	125
3 201 and over	200

The bags in a sample shall be selected at random ( see IS 4905 : 1968 ).

**B-1.1** The number of bags in a sample showing a minus error greater than 2 percent of the specified net mass ( 50 kg ) shall be not more than 5 percent of the bags in the sample. Also the minus

error in none of such bags in the sample shall exceed 4 percent of the specified net mass of cement in the bag.

**NOTE**— The matter given in **B-1** and **B-1.1** are extracts based on the *Standards of Weights and Measures ( Packaged Commodities ) Rules, 1977* to which reference shall be made for full details. Any modification made in these Rules and other related Acts and Rules would apply automatically.

**B.1.2** In case of a wagon/truck load of 20 to 25 tonnes, the overall tolerance on net mass of cement shall be 0 to +0.5 percent.

**NOTE**— The mass of a jute sacking bag conforming to IS 2580 : 1982 to hold 50 kg of cement is 531 g, the mass of a double hessian bituminized ( CRI type ) bag to hold 50 kg of cement is 630 g, the mass of a 6-ply paper bag to hold 50 kg of cement is approximately 400 g and the mass of a polyethylene lined ( CRI type ) jute bag to hold 50 kg of cement is approximately 480 g.

# ANNEX A

## COMPOSITION OF THE TECHNICAL COMMITTEE

### CEMENT AND CONCRETE SECTIONAL COMMITTEE, CED 2

**Chairman**

DR H. C. VISVESVARAYA

**Members**

SHRI K. P. BANERJEE  
SHRI HARISH N. MALANI ( *Alternate* )  
SHRI S. K. BANERJEE  
CHIEF ENGINEER ( BD )  
SHRI J. C. BASUR ( *Alternate* )  
CHIEF ENGINEER ( DESIGNS )  
SUPERINTENDING ENGINEER ( S & S )  
( *Alternate* )  
CHIEF ENGINEER ( RESEARCH-CUM-DIRECTOR )  
RESEARCH OFFICER ( CONCRETE TECHNOLOGY ) ( *Alternate* )  
DIRECTOR  
JOINT DIRECTOR ( *Alternate* )  
DIRECTOR  
CHIEF RESEARCH OFFICER ( *Alternate* )  
DIRECTOR ( C & MDD-II )  
DEPUTY DIRECTOR ( C & MDD-II )  
( *Alternate* )  
SHRI V. K. GHANEKAR  
SHRI S. GOPINATH  
SHRI A. K. GUPTA  
SHRI J. SEN GUPTA  
SHRI P. J. JAGUS  
DR A. K. CHATTERJEE ( *Alternate* )  
JOINT DIRECTOR STANDARDS ( B & S )/CB-I  
JOINT DIRECTOR STANDARDS ( B & S )/  
CB-II ( *Alternate* )  
SHRI N. G. JOSHI  
SHRI R. L. KAPOOR  
  
SHRI R. K. SAXENA ( *Alternate* )  
DR A. K. MULLICK  
SHRI G. K. MAJUMDAR  
  
SHRI P. N. MEHTA  
SHRI S. K. MATHUR ( *Alternate* )  
SHRI NIRMAL SINGH  
  
SHRI S. S. MIGLANI ( *Alternate* )  
SHRI S. N. PAL  
SHRI BIMAN DASGUPTA ( *Alternate* )  
SHRI R. C. PARATE  
LT-COL R. K. SINGH ( *Alternate* )  
SHRI H. S. PASRICHA  
SHRI Y. R. PHULL  
  
SHRI S. S. SEEHRA ( *Alternate* )  
DR MOHAN RAI  
DR S. S. REHSI ( *Alternate* )  
SHRI A. V. RAMANA  
DR K. C. NARANG ( *Alternate* )  
SHRI G. RAMDAS  
SHRI T. N. SUBBA RAO  
SHRI S. A. REDDI ( *Alternate* )

**Representing**

National Council for Cement and Building Materials, New Delhi  
  
Larsen and Toubro Limited, Bombay  
  
National Test House, Calcutta  
Bhakra Beas Management Board, Nangal Township  
  
Central Public Works Department, New Delhi  
  
Irrigation Department, Government of Punjab  
  
A. P. Engineering Research Laboratories, Hyderabad  
  
Central Soil and Materials Research Station, New Delhi  
  
Central Water Commission, New Delhi  
  
Structural Engineering Research Centre ( CSIR ), Ghaziabad  
The India Cements Limited, Madras  
Hyderabad Industries Limited, Hyderabad  
National Buildings Organization, New Delhi  
The Associated Cement Companies Ltd, Bombay  
  
Research, Designs and Standards Organization ( Ministry of Railways ), Lucknow  
  
Indian Hume Pipes Co Limited, Bombay  
Roads Wing ( Ministry of Transport ), Department of Surface Transport, New Delhi  
  
National Council for Cement and Building Materials, New Delhi  
Hospital Services Consultancy Corporation ( India ) Ltd, New Delhi  
Geological Survey of India, Calcutta  
  
Development Commissioner for Cement Industry ( Ministry of Industry ), New Delhi  
  
M.N. Dastur and Company Private Limited, Calcutta  
  
Engineer-in-Chief's Branch, Army Headquarters  
  
Hindustan Prefab Limited, New Delhi  
Indian Roads Congress, New Delhi; and Central Road Research Institute ( CSIR ), New Delhi  
Central Road Research Institute ( CSIR ), New Delhi  
Central Building Research Institute ( CSIR ), Roorkee  
  
Dalmia Cement ( Bharat ) Limited, New Delhi  
  
Directorate General of Supplies and Disposals, New Delhi  
Gammon India Limited, Bombay

*Members*

DR M. RAMAIAH  
DR A. G. MADHAVA RAO ( *Alternate* )  
SHRI A. U. RIJHSINGHANI  
SHRI C. S. SHARMA ( *Alternate* )  
SECRETARY  
SHRI K. R. SAXENA ( *Alternate* )  
SUPERINTENDING ENGINEER ( DESIGNS )  
EXECUTIVE ENGINEER ( SMD DIVISION )  
( *Alternate* )  
SHRI L. SWAROOP  
SHRI H. BHATTACHARYA  
( *Alternate* )  
SHRI S. K. GUHA THAKURTA  
SHRI S.P. SANKARNARAYANAN  
( *Alternate* )  
DR H. C. VISVESVARAYA  
SHRI D. C. CHATURVEDI ( *Alternate* )  
SHRI G. RAMAN,  
Director ( Civ Engg )

*Representing*

Structural Engineering Research Centre ( CSIR ), Madras  
Cement Corporation of India, New Delhi  
Central Board of Irrigation and Power, New Delhi  
Public Works Department, Government of Tamil Nadu  
Orissa Cement Limited, New Delhi  
Gannon Dunkerly & Co Ltd, Bombay  
The Institution of Engineers ( India ), Calcutta  
Director General, BIS ( *Ex-officio Member* )

*Secretary*

SHRI N. C. BANDYOPADHYAY  
Joint Director ( Civ Engg ), BIS

**Cement, Pozzolana and Cement Additives Subcommittee, CED 2 : 1**

*Convener*

DR H. C. VISVESVARAYA

National Council for Cement and Building Materials,  
New Delhi

*Members*

DR A. K. MULLICK DR ( SHRIMATI ) S. LAXMI	} ( <i>Alternates to Dr H. C. Visvesvaraya</i> )	
SHRI S. K. BANERJEE SHRI N. G. BASAK SHRI T. MADNESHWAR ( <i>Alternate</i> ) SHRI SOMNATH BANERJEE CHIEF ENGINEER ( RESEARCH-CUM-DIRECTOR ) RESEARCH OFFICER ( CT ) ( <i>Alternate</i> ) SHRI N. B. DESAI SHRI J. K. PATEL ( <i>Alternate</i> ) DIRECTOR RESEARCH OFFICER ( <i>Alternate</i> ) DIRECTOR ( C & MDD II ) DEPUTY DIRECTOR ( C & MDD II ) ( <i>Alternate</i> ) SHRI R. K. GATTANI SHRI R. K. VAISHNAVI ( <i>Alternate</i> ) SHRI J. SEN GUPTA SHRI P. J. JAGUS DR A. K. CHATTERJEE ( <i>Alternate</i> ) JOINT DIRECTOR, STANDARDS ( B & S )/CB-I JOINT DIRECTOR, STANDARDS ( B & S )/CB-II ( <i>Alternate</i> ) SHRI R. L. KAPOOR SHRI R. K. DATTA ( <i>Alternate</i> ) SHRI W. N. KARODE SHRI R. KUNJITHAPATTAM SHRI G. K. MAJUMDAR		
		National Test House, Calcutta Directorate General of Technical Development, New Delhi Cement Manufacturers Association, Bombay Irrigation Department, Government of Punjab Gujarat Engineering Research Institute, Vadodara Maharashtra Engineering Research Institute, Nasik Central Water Commission, New Delhi Shree Digvijay Cement Co Ltd, Bombay National Buildings Organization, New Delhi The Associated Cement Companies Ltd, Bombay Research, Designs and Standards Organization, Lucknow Roads Wing ( Ministry of Transport ) ( Department of Surface Transport ), New Delhi The Hindustan Construction Co Ltd, Bombay Chettinad Cement Corporation Ltd, Poliyur, Tamil Nadu Hospital Services Consultancy Corporation ( India ) Ltd, New Delhi



**Members**

SHRI K. P. MOHIDEEN  
 SHRI NIRMAL SINGH  
 SHRI S. S. MIGLANI ( *Alternate* )  
 SHRI Y. R. PHULL  
 SHRI M. R. CHATTERJEE ( *Alternate* )  
 SHRI A. V. RAMANA  
 DR K. C. NARANG ( *Alternate* )  
 COL V. K. RAO  
 SHRI N. S. GALANDE ( *Alternate* )  
 SHRI S. A. REDDI  
 DR S. S. REHSI  
 DR IRSHAD MASOOD ( *Alternate* )  
 SHRI A. U. RIJHSINGHANI  
 SHRI M. P. SINGH  
 SUPERINTENDING ENGINEER (D)  
 SENIOR DEPUTY CHIEF ENGINEER  
 ( GENERAL ) ( *Alternate* )  
 SHRI L. SWAROOP  
 SHRI H. BHATTACHARYA ( *Alternate* )  
 SHRI V. M. WAD

**Representing**

Central Warehousing Corporation, New Delhi  
 Development Commissioner for Cement Industry ( Ministry of Industry )  
 Central Road Research Institute ( CSIR ), New Delhi  
 Dalmia Cement ( Bharat ) Ltd, New Delhi  
 Engineer-in-Chief's Branch, Army Headquarters  
 Gammon India Ltd, Bombay  
 Central Building Research Institute ( CSIR ), Roorkee  
 Cement Corporation of India Ltd, New Delhi  
 Federation of Mini Cement Plants, New Delhi  
 Public Works Department, Government of Tamil Nadu  
 Orissa Cement Ltd, New Delhi  
 Bhilai Steel Plant, Bhilai

## Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

### Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publication), BIS.

### Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards Monthly Additions'.

This Indian Standard has been developed from Doc: No. CED 2 ( 4746 )

### Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

## BUREAU OF INDIAN STANDARDS

### Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 323 01 31, 323 33 75, 323 94 02

Telegrams: Manaksanstha  
(Common to all offices)

### Regional Offices:

Telephone

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg  
NEW DELHI 110002

323 76 17, 323 38 41

Eastern : 1/14 C.I.T. Scheme VII M, V.I.P. Road, Maniktola  
CALCUTTA 700054

{ 337 84 99, 337 85 61  
337 86 26, 337 91 20

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022

{ 60 38 43  
60 20 25

Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113

{ 235 02 16, 235 04 42  
235 15 19, 235 23 15

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)  
MUMBAI 400093

{ 832 92 95, 832 78 58  
832 78 91, 832 78 92

Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR.  
COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI.  
HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR.  
PATNA. PUNE. THIRUVANANTHAPURAM.

**AMENDMENT NO. 1 JANUARY 1991**  
**TO**  
**IS 8112 : 1989 43 GRADE ORDINARY PORTLAND**  
**CEMENT — SPECIFICATION**

*( First Revision )*

*( Page 3, Clause 9.2.1.1 )* — Insert the following new clauses after 9.2.1.1:

**9.2.2** When cement is intended for export and if the purchaser so requires, packing of cement may be done in bags other than those given in 9.2 and 9.2.1 with an average net mass of cement per bag as agreed to between the purchaser and the manufacturer.

**9.2.2.1** For this purpose the permission of the certifying authority shall be obtained in advance for each export order.

**9.2.2.2** The words 'FOR EXPORT' and the average net mass of cement per bag shall be clearly marked in indelible ink on each bag.

**9.2.2.3** The packing material shall be as agreed to between the supplier and the purchaser.

**9.2.2.4** The tolerance requirements for the mass of cement packed in bags shall be as given in 9.2.1.1 except the average net mass which shall be equal to or more than the quantity in 9.2.2.'

( CED 2 )

**AMENDMENT NO. 2 NOVEMBER 1991  
TO  
IS 8112 : 1989 43 GRADE ORDINARY PORTLAND  
CEMENT — SPECIFICATION**

*( First Revision )*

*( Page 4, clause B-1.2 )* — Substitute 'up to 25 tonnes' for 'of 20 to 25 tonnes'.

( CED 2 )

---

Printed at Dee Kay Printers, New Delhi-110015, India.

**AMENDMENT NO. 3 NOVEMBER 1993**  
**TO**  
**IS 8112 : 1989 43 GRADE ORDINARY PORTLAND**  
**CEMENT — SPECIFICATION**

*( First Revision )*

[ Page 3, clause 9.2.1.1 ( see also Amendment No. 1 )] — Substitute the following for the existing matter:

**‘9.2.2** When cement is intended for export and if the purchaser so requires, packing of cement may be done in bags or in drums with an average net mass of cement per bag or drum as agreed to between the purchaser and the manufacturer.

**9.2.2.1** For this purpose the permission of the certifying authority shall be obtained in advance for each export order.

**9.2.2.2** The words ‘**FOR EXPORT**’ and the average net mass of cement per bag/drum shall be clearly marked in indelible ink on each bag/drum.

**9.2.2.3** The packing material shall be as agreed to between the manufacturer and the purchaser.

**9.2.2.4** The tolerance requirements for the mass of cement packed in bags/drum shall be as given in 9.2.1.1 except the average net mass which shall be equal to or more than the quantity in 9.2.2.’

( CED 2 )

---

Printed at Dee Kay Printers, New Delhi-110015, India.

**AMENDMENT NO. 4    OCTOBER 1998**  
**TO**  
**IS 8112 : 1989    43 GRADE ORDINARY PORTLAND**  
**CEMENT — SPECIFICATION**

*( First Revision )*

*( Page 3, clause 9.2.1 )* — Substitute the following for the existing clause:

**‘9.2.1 The average net mass of cement per bag may also be 25 kg, 10 kg, 5 kg, 2 kg or 1 kg, subject to tolerances as given in 9.2.1.1 and packed in suitable bag as agreed to between the purchaser and the manufacturer.’**

*( Page 3, clause 9.2.1.1 )* — Substitute the following for the existing clause:

**‘9.2.1.1 The number of bags in a sample taken for weighment showing a minus error greater than 2 percent of the specified net mass shall not be more than 5 percent of the bags in the sample. Also the minus error in none of such bags in the sample shall exceed 4 percent of the specified net mass of cement in the bag. However, the average mass of the cement in a sample shall be equal to or more than 25 kg, 10 kg, 5 kg, 2 kg or 1 kg, as the case may be.’**

*( Page 4, clause B-1.2 )* — Substitute ‘up to 25 tonnes’ for ‘20 to 25 tonnes’.

( CED 2 )

**AMENDMENT NO. 5    OCTOBER 1999**  
**TO**  
**IS 8112 : 1989    43 GRADE ORDINARY PORTLAND**  
**CEMENT — SPECIFICATION**

*( First Revision )*

*( Page 1, clause 5.1 )* — Insert the following after the clause:

**‘5.2** Total chloride content in cement shall not exceed 0.1 percent by mass for cement used in structures other than prestressed concrete. For determination of chloride content in cement, IS 12423 may be referred.

NOTE — For use in special structures like prestressed concrete, where chloride is a critical parameter, the limit of chloride content shall be 0.05 percent and shall be required to be measured if desired by the purchaser.’

*[ Page 1, Table 1, Sl No. (iii), col 3 ]* — Substitute ‘3.0’ for ‘2’.

*[ Page 1, Table 1, Sl No. (iv), col 3 ]* — Substitute ‘6.0’ for ‘6’.

*( Page 1, Table 1, Notes 3 and 4 )* — Delete.

( CED 2 )

**AMENDMENT NO. 6 JUNE 2000**  
**TO**  
**IS 8112 : 1989 43 GRADE ORDINARY PORTLAND**  
**CEMENT — SPECIFICATION**

*( First Revision )*

Substitute 'net mass' for 'average net mass' wherever it appears in the standard.

( *Cover page 2, para 3 of Foreword* ) — Substitute the following for the existing text:

"Specific requirements of ordinary Portland cement for manufacture of railway sleepers to be designated as 43-S grade are given in the standard in 5.2, 6.1, 6.2.2, 6.3, 6.4 and 9.1. To differentiate it with normal grade, '43-S grade' shall be marked on the bags/packages for such cement in place of '43-S grade'."

( *Page 1, clause 5* ) — Insert a new clause 5.2 as follows:

**5.2** Cement used for railway sleepers shall satisfy the following chemical/minerological requirements and shall be designated as 43-S grade:

- i) Magnesia, percent by mass — Not more than 5.0
- ii) Tricalcium aluminate content, percent — Not more than 10.0
- iii) Tricalcium silicate, percent — Not less than 45'

( *Page 1, clause 6.1* ) — Insert the following at the end of the clause:

'For 43-S grade cement, the specific surface shall not be less than  $370 \text{ m}^2/\text{kg}$ .'

( *Page 1, Table 1, Note 1* ) — Insert the following at the end:

'The tricalcium silicate content (C3S) is calculated by the formula:

$$\text{C3S} = 4.07 \text{ CaO} - 7.60 \text{ SiO}_2 - 6.72 \text{ Al}_2\text{O}_3 - 1.43 \text{ Fe}_2\text{O}_3 - 2.85 \text{ SO}_3$$

( *Page 2, clause 6.2.1.1* ) — Insert a new clause 6.2.2 as follows:

**6.2.2** For 43-S grade cement, soundness of unaerated cement when tested by the Le-Chatelier method shall not have an expansion of more than 5 mm.'



**Amend No. 6 to IS 8112 : 1989**

( *Page 2, clause 6.3* ) — Insert the following under (a) :

‘Initial setting time for 43-S grade cement in minutes — Not less than 60.’

( *Page 2, clause 6.4* ) — Insert the following as new para:

‘For 43-S grade cement, compressive strength at  $168 \pm 2$  h shall not be less than 37.5 MPa.’

( *Page 2, clause 9.1, line 12* ) — Insert the following after ‘43 Grade Ordinary Portland cement’:

“or ‘43-S Grade Ordinary Portland Cement’, whichever is applicable.”

( CED 2 )

# AMENDMENT NO. 7 DECEMBER 2003

## TO

### IS 8112 : 1989 43 GRADE ORDINARY PORTLAND CEMENT — SPECIFICATION

( First Revision )

( Page 1, clause 4.1, last sentence ) — Substitute the following for the existing sentence:

'No material shall be added after burning, other than gypsum (natural or chemical) or water or both; performance improvers; and not more than one percent of air-entraining agents or other agents including colouring agents, which have proved not to be harmful. Limit of addition of performance improvers shall be as follows and shall be inclusive of one percent additives as mentioned above:

<i>Performance Improver</i>	<i>Percentage Addition, Max</i>	<i>Requirement</i>
Fly ash	5	As per IS 3812 (Part 1)
Granulated slag	5	As per IS 12089
Silica fume	5	As per IS 15388
Limestone	5	CaCO <sub>3</sub> content calculated from CaO content shall not be less than 75 percent when tested as per IS 1760 (Part 3)
Rice husk ash	5	a) Reactive silica shall not be less than 85 percent when tested as per IS 3812 (Part 1) b) Pozzolanic Activity Index shall not be less than 90 percent when tested as per 10 of IS 1727 c) Loss on ignition shall not be more than 8 percent when tested as per IS 1727
Metakaoline	5	a) Silicon dioxide (SiO <sub>2</sub> ) plus aluminium oxide (Al <sub>2</sub> O <sub>3</sub> ) plus iron oxide (Fe <sub>2</sub> O <sub>3</sub> ) in percent by mass shall not be less than 95 percent when tested as per IS 1727 b) Loss on ignition shall not be more than 1 percent when tested as per IS 1727 c) Total alkalis as sodium oxide (Na <sub>2</sub> O) in percent by mass shall not be more than 0.6 percent when tested as per IS 4032 d) Particles retained on 45 micron IS sieve ( wet sieving ) shall not be more than 1 percent when test as per IS 1727

## Amend No. 7 to IS 8112 : 1989

If a combination of above performance improvers is added, the maximum limit of addition shall be 5 percent.

[ Page 1, Table 1, Sl No. (iii) ( see also Amendment No. 5 ) ] — Substitute the following for the existing matter:

Sl No. (1)	Characteristic (2)	Requirement (3)
iii)	Insoluble residue, percent by mass	a) In case no flyash, silica fume, rice husk ash and metakaoline is added — Not more than 3.0 b) In case of addition of fly ash and/or silica fume and/or rice husk ash and/or metakaoline — Not more than 5.0

( Page 2, clause 6.3.1, line 6 ) — Substitute 'less than' for the words 'not less than'.

( Page 2, clause 9.1, last sentence ) — Insert the following sentence before the existing sentence:

'Bags shall also be marked with the type and the percentage of performance improvers added.'

( Page 4, Annex A ) — Insert the following matter at the appropriate place:

IS No.	Title
1727 : 1967	Methods of test for pozzolanic materials ( <i>first revision</i> )
1760 (Part 3): 1992	Methods of chemical analysis of limestone, dolomite and allied materials : Part 3 Determination of iron oxide, alumina, calcium oxide and magnesia ( <i>first revision</i> )
3812 ( Part 1 ) : 2003	Pulverized fuel ash — Specification : Part 1 For use as pozzolana in cement, cement mortar and concrete ( <i>second revision</i> )
12089 : 1987	Granulated slag for the manufacture of Portland slag cement — Specification
15388 : 2003	Silica fume — Specification

( CED 2 )