

Indian Standard
METHODS OF TEST FOR
DETERMINATION OF STRENGTH PROPERTIES
OF NATURAL BUILDING STONES
PART II TRANSVERSE STRENGTH
(*First Revision*)

Third Reprint JANUARY 1992

UDC 691.21:620.17

© Copyright 1975

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

*Indian Standard*METHODS OF TEST FOR
DETERMINATION OF STRENGTH PROPERTIES
OF NATURAL BUILDING STONES

PART II TRANSVERSE STRENGTH

(First Revision)

Stones Sectional Committee, BDC 6

Chairman

SHRI C. B. L. MATHUR

*Representing*Public Works Department, Government of
Rajasthan, Jaipur*Members*

SHRI K. K. AGRAWALA

Builders' Association of India, Bombay

SHRI K. K. MADHOK (*Alternate*)

SHRI T. N. BHARGAVA

Ministry of Shipping & Transport (Roads Wing)

CHIEF ARCHITECT

Central Public Works Department, New Delhi

LALA G. C. DAS

National Test House, Calcutta

SHRI P. R. DAS (*Alternate*)DEPUTY DIRECTOR (*RESEARCH*)Public Works Department, Government of Uttar
Pradesh, LucknowDEPUTY DIRECTOR (*RESEARCH*),
CONTROL AND RESEARCH
LABORATORYPublic Works Department, Government of Orissa,
Bhubaneswar

DR M. P. DHIR

Central Road Research Institute (CSIR), New
DelhiSHRI R. L. NANDA (*Alternate*)

DIRECTOR

Engineering Research Institute, Baroda

DIRECTOR (CSMRS)

Central Water & Power Commission, New Delhi

DEPUTY DIRECTOR (CSMRS) (*Alternate*)

DIRECTOR, MERI

Building & Communication Department, Govern-
ment of Maharashtra, BombayRESEARCH OFFICER, MERI (*Alternate*)

SHRI M. K. GUPTA

Himalayan Tiles & Marble Pvt Ltd, Bombay

SHRI S. D. PATHAK (*Alternate*)

DR IQBAL ALI

Engineering Research Laboratory, Government of
Andhra Pradesh, HyderabadSHRI A. B. LINGAM (*Alternate*)

Hindustan Construction Co Ltd, Bombay

SHRI D. G. KADKADE

SHRI V. B. DESAI (*Alternate*)*(Continued on page 2)*

© Copyright 1975

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 1121 (Part II) - 1974

(Continued from page 1)

Members

SHRI T. R. MEHANDRU
SHRI PREM SWARUP

SHRI A. K. AGARWAL (*Alternate*)

DR A. V. R. RAO

DEPUTY DIRECTOR (MATERIALS) (*Alternate*)

SHRI M. L. SETHI

SHRI Y. N. DAVE (*Alternate*)

DR B. N. SINHA

SUPERINTENDING ENGINEER (DESIGN)

DEPUTY CHIEF ENGINEER (I & D) (*Alternate*)

SUPERINTENDING ENGINEER (DESIGN
AND PLANNING)

SUPERINTENDING ENGINEER (DESIGNS)

SUPERINTENDING ENGINEER
(PLANNING CIRCLE)

SUPERINTENDING SURVEYOR OF
WORKS

SHRI M. V. YOGI

SHRI J. K. CHARAN (*Alternate*)

SHRI D. AJITHA SIMHA,
Director (Civ Engg)

Representing

Institution of Engineers (India), Calcutta
Department of Geology & Mining, Government of
Uttar Pradesh, Lucknow

National Buildings Organisation, New Delhi

Department of Geology & Mining, Government of
Rajasthan, Jaipur

Geological Survey of India, Calcutta

Public Works Department, Government of Tamil
Nadu, Madras

Public Works Department, Government of Andhra
Pradesh, Hyderabad

Public Works Department, Government of Mysore,
Bangalore

Public Works Department, Government of West
Bengal, Calcutta

Public Works Department, Government of Hima-
chal Pradesh, Simla

Engineer-in-Chief's Branch (Ministry of Defence)

Director General, ISI (*Ex-officio Member*)

Secretary

SHRI K. M. MATHUR

Deputy Director (Civ Engg), ISI

Indian Standard

METHODS OF TEST FOR DETERMINATION OF STRENGTH PROPERTIES OF NATURAL BUILDING STONES

PART II TRANSVERSE STRENGTH

(First Revision)

0. FOREWORD

0.1 This Indian Standard (Part II) (First Revision) was adopted by the Indian Standards Institution on 1 October 1974, after the draft finalized by the Stones Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 Building stones are available in large quantity in various parts of the country and to choose and utilize them for their satisfactory performance, it is necessary to know the various strength properties determined according to standard procedure. This standard has, therefore, been formulated to cover the standard method for determining the strength properties of various stones. This standard covering compressive, transverse and shear strength properties was published in 1957 and is being revised based on the actual use of it in the past 17 years and the experience gained in testing of building stones for these properties in the various research laboratories of this country. In this revision, property of tensile strength has also been added which is also important for assessing the suitability of stone.

0.2.1 This standard is now being issued in four parts, each part covering a specific property to facilitate the use of this standard. Part II covers the determination of transverse strength of natural building stones.

0.3 In reporting the results of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS : 2-1960*.

1. SCOPE

1.1 This standard (Part II) lays down the procedure for the determination of transverse strength of natural building stones used for constructional purposes.

*Rules for rounding off numerical values (*revised*).

2. SELECTION OF SAMPLES

2.1 The sample shall be selected to represent a true average of the type or grade of stone under consideration.

2.2 The sample shall be selected from the quarried stone or taken from the natural rock, as described in **2.2.1** and **2.2.2** and shall be of adequate size to permit the preparation of the requisite number of test pieces.

2.2.1 *Stones from Ledges or Quarries* — The ledge or quarry face of the stone shall be inspected to determine any variation in different strata. Differences in colour, texture and structure shall be observed. Separate samples of stone weighing at least 25 kg each of the unweathered specimens shall be obtained from all strata that appear to vary in colour, texture and structure. Pieces that have been damaged by blasting, driving wedges, heating, etc, shall not be included in the sample.

2.2.2 *Field Stone and Boulders* — A detailed inspection of the stone and boulders over the area shall be made where the supply is to be obtained. The different kinds of stones and their condition at various quarry sites shall be recorded. Separate samples for each class of stone that would be considered for use in construction as indicated by visual inspection shall be selected.

2.3 When perceptible variations occur in the quality of rock, as many samples as are necessary for determining the range in properties shall be selected.

3. TEST PIECES AND CONDITIONING

3.1 Test pieces shall be made from samples selected in accordance with **2** and shall be blocks of size $20 \times 5 \times 5$ cm. The test pieces shall be measured at the centre section. The width shall be measured to the nearest 0.2 mm and the thickness shall be taken as the average of three measurements to the nearest 0.2 mm, one taken at centre and the other two near edges.

3.2 The direction of the rift shall be carefully marked on each test piece after finishing.


3.3 Three test pieces shall be used for conducting the test in each of the conditions mentioned in **3.3.1** and **3.3.2** separately.

3.3.1 The test pieces shall be immersed in water maintained at 20 to 30°C for 72 h before testing and shall be tested in saturated condition.

3.3.2 The test pieces shall also be tested in dry condition and shall be dried in an oven at $105 \pm 5^\circ\text{C}$ for 24 h and cooled in a desiccator to room temperature (20 to 30°C).

4. APPARATUS

4.1 A suitable form of apparatus is shown in Fig. 1.



5. PROCEDURE

5.1 Each test piece to be tested shall be evenly supported upon two self-aligning bearers (*A* and *B* in Fig. 1) 4 cm in diameter, the distance between the centres of bearers being 15 cm. Bearer *A* is supported horizontally on two bearer screws (*C* in Fig. 1), which carry hardened steel balls (*D* in Fig. 1) concentric with the bearer. Bearer *B* is supported on one such bearer screw and ball.

5.2 The load shall then be applied centrally at a uniform rate of 200 kg/min through a third bearer (*E* in Fig. 1), also 4 cm in diameter, placed midway between the supports upon the upper surface of the specimen (*S* in Fig. 1) and parallel to the supports. The length of all bearers shall exceed the maximum width of the specimen to be tested.

6. EVALUATION AND REPORT OF TEST RESULTS

6.1 The transverse strength of the specimen tested shall be calculated as follows :

$$R = \frac{3WL}{2bd^2}$$

where

R = transverse strength in kg/cm²,

W = central breaking load in kg,

L = length of span in cm,

b = average width in cm of the test piece at the mid section, and

d = average depth in cm of the test piece at the mid section.

6.2 The average of all the three results (separately for saturated and dry condition) shall be taken for the purpose of determining transverse strength of the sample.

6.3 In case any specimen gives a value of as much as 15 percent below the average, it may be examined for defects and if the low value appears to be due to a flaw or faulty test piece, a fresh test shall be made and the average of three tests taken.

6.4 The transverse strength of the sample shall be expressed in kg/cm².

6.5 Identification of the sample, date when the sample was taken and type of stone shall be reported.

6.6 The size and shape of the test piece used in the test shall be indicated.

6.7 A description of the way in which the test pieces were prepared shall be included.

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones: 331 01 31, 331 13 75

Telegrams: Manaksanstha
(Common to all Offices)

Regional Offices:

Telephone

| | |
|-------------------------------------------------------------------------------------|----------------------------------|
| Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002 | { 331 01 31 331 13 75 |
| *Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola, CALCUTTA 700054 | 36 24 99 |
| Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036 | { 2 18 43 3 16 41 41 24 42 |
| Southern : C. I. T. Campus, MADRAS 600113 | { 41 25 19 41 29 16 |
| †Western : Manakalaya, E9 MIDC, Marol, Andheri (East), BOMBAY 400093 | 6 32 92 95 |

Branch Offices:

| | |
|------------------------------------------------------------------------------|------------------------|
| 'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMADABAD 380001 | { 2 63 48 2 63 49 |
| †Peenya Industrial Area 1st Stage, Bangalore Tumkur Road BANGALORE 560058 | { 38 49 55 38 49 56 |
| Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar, BHOPAL 462003 | 6 67 16 |
| Plot No. 82/83, Lewis Road, BHUBANESHWAR 751002 | 5 36 27 |
| 53/5, Ward No. 29, R.G. Barua Road, 5th Byelane, GUWAHATI 781003 | 3 31 77 |
| 5-8-56CL, N. Gupta Marg (Nampally Station Road), HYDERABAD 500001 | 23 10 83 |
| R14 Yudhister Marg, C Scheme, JAIPUR 302005 | { 6 34 71 6 98 32 |
| 117/418 B Sarvodaya Nagar, KANPUR 208005 | { 21 68 76 21 82 92 |
| Patliputra Industrial Estate, PATNA 800013 | 6 23 05 |
| T.C. No. 14/1421, University P.O., Palayam TRIVANDRUM 695035 | { 6 21 04 6 21 17 |

Inspection Offices (With Sale Point):

| | |
|----------------------------------------------------------------------------------------------|---------|
| Pushpanjali, First Floor, 205-A West High Court Road, Shankar Nagar Square, NAGPUR 440010 | 2 51 71 |
| Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005 | 5 24 35 |

*Sales Office in Calcutta is at 5 Chowringhee Approach, P. O. Princep Street, Calcutta 700072

†Sales Office in Bombay is at Novelty Chambers, Grant Road, Bombay 400007

†Sales Office in Bangalore is at Unity Building, Narasimharaja Square, Bangalore 560002

Reprography Unit, BIS, New Delhi, India