

Mechanical Properties of Li₂TiO₃ and Li₂ZrO₃ Ceramics
Flexural Strength
Flexural Strength (MPa)
85.2
98.6
Li₂TiO₃
Li₂ZrO₃
Hardness (Pre- vs Post-Irradiation)
Hardness (GPa)
Initial
After Irradiation
3.7
3.145
5.1
4.2
Fracture Toughness (Pre- vs Post-Irradiation)
Fracture Toughness (MPa·m¹/²)
2.38
3.2
3.2