
Advanced Ceramic Performance Metrics for Fusion Reactors
Porosity Comparison by Fabrication Method
Porosity (%)
0
2
4
6
8
10
12
14
16
4.5
12.5
10
SiO₂-based CCS
Li₂TiO₃
Li₄SiO₄
Swelling Resistance under Fusion Neutron Irradiation
Swelling (%) at 15 dpa
0
1
2
3
4
5
6
0.5
4.0
Li₂ZrO₃
Li₂TiO₃