Test Report

Applicant : Shenzhen INNO Technology Co., LTD

Address : F9, Building 20, Xiangnan District 4, Zhangkeng Community, Minzhi Street, Longhua District, Shenzhen,Guangdong,Chin

The following sample(s) was/were submitted and identified on behalf of the client as:

Product Name : U20CAM-1080P

Manufacturer : Shenzhen INNO Technology Co., LTD

Address : F9, Building 20, Xiangnan District 4, Zhangkeng Community, Minzhi Street, Longhua District, Shenzhen,Guangdong,Chin

Date of Sample Received : Oct. 15, 2025

Test period : Oct. 15, 2025 - Oct. 22, 2025

Test requested	**Conclusion**
In accordance with RoHS Directive 2011/65/EU and amendment 2015/863/EU, to determine Cadmium (Cd), Lead (Pb), Mercury (Hg), Chromium (Cr (VI)), PBBs, PBDEs, Di (2-ethyl hexyl)-phthalate (DEHP), Dibutyl phthalate (DBP), Butylbenzyl phthalate (BBP), Diisobuty phthalate (DIBP) content on submitted samples.	Pass

Test method : Please refer to next page.

Test result : Please refer to next page.

Approved by: Richard Ke **Date:** Oct. 22, 2025

Richard Ke
(Signed for and on behalf)

Dongguan NTEK Testing Technology Co., Ltd. NTEK Report Seal

Test method:

1. For the Cadmium (Cd), Lead (Pb),Mercury (Hg), Chromium (Cr (VI)), PBBs, PBDEs:

With reference to IEC 62321 Procedures for the Determination of Levels of Regulated Substances in Electrotechnical Products, XRF scanning first test, then using chemical test method to confirm.

Testing Item		Test Method	Measuring Instrument	MDL
Screening test		IEC 62321-3-1: 2013 scanning	XRF	--
Wet Chemical test	Lead (Pb)	IEC 62321-5: 2013	ICP-OES	2mg/kg
	Cadmium (Cd)	IEC 62321-5: 2013	ICP-OES	2mg/kg
	Mercury (Hg)	IEC 62321-4: 2013+AMD1:2017	ICP-OES	2mg/kg
	Chromium (Cr (VI))▼	IEC 62321-7-2:2017	UV-Vis	8mg/kg
		IEC 62321-7-1: 2015		0.10μg/cm^2
	PBBs, PBDEs	IEC 62321-6: 2015	GC-MS	5 mg/kg

2. For the DEHP, DBP, BBP and DIBP:

Testing Item	Pretreatment Method	Measuring Instrument	MDL
Di (2-ethyl hexyl)-phthalate (DEHP)	IEC 62321-8: 2017	GC-MS	30mg/kg
Butylbenzyl phthalate (BBP)			30mg/kg
Dibutyl phthalate (DBP)			30mg/kg
Diisobuty phthalate (DIBP)			30mg/kg

Test Report

1. Description of the test subject:

Sample No.	Location	Sample Description
1	U20CAM-1080P	Black plastic frame
2	U20CAM-1080P	Glass chip
3	U20CAM-1080P	Black PCB board
4	U20CAM-1080P	Silver solder
5	U20CAM-1080P	Surface mount IC
6	U20CAM-1080P	Surface mount resistor
7	U20CAM-1080P	Black metal screw
8	U20CAM-1080P	Surface mount capacitor
9	U20CAM-1080P	Surface mount IC
10	U20CAM-1080P	Surface mount IC
11	U20CAM-1080P	Surface mount inductor
12	U20CAM-1080P	Beige plastic terminal block
13	U20CAM-1080P	Silver metal pins

2. Test results (Unit: mg/kg):

No.	Test Method	Heavy Metals and Flame Retardants					Phthalates				Conclusion
		Cd	Pb	Hg	Cr (Cr (VI))	Br (PBBs, PBDEs)	DEHP	BBP	DBP	DIBP	
1	Screening	BL	BL	BL	BL	BL	BL	BL	BL	BL	Pass
2	Screening	BL	BL	BL	BL	BL	N.A.	N.A.	N.A.	N.A.	Pass
3	Screening	BL	BL	BL	BL	IN	BL	BL	BL	BL	Pass
	Wet Chem.	---	---	---	---	N.D.	---	---	---	---	
4	Screening	BL	BL	BL	BL	N.A.	N.A.	N.A.	N.A.	N.A.	Pass
5	Screening	BL	BL	BL	BL	BL	N.A.	N.A.	N.A.	N.A.	Pass
6	Screening	BL	BL	BL	BL	BL	N.A.	N.A.	N.A.	N.A.	Pass
7	Screening	BL	BL	BL	IN	N.A.	N.A.	N.A.	N.A.	N.A.	Pass
	Wet Chem.	---	---	---	N.D.	---	---	---	---	---	
8	Screening	BL	BL	BL	BL	BL	N.A.	N.A.	N.A.	N.A.	Pass
9	Screening	BL	BL	BL	BL	BL	N.A.	N.A.	N.A.	N.A.	Pass
10	Screening	BL	BL	BL	BL	IN	N.A.	N.A.	N.A.	N.A.	Pass
	Wet Chem.	---	---	---	---	N.D.	---	---	---	---	
11	Screening	BL	BL	BL	IN	BL	N.A.	N.A.	N.A.	N.A.	Pass
	Wet Chem.	---	---	---	N.D.	---	---	---	---	---	
12	Screening	BL	BL	BL	BL	IN	BL	BL	BL	BL	Pass
	Wet Chem.	---	---	---	---	N.D.	---	---	---	---	
13	Screening	BL	BL	BL	BL	N.A.	N.A.	N.A.	N.A.	N.A.	Pass

Note:

(1) (a) It is the result on total Br while test PBBs, PBDEs by XRF, It is the result on total Cr while test Cr (VI)I by XRF.

(b) Results are obtained by XRF for primary screening and further chemical testing by ICP-OES (for Pb, Cd and Hg), UV-Vis (for Cr (VI)) and GC-MS (for PBBs, PBDEs) is recommended to be performed, if the concentration exceeds the below warning value according to IEC 62321-3-1:2013 (unit: mg/kg).

Element	Polymer	Metal	Composite Materials
Cadmium (Cd)	BL≤70<X<130≤OL	BL≤70<X<130≤OL	LOD<X<150≤OL
Lead (Pb)	BL≤700<X<1300≤OL	BL≤700<X<1300≤OL	BL≤500<X<1500≤OL
Mercury (Hg)	BL≤700<X<1300≤OL	BL≤700<X<1300≤OL	BL≤500<X<1500≤OL
Chromium (Cr)	BL≤700<X	BL≤700<X	BL≤500<X
Bromine (Br)	BL≤300<X	--	BL≤250<X

(c) The XRF screening test for RoHS elements –The reading may be different to the actual content in the sample be of non-uniformity composition.

(d) The Screening results of Phthalates are for primary screening, and further chemical testing by GC-MS are recommended to be performed if the concentration exceeds the warning value.Where n= number of mixed tests.

Compound	Polymer
DBP	BL ≤ 1000/n< X
BBP	BL ≤ 1000/n< X
DEHP	BL ≤ 1000/n< X
DIBP	BL ≤ 1000/n< X

(e) OL=Over Limit, BL=Below Limit, IN=Inconclusive, LOD= Limit of Detection;

(2) mg/kg=ppm=0.0001%, N.D.=Not detected(<MDL), MDL=Method Detection Limit, "---"=Not conducted, "--"=Not regulated, "N.A."=Not applicable.

(3)"▼" =Metal sample

a. The sample is positive for Cr (VI) if the Cr (VI) concentration is greater than 0.13 μg/cm². The sample coating is considered to contain Cr (VI) ;

b. The sample is negative for Cr (VI) if Cr (VI) concentration is less than 0.10 μg/cm². The coating is considered a non-Cr (VI) based coating ;

c. The result between 0.10 μg/cm² and 0.13 μg/cm² is considered to be inconclusive - unavoidable coating variations may influence the determination ;

Information on storage conditions and production date of the tested sample is unavailable and thus Cr (VI) results represent status of the sample at the time of testing.

(4) RoHS Requirement

Restricted substances	Limits
Lead (Pb)	0.1% (1000 ppm)
Cadmium (Cd)	0.01% (100 ppm)
Chromium(VI) (Cr (VI))	0.1% (1000 ppm)
Mercury (Hg)	0.1% (1000 ppm)
Polybrominated biphenyls (PBBs)	0.1% (1000 ppm)
Polybrominated diphenyl ethers (PBDEs)	0.1% (1000 ppm)
Di (2-ethyl hexyl)-phthalate (DEHP)	0.1% (1000 ppm)
Butylbenzyl phthalate (BBP)	0.1% (1000 ppm)
Dibutyl phthalate (DBP)	0.1% (1000 ppm)
Diisobuty phthalate (DIBP)	0.1% (1000 ppm)

The above limits are reference with RoHS Directive 2011/65/EU and amendment 2015/863/EU.

(5) Unless otherwise specified, refer to ILAC-G8:09/2019 and use the binary decision rule of simple acceptance (W=0) for conformity assessment.

Photographs of Sample:






5
6
7
8
9
10
11
12-13

Test Report

声明: Statement:

1.检测报告无批准人签字、“检测专用章”或“报告章”无效;

1.This report is considered invalid without approved signature, Detection special seal or Report seal;

2.样品及样品信息由申请者提供，申请者应对其真实性负责，NTEK 未核实其真实性;

2. The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which NTEK hasn't verified;

3. 本报告检测结果仅对受测样品负责;

3. The result(s) shown in this report refer(s) only to the sample(s) tested;

4. 未经 NTEK 书面同意，不得部分复制本报告;

4. Without written approval of NTEK, this report can't be reproduced except in full;

5. 如检测报告中的英文内容与中文内容有差异，以中文为准。

5. In case of any discrepancy between the English version and Chinese version of the testing reports(if generated), the Chinese version shall prevail.

备注:报告未加盖 CMA 资质章时，本报告中的数据结果仅供科研、教学、企业内部质量控制、企业产品研发等目的用。

Remark: When the report without CMA qualification seal, the testing data and result(s) in this report is(are) just for scientific research, education, internal quality control and product development etc.

*** End of Report***