Warm ClayS25 AFDT

Visual Hue Request: RED/YELLOWISH

New Std	Retrieve Std	Store Std	List Std

Instrument Setup: %R LAV SCI UV Cal

Date: 21-Dec-23 Time: 06:16:08

Batch Name 3 of 3

)20963 159559 DOM2401217 WARM CLAY

New Bat	Retrieve Bat	Store Bat	List Bat

Instrument Setup: %R LAV SCI UV Cal

Date: 03-Sep-24 Time: 10:18:53

Delta | D65 / 10 | F11 / 10

+Δb*
more yellow
Stron
+Δa*
-Δa*
Weaker
a
more blu
-Δb*

+ΔL*
a
-ΔL*

DataColor TOOLS 2.8.1 S/N NO. 8823242

Standard %R

400-450nm	29.99	25.35	21.77	18.84	16.59	15.31
460-510nm	14.79	14.79	15.84	17.67	18.59	18.41
520-570nm	17.85	17.65	17.67	18.18	19.23	21.04
580-630nm	23.67	26.46	28.90	30.49	31.67	33.52
640-690nm	36.55	40.92	45.78	52.94	59.62	63.76
700nm	68.84					

Single/All	Zoom In	Zoom Out	CMC Plot	Print Form

CMC DE Pass/Fail Tolerance: 0.80

l:c Ratio: (2.00 1.00)

Batch Name	Ill/Obs	DL*	Da*	Db*	DL*/lSL	DC*/cSC	DH*/SH	CMC DE	M.I.	P/F		Color	Comments
70017368 24020963 159559 DOM2401217 WARM CLAY	D65 10 Deg	1.01	-0.21	-0.49	0.45	-0.28	-0.38	**0.65**		**Warn**	too light	too dull	too blue
70017368 24020963 159559 DOM2401217 WARM CLAY	F11 10 Deg	0.86	0.30	-0.02	0.38	0.15	-0.24	**0.47**	0.69	**Pass**	too light	too bright	too blue