Warm ClayS25 AFDT

Visual Hue Request: RED/YELLOWISH

| New Std	Retrieve Std	Store Std	List Std

Instrument Setup: %R LAV SCI UV Cal

Date: 21-Dec-23   Time: 06:16:08

Batch Name   1   of   2

149636 MNB2400034 AFDT WARM CLAY

New Bat	Retrieve Bat	Store Bat	List Bat

Instrument Setup: %R LAV SCI UV Cal

Date: 15-Jun-24   Time: 09:48:57

Delta | D65 / 10 | F11 / 10 |

Single/All	Zoom In	Zoom Out	CMC Plot	Print Form

DataColor TOOLS 2.8.1   **S/N NO.   8823242**

Standard %R

400-450nm	29.99	25.35	21.77	18.84	16.59	15.31
460-510nm	14.79	14.79	15.84	*17.67*	18.59	18.41
520-570nm	17.85	17.65	17.67	18.18	19.23	21.04
580-630nm	23.67	26.46	28.90	30.49	31.67	33.52
640-690nm	36.55	40.92	45.78	52.94	59.62	63.76
700nm	68.84					

CMC DE Pass/Fail Tolerance: 0.80

I:c Ratio: (2.00   1.00)

Batch Name	Ill/Obs	DL*	Da*	Db*	DL*/lSL	DC*/cSC	DH*/SH	CMC DE	M.I.	P/F		Color	Comments	
70035343 MINIBULK 149636 MNB2400034 AFDT WARM CLAY	D65 10 Deg	-0.64	0.45	0.28	-0.29	0.34	-0.01	**0.45**		Pass	too dark	too bright		too blue
70035343 MINIBULK 149636 MNB2400034 AFDT WARM CLAY	F11 10 Deg	-0.33	0.67	0.96	-0.14	0.71	0.48	**0.87**	0.80	Fail	too dark	too bright		too yellow