

Standard Name92 of 237

⬆️ AA2V Grey Five-FW17 ⬇️

Visual Hue Request:

New Std	Retrieve Std	Store Std	List Std
---------	--------------	-----------	----------

Instrument Setup:%R LAV SCI UV Cal
Date: 14-Jun-24Time: 14:27:20


Batch Name9 of 9

⬆️ 4A/E1778 144130 DOM2400843 AA2V GR ⬇️

New Bat	Retrieve Bat	Store Bat	List Bat
---------	--------------	-----------	----------

Instrument Setup: %R LAV SCI UV Cal
Date: 15-Jun-24Time: 10:19:37

DeltaD65 / 10F11 / 10



Single/All	Zoom In	Zoom Out	CMC Plot	Print Form
------------	---------	----------	----------	------------

DataColor TOOLS 2.8.1S/N NO. 8823242

Standard %R						
400-450nm	13.65	12.16	11.12	10.30	9.69	9.25
460-510nm	9.04	8.93	8.92	8.96	9.02	9.06
520-570nm	9.10	9.08	8.97	8.93	8.90	8.80
580-630nm	8.46	8.22	8.24	8.33	8.13	7.47
640-690nm	7.55	8.43	12.00	19.39	31.09	40.81
700nm	53.71					

CMC DE Pass/Fail Tolerance: 0.80

I:c Ratio: (2.00 1.00)

Batch Name	III/Obs	DL*	Da*	Db*	DL*/ISL	DC*/cSC	DH*/SH	CMC DE	M.I.	P/E	Color	Comments	
60017204 POAO2404A/E1778 144130 DOM2400843 AA2V GR D65 10 Deg	-0.20	-0.43	-0.01	-0.11	-0.04	-0.57	0.59			Pass	too dark	too dull	too green
60017204 POAO2404A/E1778 144130 DOM2400843 AA2V GR F11 10 Deg	-0.22	-0.23	0.02	-0.12	0.06	-0.29	0.32	0.20		Pass	too dark	too bright	too green