Optimising Concrete Strength: Regression Analysis of Concrete Mixture Efficiency

---

Executive Summary

Purpose of the report:

The report aims to determine the optimal concrete mixture for construction projects by exploring various components of concrete such as cement, water, fly ash, and aggregates, and their impact on compressive strength using regression analysis. It is used to identify how to improve the mixture efficiency by reducing the material cost and promoting sustainability.

Key descriptive Statistics:

The dataset is examined by formatting the variable name for flexibility and removing duplicates. Additionally, Boxplot was plotted to detect any outliers for the data integrity.

The components of concrete had positive and negative correlations with the compressive strength such as

- Cement and fly ash increases the compressive strength
- Water and coarse aggregates decrease the compressive strength

Main results and inferences:

Model selection: For the analysis, multiple models were created, tested, and plotted to predict concrete strength. The multiple regression model 5 has 89% of variability even with the minor issue in residual plots. The model also cleared the assumptions test for heteroscedasticity and normality.

Inferences: The results show that increasing the usage of cement and fly ash while reducing the water and coarse aggregate usage will enhance the strength of the concrete.

Recommendations and conclusion:

The regression analysis offers strategies for the optimisation of concrete mixtures. It also shows slumps should be controlled for workability and integrity. Moreover, the model's high accuracy can be used for marketing strategies in companies to increase product quality, reduce costs, and have a strong market position.

Table of Contents

Sr. No.	Particulars
1	Introduction
2	Descriptive Statistics and Preliminary Correlation Analysis
3	Method
4	Analytics
5	Recommendations & Conclusions
6	References

Introduction:

In the construction industry, finding the appropriate strength, cost, and sustainability of concrete and proportions of the concrete mixture is important to have a safe, strong, and cost-effective construction project. Concrete is one of the important materials in construction and its compressive strength is an important factor that fully depends on the concrete's ingredients and proportions. Therefore, it is important to know the appropriate selection of the mixture (Tran et al., 2020).

The purpose of this analysis is to explore various factors such as cement, water, aggregates, fly ash, and superplasticizer relationships and their impact on the concrete mixture. By utilising this dataset, the predictive linear model can be built which will help concrete manufacturing companies to determine the appropriate concrete mixture to find the balancing material cost and quality. Therefore, the goal is to create a model to reduce costs, minimise the wastage of resources, increase the mixture's efficiency, and deliver a sustainable approach toward concrete manufacturing.

Descriptive Statistics and Preliminary Correlation Analysis:

This analysis aims to determine the optimal concrete mixture for construction projects based on slump test observation. In the dataset primary dependent variable is 28-day compressive strength and the independent variables are slump, flow, cement, slag, fly ash, water, superplasticizer (SP), coarse aggregate, and fine aggregate.

Summary Statistics

Before executing any statistical analysis, the dataset was examined for any duplicates, and the variable names were formatted for easy access.

Below are the summary statistics for the variables:

Variable	Mean	Median	Standard Deviation	Variance	Mode	Range	IQR
Cement	229.89	248	78.88	6221.62	159	237	151.9
Slag	77.97	100	60.46	3655.58	0	193	124.95
Fly Ash	149.01	164	85.42	7296.25	0	260	120.45
Water	197.17	196	20.21	408.37	168	80	29.5
SuperPlasticizers (SP)	8.54	8	2.81	7.88	6	14.6	4
Coarse Aggregate	883.98	879	88.39	7813.04	904	341.9	133.3
Fine Aggregate	739.6	742.7	63.34	4012.22	757	261.4	103.5
Slump	18.05	21.5	8.75	76.58	0	29	9.5
Flow	49.61	54	17.57	308.66	20	58	25.25
Strength	36.04	35.52	7.84	61.44	26.42	41.34	10.31

Outlier detection:



A boxplot was created to identify the outliers.

Correlation Analysis:

The correlation table was created to understand the relationship between the concrete's ingredients to the compressive strength. The table highlights high and moderate correlation values in bold:

	Cement	Slag	Fly ash	Water	SP	Coarse aggregate	Fine_aggregate	Slump	Flow	Strength
Cement	1.0000	-0.2436	-0.4865	0.2211	-0.1064	-0.3099	0.0570	0.1459	0.1865	**0.4457**
Slag	-0.2436	1.0000	-0.3226	-0.0268	**0.3065**	-0.2238	-0.1835	-0.2840	-0.3272	-0.3316
Fly ash	-0.4865	-0.3226	1.0000	-0.2413	-0.1435	0.1726	-0.2829	-0.1186	-0.0554	**0.4444**
Water	0.2211	-0.0268	-0.2413	1.0000	-0.1555	**-0.6022**	0.1146	**0.4666**	**0.6320**	-0.2542
SP	-0.1064	**0.3065**	-0.1435	-0.1555	1.0000	-0.1042	0.0583	-0.2129	-0.1763	-0.0379
Coarse aggregate	-0.3099	-0.2238	0.1726	**-0.6022**	-0.1042	1.0000	**-0.4885**	-0.1882	-0.3258	-0.1607
Fine_aggregate	0.0570	-0.1835	-0.2829	0.1146	0.0583	**-0.4885**	1.0000	0.2023	0.1904	-0.1545
Slump	0.1459	-0.2840	-0.1186	**0.4666**	-0.2129	-0.1882	0.2023	1.0000	**0.9061**	-0.2234
Flow	0.1865	-0.3272	-0.0554	**0.6320**	-0.1763	-0.3258	0.1904	**0.9061**	1.0000	-0.1240
Strength	**0.4457**	-0.3316	**0.4444**	-0.2542	-0.0379	-0.1607	-0.1545	-0.2234	-0.1240	1.0000

- High correlation = ($|R| \geq 0.7$).
- Moderate correlation = ($0.4 \leq |R| < 0.7$)

Individual Scatterplot for all models:



Scatterplots are used to visualise the relationships between different material proportions and concrete strength.

Insights:

- Strength vs. Cement: The correlation is positive (R = 0.4457) and the scatterplot suggests that the strength of the material increases with the amount of cement used.
- Fly Ash vs. Strength: These two variables also indicate a positive connection (R = 0.4444) by showing stronger concrete materials have a higher fly ash content.
- Water vs Strength: The correlation is negative (R = -0.2542) and the scatterplot indicates that strength decreases with an increase in water content.
- Coarse aggregate vs Strength: The two variables show a weak negative correlation (R = -0.1607), the coarse aggregate has little impact on the strength.

Method:

The regression models have been developed to estimate the strength of concrete to dependent variables that include slag, water, coarse aggregate, fine aggregate, fly ash, cement, slump, and flow. All these factors impact the characteristics of the concrete as the concrete strength is the most important measure in construction materials and performance.

The selection of multiple linear regression is because in this case, it assumes a linear relation between concrete strength and its predictors. Some preliminary visualisations were implemented in the correlation matrix to support the linear relation by the majority of variables. Regression plots are also used to visualise and assess the fit of the linear model.

Moreover, other aspects also need to be examined such as homoscedasticity support, the independence of observations, and normality factors of residuals. This approach gives more accurate outcomes and improves decision-making in construction projects.

Analytics:

When comparing all the five models, model 5 indicates the best fit. This regression model predicts concrete strength using the variables: water, coarse aggregate, fly ash, cement, and slump.

Model fit analysis:

```
Call:
lm(formula = strength ~ +water + coarse_aggr + fly_ash + cement +
   slump, data = data_unique)

Residuals:
   Min     1Q  Median     3Q    Max
-6.3584 -1.6836 -0.1591  1.6507  5.6722

Coefficients:
              Estimate   Std. Error  t value   Pr(>|t|)
(Intercept)   55.438357  6.207462   8.931    2.72e-14 ***
water         -0.133630  0.017772  -7.519    2.78e-11 ***
coarse_aggr   -0.023969  0.003724  -6.436    4.67e-09 ***
fly_ash        0.073854  0.003436  21.496     < 2e-16 ***
cement         0.084512  0.003812  22.171     < 2e-16 ***
slump         -0.127279  0.033010  -3.856    0.000208 ***
---
Signif. codes:  0 '***' 0.001 '**' 0.01 '*' 0.05 '.' 0.1 ' ' 1

Residual standard error: 2.548 on 97 degrees of freedom
Multiple R-squared:  0.8995,	Adjusted R-squared:  0.8943
F-statistic: 173.6 on 5 and 97 DF,  p-value: < 2.2e-16
```

- The Adjusted R-squared value of 0.8943 suggests that about 89% of the variability in concrete strength is a strong model fit.

- The F-statistic (173.6) and p-value (< 2.2e-16) confirm the overall model significance.

Residuals plot:

- In the **Residuals vs Fitted plot**, the residuals are randomly scattered around zero without any clear pattern by supporting the linear assumption.

- In the **Q-Q Residual plot**, the points follow the straight diagonal line which shows that residuals are normally distributed.

- In the **Scale-Location plot**, shows a slight upward curve which denotes mild heteroscedasticity but it doesn't seem severe.

- In the **Residuals vs Leverage plot**, there are no significant points with high cook's distance, therefore no points are significantly influencing the model.



Checking assumptions:

- **BP Test:** The p-value of 0.1606 shows no significant heteroscedasticity.
- **Shapiro-Wilk Test**: A p-value of 0.8499 shows that the residuals are normally distributed.

Inferences for analysis:

With the above analysis, we can involve these ideas,

- Cement and fly ash can be used more to improve strength, leading to cost-effective production.
- Water and coarse aggregate can be reduced to enhance strength, emphasising precise mixing measurements.
- The slump can be controlled within optimal ranges to balance workability and strength

Recommendation & conclusion:

The regression analysis on concrete strength provides effective strategies for production in construction projects. The key takeaway from the analysis is material optimisation such as reducing water and coarse aggregate to improve the strength and usage of fly ash as a cost-effective product that enhances the concrete quality and also minimises the environmental impact which aligns with sustainability trends that attract eco-friendly clients.

To reduce the risks of concrete failure, slump can be controlled to the ideal range to have workability and structure integrity. Doing this not only prevents any product risks but also increases customer satisfaction.

Moreover, the regression model can be used by companies in their marketing strategies. They can present this model's high R-squared value to their potential clients by demonstrating calculated concrete mixes to build trust and credibility.

In conclusion, the insights from the model can help concrete manufacturers to increase product quality, reduction of costs, and have a better market position. Companies can exceed client expectations and have long-term growth and success if they can follow these recommendations and market data-based solutions.

References

- Tran, V. Q., Mai, H.-V. T., Ly, H.-B., & Nguyen, T.-A. (2020). Prediction of Later-Age Concrete Compressive Strength Using Feedforward Neural Network. *Advances in Materials Science and Engineering*, *2020*(2020), 1–8. https://doi.org/10.1155/2020/9682740.
- Yeh, I. (2007). Concrete Slump Test [Dataset]. UCI Machine Learning Repository. https://doi.org/10.24432/C5FG7D.