



Complete Analytical Solution
ISO 9001-2015 Certified

SHREE RAM TESTING LABORATORIES

ISO 9001 : 2015 Approved Laboratory

Lab: A-2/103, Site-V, UPSIDC Industrial Area, Kasna, Greater Noida-201306

Mob: 9953984801, 9717160780, 9999024801, E-mail: stl.noida@gmail.com

E-mail: shreeramlab@yahoo.com, Website: www.shreeramlab.in

TEST REPORT

Issued to: M/S Satya Ventures	Report No.	MS-170519-01
Satya Parkash Bhawan, Phagwara Road	Report Date:	11/06/2019
Hoshiarpur - 146001 (Punjab)	Sample Received:	17/05/2019
	Analysis Date:	18/05/2019 to 10/06/2019
	Sampled By:	Customer

Sample Description : WPC Wood

Products Description : Wood polymer composite, the main components that are used in marking of WPC are wood & polymer. The origin of wood is punjab (Hoshiarpur) & polymer is Taiwan.

RESULT

Sr. No.	Parameters	Test method	Unit	Result
1	Density	IS:2380(P-3):1997	kg/m ³	997.5
2	Water Absorption (at 2 Hrs.)	IS:2380(P-3):1997	%	0.17
3	Water Absorption (at 24 Hrs.)	IS:2380(P-3):1997	%	0.42
4	Modulus of Rupture	IS:2380(P-4):1997	N/m ²	35.8
5	Modulus of Elasticity	IS:2380(P-4):1997	N/mm ²	1914
6	Thickness Swelling after 24 hrs.	IS:2380(P-17):1997	%	0.68
7	Moisture Content	IS:2380(P-3):1997	%	0.39
8	Tensile Strength	IS:2380(P-4):1997	N/mm ²	39.45
9	Flexure Test	IS:4020	-	Passing Test
10	Screw withdrawal Strength			
a	Face	IS:2380(P-14):1997	N	1505
b	Edge	IS:2380(P-14):1997	N	895
11	Nail withdrawal Strength			
a	Face	IS:2380(P-14):1997	N	890
b	Edge	IS:2380(P-14):1997	N	430
12	Edge Loading Test	IS:2380(P-14):1997	N	162

Note:- (1) The above results are related only to the test performed on the sample, Endorsement to product is neither inferred. (2) This report is not to be reproduced wholly or in part & can not be used as an evidence in the court of law & should not be used in a any advertising media without special permission in writing (3) Sample will be destroyed after 90 days from the date of reporting unless otherwise specified. (4) Total liability of our lab is limited to the invoice amount (5) report refers to the sample drawn by shree ram testing Laboratories unless mentioned otherwise



Complete Analytical Solution
ISO 9001:2015 Certified

SHREE RAM TESTING LABORATORIES

ISO 9001 : 2015 Approved Laboratory

Lab: A-2/103, Site-V, UPSIDC Industrial Area, Kasna, Greater Noida-201306

Mob: 9953984801, 9717160780, 9999024801, E-mail: stl.noida@gmail.com

E-mail: shreeramlab@yahoo.com, Website: www.shreeramlab.in

TEST REPORT

Issued to: M/S Satya Ventures Satya Parkash Bhawan, Phagwara Road Hoshiarpur - 146001 (Punjab)	Report No.	MS - 170519 - 01
	Report Date:	11/06/2019
	Sample Received:	17/05/2019
	Analysis Date:	18/05/2019 to 10/06/2019
	Sampled By:	Customer

Sample Description : WPC Wood

P- 2/2

Sr. No.	Parameters	Test method	Unit	Result
13	Edge Straightness test	IS:2380(P-14):1997	mm	0.07
14	Shock Resistance Test (as 5kgf)	IS:2823:1990	-	Passing The Test
14	Shock Resistance Test (as 5kgf)	IS:2823:1990	-	Passing The Test
15	Shock Resistance test	IS:4020(P-8)	-	There shall be no visible damage in any part of the wood after twentyfive blows on each end
16	Knife Test	IS:2380(P-14):1997	-	Passing The Test
17	Resistance to stain	IS:2823:1990	-	Passing The Test
18	Resistance to Crack	IS:2823:1990	-	No Crack
19	Resistance to Steam	IS:2823:1990	-	Passing The Test
20	Resistance to Cigarette burn	IS:2823:1990	-	Passing The Test
21	Spot Test	IS:2823:1990	-	No Spot
22	Humidity Test (Varying) - at 27± 2°C & 30 ±5 % RH for one week (Length)	IS:4020 (P-11):1997	mm	0.095
23	Humidity Test (Varying) - at 27± 2°C & 85 ±5 % RH for one week (Thickness)	SRTL/SOP/15	mm	0.048
24	Squareness	IS:2380(P-2):1977	mm	0.043
25	Workability Test	ASTM 648	-	Satisfactory
26	Fungus Proof	ASTM G 21	-	Satisfactory

END OF REPORT

Tested By

AUTHORIZED SIGNATORY

Note:- (1) The above results are related only to the test performed on the sample, Endorsement to product is neither inferred. (2) This report is not to be reproduced wholly or in part & can not be used as an evidence in the court of law & should not be used in any advertising media without special permission in writing (3) Sample will be destroyed after 90 days from the date of reporting unless otherwise specified. (4) Total liability of our lab is limited to the invoice amount (5) report refers to the sample drawn by shree ram testing Laboratories unless mentioned otherwise