PRODUCT INFORMATION DATA SHEET

17451 Von Karman Avenue, Irvine, CA 92614
Tel (949) 474-0400 (800) 544-3338
Fax (949) 474-7269
www.deftfinishes.com

09Y010 (09-Y-10) Chrome Free Polyurethane Primer

Product Information

Qualified Specifications LMA-MR035B CLASS N TYPE II
5PTMRL42 TYPE I

Description Non-chromated, two-component, high solids, elastomeric polyurethane primer

Features
- Corrosion inhibiting
- Resistant to immersion in water, jet fuels, engine oils, hydraulic and de-icing fluids
- Exhibits 60% minimum elongation at ambient conditions as well as flexibility at low (-60° ± 5°F) and high (350° ± 5°F) temperatures.

Color Brown (tinted to improve hiding)

Reducer None required.

Mix Ratio 1 part 09Y010 base by volume to 1 part 09Y010CAT catalyst by volume

Kit Size	09Y010 base	09Y010CAT
GK	128 oz / 3.79 L	128 oz / 3.79 L
QK	32 oz / 946 mL	32 oz / 946 mL
PK	16 oz / 473 mL	16 oz / 473 mL

Pot Life: 4 hours at 75° ± 10°F, 50 ± 10% R.H.

Viscosity (per LMA-MR035) Mixed, initial: 30 seconds, max # 4 Ford Cup
Mixed, pot life: 60 seconds, max # 4 Ford Cup

Induction Time none required

Application Thickness 1.5 – 2.0 mils dry film thickness (5PTMRL42)
0.6 – 1.2 mils dry film thickness (LMA-MR035B)

Storage Stability (Per 5PTMRL42) 1 year from date of manufacture when stored between 35 – 115°F.

Recommended Storage 1 year from date of manufacture when stored indoors in original unopened containers between 70° - 90°F.

Dry Times*

Set to Touch/Tack Free 5 hours, max
Dry Hard 8 hours, max
Full Cure 7 days, max (LMA-MR035B)
Dry to Topcoat* 4 hours, min; 48 hours, max (LMA-MR035B)
Accelerated cure** Air dry 1 hour followed by 5 hours at 101 – 140°F (LMA-MR035B)

* Dry times are established at ambient conditions, 75° ± 10°F, 50 ± 10% R.H.
** For testing purposes without topcoat, full cure is required. Under these conditions, the panels will be fully cured. It is not recommended to apply topcoat to fully cured panels. For optimum adhesion, apply topcoat when panels are set to touch/tack free.

Mixing Instructions

GK, QK & PK: Stir or shake the base component to ensure any pigment, which may have settled on the bottom of the can, has been fully incorporated into the base. Do not shake the base component longer than 5 minutes. Slowly add the one volume of catalyst to one volume base component. Mix by hand stirring, paint shaker or mechanical mixing to ensure the base/catalyst mixture is homogeneous. DO NOT SHAKE OR MECHANICALLY MIX MATERIAL FOR LONGER THAN 15 MINUTES.

Application Equipment

Conventional, Air, Air Assisted Airless, or HVLP spray equipment may be used to apply this material. For your application, please contact the equipment manufacturer for more specific information on Conventional or HVLP spray applications, and recommendations on hose diameter and lengths.

Typical Characteristics*

Characteristics	Base	Catalyst	Admixed
Weight per gallon	11.65	8.14	9.89
% Solids by weight	78.6%	53.0%	68.1%
% Solids by volume	68.9%	46.4%	57.6%
Coatings VOC (g/L)	268	414	340
Coatings VOC (lbs/gal)	2.24	3.45	2.84
Material VOC (g/L)	260	394	327
Material VOC (lbs/gal)	2.17	3.29	2.73

Dry Film Density:** 1.40 g/cc
Theoretical Coverage per gallon (GK) as applied: 924 sq. ft.
Theoretical Coverage per gallon kit (GK) as applied: 1848 sq. ft.
Theoretical Dry Film Weight (per gallon kit as applied): 3.31 g/sq. ft. (0.00730-lbs/sq. ft.)

* Characteristics are calculated based on product formulas and ingredient characteristics as reported to Deft, Incorporated by raw material suppliers. Values reported are not specification values. They are presented for general information only.
** Dry film density, theoretical coverage and dry film weight is based on proper application of coating at 1 mil dry film thickness and 100% transfer efficiency.

Packaging, Yields, Shipping Weight

This material is available in the follow kit sizes:

Kit size	Approx. Yield (Mixed)	Approx. Shipping Weight
GK	2 gallons	21.8 lbs (9.9 kg)
QK	2 quarts	5.9 lbs (2.7 kg)
PK	2 pints	3.8 lbs (1.7 kg)

Additional kit sizes are available upon request.

Equipment Cleanup

IS-213 Polyurethane Reducer may be used for general clean up of parts and equipment before coating has fully cured and is still in a liquid state. Once material is cured, use an approved chemical paint removal system to strip coating.

Safety

Refer to the product label or Material Safety Data Sheet (MSDS) for each component for Personal Protective Equipment and Proper Handling.