E INF. 190615.-

CAAP CO., INC.

POLYURETHANE * **Erosion Resistant Aircraft Coatings** * FLUOROELASTOMER

P.O. BOX 2066, HUNTINGTON, CONNECTICUT 06484-2066
Plant: 152 Pepe's Farm Road • Milford, Connecticut 06460
PHONE (203) 877-0375 • FAX (203) 874-6072 • EMAIL: email@caapco.com

APPLICATION PROCEDURE

CAAPCOAT FP-500 COLOR MATCHED GLOSS POLYURETHANE RAIN ERISOION COATING

CAAPCOAT FP-500 Color Matched Gloss Polyurethane Coating is a two component room temperature curing polyurethane elastomer designed for application to aircraft radomes, antennas and leading edges. Its purpose is to protect aircraft parts from rain impact at high speed while providing color tailorability for camouflage or aesthetic purposes. Materials used are designed to provide superior resistance to humidity while substantially reducing VOC and HAPs compounds.

The complete application procedure should be read and understood prior to application.

COMPONENTS

800 g	Quart can	FP-500 Color Matched Gloss Polyurethane
96 g	Glass bottle	Type II Curing Agent

SURFACE PREPARATION AND PRIMING

All surfaces to be coated must be primed. Surfaces should first be well sanded or grit blasted and thoroughly cleaned to insure maximum primer adhesion. Aeroglaze 9947 Wash Primer is recommended if stripping or repair of the coating may be necessary. Mix the primer 1:1 by volume. A primer thickness of 0.5 - 1.0 mil is adequate and may be topcoated after 30 minutes to 24 hours dry time without affecting peel strength. Epoxy primers, such as MIL-P-23377 are also suitable, although stripping of the coating is more difficult. **Sanding or solvent wiping the primer is not recommended**.

FP-500 POLYURETHANE APPLICATION

Thoroughly stir or shake the FP-500 to disperse pigments. Add the Curing Agent to the FP-500 and mix well. Dilution is not necessary, however, the coating may be diluted with PCBTF (Oxsol 100) solvent if desired. Apply 11 - 13 mils of FP-500 in multiple thin coats with suction or pressure spray equipment. Allow 5 - 20 minutes between coats for solvent evaporation. Approximately 1 – 2 mils of dry film thickness per crosscoat can be achieved, depending on equipment used and spray technique. Witness panels should be sprayed concurrently with production articles to establish build rate and final thickness. Recommended conditions are 60 - 80°F and 40 - 70 % RH. A total of 11 - 13 mils can be applied in less than 3 hours.

CURING

CAAPCOAT FP-500 coating cures in 2 - 3 days at ambient conditions. After an initial 16 hour ambient cure, the cure may be accelerated by heating at 150°F for 3 hours.

COVERAGE

One quart of CAAPCOAT FP-500 will cover 3- 4 square feet to a dry film thickness of 11 - 13 mils depending on application technique. Film density is 1.25 g/cc.

CLEAN-UP AND REMOVAL OF CURED COATING

All spray equipment should be flushed thoroughly with acetone or methyl ethyl ketone (MEK) immediately after use. Should any material cure within the gun, soaking the affected pieces in acetone or MEK will soften the coating sufficiently for removal. The coating can be stripped with acetone or methyl ethyl ketone (MEK). It may be necessary to maintain solvent contact by wrapping the solvent wetted surface in polyethylene film.

HANDLING PRECAUTIONS

Refer to the MSDS prior to use. CAAPCOAT Polyurethanes contain combustible and flammable solvents and should not be used in confined areas where there are open flames, arcing equipment, hot surfaces, or where smoking is permitted. Ground all metal surfaces to prevent the accumulation of static charge while spraying. Use only with adequate ventilation. Avoid prolonged or repeated breathing of vapor. Do not get in eyes, on skin or clothing. In case of contact, immediately flush eyes or skin with plenty of water for at least 15 minutes; for eyes, get medical attention. Do not store at temperatures above 38°C (100°F). Contains parachlorobenzotrifluoride (PCBTF), and less than 1% free isocyanate.

FOR INDUSTRIAL USE ONLY

No warranty, expressed or implied, is made except that the product conforms to CAAP Co.'s specifications. The technical data furnished is believed to be accurate and complete. Buyer assumes all risk of use, storage and handling of this product. CAAP CO., INC. shall not be responsible for special or consequential damages. Nothing contained herein shall be construed as a permission or recommendation for the use of the product in the infringement of any existing patent.