

Solicitud de ensayos de laboratorio

Laboratory Test Request

Quién suscribe / The Undersigned

Nombre / Name:

Jose Antonio Blanco Peran

Por la presente solicitamos la cotización de los ensayos de laboratorio correspondientes sobre el producto, su uso y aplicación aquí descrito, con el objetivo de obtener la certificación que demuestre que el producto cumple con todas las normativas exigidas por la legislación vigente de la comunidad europea.

Hereby, we request a quotation for the corresponding laboratory tests on the product, its use, and application as described here, with the aim of obtaining certification demonstrating that the product complies with all regulations required by current legislation of the European community.

Descripción del producto / Product description

Marca/Trade Mark

JANURSTYLE

Nombre del producto / Product name

PARCHIKIDS

Modelo / Model

1/1 TO 50

Descripcion breve / short description

Parches Termoadhesivos Para reparación ropa

Uso y aplicación del producto / Used for

Kit de 8 parches de reparación de rotura de ropa de tela termoadhesiva con dibujos, se pueden usar también como decoración para mochilas

Información adicional / Additional Information

Imágenes del producto**Voltage de trabajo del producto****Frecuencia de trabajo del equipo**

Agradezco su atención y espero su pronta respuesta, Atentamente

Appreciate your attention and look forward to your prompt, Sincely

Lugar / Place

San Juan de Alicante

Nombre/Name

Jose Antonio Blanco Peran

Título o cargo / Title or position

Director / Administrador

Fecha/Date

10/9/2025



BV CPS TEST LABORATUVARLARI LTD. STI.
BUREAU VERITAS CONSUMER PRODUCTS
SERVICES
Yalcin Kores Cad. No:22 Erdinc Binalari
A Blok 1.Kule 1.Kat 34209 Gunesli, Istanbul / Turkey
Tel:+90.212.494 35 35 Fax:+90.212.494 35 60
email:info.turkey@bvcps.com.tr
website: www.bureauveritas.com/cps



AB-0505-T
72252580106 (R2)
09-25

TEST REPORT

LAB LOCATION: TURKEY

SERVICE TYPE: Regular

LAB NUMBER: (7225)258-0106 REVISION2

THE DATE OF RECEIPT OF TEST ITEM: September 15, 2025

RE-CONFIRMATION DATE: September 17, 2025

START DATE FOR TESTING: September 17, 2025

DATE END OF TEST: September 22, 2025

REPORT REVISION DATE: September 23, 2025

REPORT REVISION DATE2: September 25, 2025

NUMBER OF WORKING DAYS: 4.0

CUSTOMER NAME / ADDRESS : JABP GLOBAL LLC
(Address: Calle Cervantes, 21 Escalera 6. Bajo M 03550, San Juan
(Alicante)
CONTACT NAME : (Attn: Jose Antonio Blanco Peran)

BUYER : JABP GLOBAL LLC

SUPPLIER REFERENCE : Style Number: MOD Patch 1 to 50
Po Number: ESP-8-PARCHIKIDS240924
Brand: Janurstyle

SAMPLE DESCRIPTION : Patch Sample (Parchikids-Models 1 to 50 Representative sample of a series of iron-on patches, all manufactured with the same materials, adhesive and production process. Only the design differs. Test results apply to all models in this series)
(Claimed Fiber Content: /)
(Claimed Fabric Weight: /)

COLOUR : /

SUBMITTED CARE INSTRUCTION : /

REASON FOR REVISION : “Customer Name/Address” and “Contact Name” have been changed, and “Style Number” has been added upon vendor’s request.
“Sample Image” has been corrected.

REASON FOR REVISION2 : “Customer Name/Address” and “Po Number” have been changed, and “Sample Description” has been added upon vendor’s request.

BV CPS Test Laboratuvarları Ltd. Sti. accredited by TÜRKAK under registration number AB-0505-T for TS EN ISO/IEC 17025:2017 as test laboratory.

Turkish Accreditation Agency (TÜRKAK) is a signatory to the European co-operation for Accreditation (EA) Multilateral Agreement (MLA) and to the International Laboratory Accreditation Cooperation (ILAC) Mutual Recognition Arrangement (MRA) for the recognition of test reports.

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report. Statements of conformity are based on simple acceptance criteria without taking measurement uncertainty into account, unless otherwise requested in writing. You have 60 days from the date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty, provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents. Testing reports without signature are not valid. BV CPS Test Laboratories is not responsible for deviations for the accuracy of the information provided by the customer that may affect the validity of the test results. Test results given in this test report represent only the sample(s) delivered to the laboratory, as sent to BV CPS Test Laboratories by the client/vendor via courier, cargo and/or manual delivery. No sampling is performed by BV CPS Test Laboratories.



AB-0505-T

72252580106
(R2)

09-25



Date Out
(25/09/2025)

Furkan Yilmaz
Client Team Lead

Hasan Altingul
Deputy General Manager Operation
(25/09/2025)

SUMMARY OF TEST RESULTS

TEST PERFORMED	PASS	FAIL	DATA
Formaldehyde*	X		
Azo-amines and Arylamine salts*	X		
Phthalates Content*	X		
Polynuclear Aromatic Hydrocarbons(PAHs)*	X		
Total Cadmium Content*	X		
Total Lead Content*	X		
*TURKAK Accredited- See Appendix A			

REMARKS	
1	: P: Pass, F: Fail, DATA: No Evaluation, N/A: Not Applicable
2	: *The reported expanded uncertainty is based on the standard uncertainty multiplied by a coverage factor of k=2, providing a level of confidence of approximately 95%. Unless otherwise is specified, the uncertainty of measurement has not been taken into account when assessing pass/fail of the sample against the requirements of the standard. In case consideration of measurement uncertainties when assessing pass/ fail limits, some results may be in borderline. Information on uncertainty is contained in appendix A on this report.
3	: The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.
4	: (7225)258-0106(Revision1) test report (dated September 23, 2025) is not valid, it is replaced by this report: (7225)258-0106 (Revision2)

SAMPLE DESCRIPTION ASSIGNED BY LABORATORY:

TEST ITEM	SAMPLE DESCRIPTION
I001	Multicolor Textile Patch

ORIGINAL
(SAMPLE IMAGE)



TEST RESULTS

Formaldehyde

- Test Method I** : EN ISO 14184-1:2011
(For materials other than leather) Quantification analysis by UV-VIS Spectrophotometer
- Test Method II** : EN ISO 17226-2:2019 with EN ISO 17226-1:2021 confirmation method in case of interferences. Alternatively, EN ISO 17226-1:2021 can be used on its own
- Test Method III** : The People's Republic of China National Standard GB/T 2912.1-2009.
- Test Method IV** : ITX-GB/T 2912.1/2012C Mod.
- Test Method V** : ITX-GB/T 19941/2005D Mod.
- Test Method VI** : ISO 14184-2 UV-VIS /CPSD-AN-00055-MTHD/09
- Test Method VII** : ITX-GB/T 2912.2/2012C Mod.
- Test method VIII** : CPSD-AN-00060-MTHD/Quantification analysis by UV-VIS / HPLC - DAD

Maximum Limit:	Baby & Children (≤ 3 years): 16 mg/kg Others: 75 mg/kg			
Tested Item(s)	Test Method	Result	Unit	Conclusion
I001	I	7	mg/kg	PASS

Note:

ND = Not detected
mg/kg = milligram(s) per kilogram
10 000 mg/kg = 1 %
Detection Limit (mg/kg) – 5

“>” = Greater than
mg/kg = ppm = part(s) per million
% = percent

Conc. = Concentration

Remark:

-

TEST RESULTS

Azo-amines and Arylamine salts

Test Method I : EN ISO 14362-1:2017

Test Method II : ISO 17234-1:2015

Test Method III : EN ISO 14362-3:2017 (For textile)/ ISO 17234-2:2011 (For leather)/
CPSD-AN-00107-MTHD/26

Quantification analysis by GC-MS and confirmation by LC-DAD.

Maximum Limit:	30 mg/kg				
Tested Item(s)	Test Method	Result			Conclusion
		Detected Analyte(s)	Conc.	Unit	
I001	I	/	ND	mg/kg	PASS

Note:

ND = Not detected
mg/kg = milligram(s) per kilogram
10 000 mg/kg = 1 %
Detection Limit (mg/kg) - 5 each

“>” = Greater than
mg/kg = ppm = part(s) per million
% = percent

Conc. = Concentration

Remark:

- The list of Azo-amines and Aryl Amine salts is summarized in table of Appendix.

Polycyclic Aromatic Hydrocarbons (PAHs)

Test Method : All materials: AFPS GS 2019

Maximum Limit:	Baby & Children (≤ 3 years): Each: 0.5 mg/kg, Sum of All: 5 mg/kg Others: Each: 1 mg/kg, Sum of All: 10 mg/kg				
Tested Item(s)	Type	Result			Conclusion
		Detected Analyte(s)	Conc.	Unit	
I001	I	/	ND	mg/kg	PASS

Note:

ND = Not detected
mg/kg = milligram(s) per kilogram
10 000 mg/kg = 1 %
Detection Limit (mg/kg) - 0.1 each

“>” = Greater than
mg/kg = ppm = part(s) per million
% = percent

Conc. = Concentration

Remark:

- The list of Polycyclic Aromatic Hydrocarbons (PAHs) is summarized in table of Appendix.

TEST RESULTS

Phthalates Content

Test Method : CPSD-AN-00095-MTHD/ IEC 62321-8:2017, CNS 15331:2018 using test method CNS 15138-1:2012, CNS 15493:2015 using test method CNS 15138-1:2012, AFIRM method , CPSC-CH-C1001-09.4 / 16 CFR 1307
Quantification analysis by GC-MS or LC-DAD-MS

Maximum Limit:	1000 mg/kg			
Tested Item(s)	Result			Conclusion
	Detected Analyte(s)	Conc.	Unit	
I001	/	ND	mg/kg	PASS

Note:

ND = Not detected
mg/kg = milligram(s) per kilogram
10 000 mg/kg = 1 %
Detection Limit (mg/kg) - 50 each

“>” = Greater than
mg/kg = ppm = part(s) per million
% = percent

Conc. = Concentration

Remark:

- The list of Phthalates is summarized in table of Appendix.

TEST RESULTS

Total Lead

Test Method I : Lead in paint and surface coatings: CPSC-CH-E1003-09.1:2011
Test Method II : Non-metal: CPSC-CH-E1002-08.3:2012
Test Method III : Metal: CPSC-CH-E1001-08.3:2012
Test Method IV : All materials except Leather: DIN EN 16711-1:2016
Leather: DIN EN ISO 17072-2:2019
Quantification analysis by ICP-AES

Maximum Limit:	90 mg/kg	
	Unit	Result
Tested Item(s)		I001
Method		II
Parameter	-	-
Lead (Pb)	mg/kg	ND
Conclusion	-	PASS

Note:

ND = Not detected
mg/kg = milligram(s) per kilogram
10 000 mg/kg = 1 %
Detection Limit (mg/kg) - 10

“>” = Greater than
mg/kg = ppm = part(s) per million
% = percent

Conc. = Concentration

Remark:

Total Cadmium

Test Method I : EN 1122:2001 Method B. (For plastics)
Test Method II : All materials except Leather: DIN EN 16711-1:2016
Leather: DIN EN ISO 17072-2:2019
Test Method III : Metal: EN 16711-1

Maximum Limit:	40 mg/kg	
	Unit	Result
Tested Item(s)	-	I003
Method		II
Parameter	-	-
Cadmium (Cd)	mg/kg	ND
Conclusion	-	PASS

Note:

ND = Not detected
mg/kg = milligram(s) per kilogram
10 000 mg/kg = 1 %
Detection Limit (mg/kg) - 10

“>” = Greater than
mg/kg = ppm = part(s) per million
% = percent

Conc. = Concentration

APPENDIX A –LIST OF MEASUREMENT UNCERTAINTIES		
TEST NAME	STANDARD NAME	MEASUREMENT UNCERTAINTY
Formaldehyde	ISO 14184-1	± 4,85%
Polycyclic Aromatic Hydrocarbons (PAHs)	CPSC-AN-00090-MTHD	±19.44%
Total Lead Content	CPSC-CH-E1003-09.1 (Based on 16 CFR 1303)	±23.09%
	CPSC-CH-E1002-08	±23.09%
	CPSC-CH-E1001-08	±20.95%
Total Cadmium Content	BS EN 1122	±23.09%
	CPS-AN-00004-MTHD	±23.09%
Azo-amines and Arylamine salts	EN ISO 14362-1	± % 21.04
Phthalates Content	ISO 14389	±25.77%
	CPSC-AN-00753-MTHD	

List of Phthalates Content					
No.	Name of Analytes	CAS-No.	No.	Name of Analytes	CAS-No.
1	Bis(2-ethylhexyl) phthalate (DEHP)	117-81-7	13	1,2-Benzenedicarboxylic acid, dipentylester, branched and linear	84777-06-0
2	Dibutyl phthalate (DBP)	84-74-2	14	1,2-Benzenedicarboxylic acid, di-C7-11- branched and linear alkyl esters (DHNUP)	68515-42-4
3	Butylbenzyl phthalate (BBP)	85-68-7	15	N-pentyl-isopentyl phthalate (NPIPP)	776297- 69-9
4	Di-isobutyl phthalate (DIBP)	84-69-5	16	Di-cyclohexylphthalate (DCHP)	84-61-7
5	Di-“isononyl” phthalate (DINP)	28553-12-0 68515-48-0	17	1,2-Benzenedicarboxylic acid, dihexyl ester, branched and linear (DHxP)	68515-50-4
6	Di-“isodecyl” phthalate (DIDP)	26761-40-0 68515-49-1	18	1,2-benzenedicarboxylic acid, di-C6-10- alkyl esters; 1,2-benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters with ≥ 0.3% of dihexyl phthalate (EC No. 201-559-5)	68515-51-5 68648-93-1
7	Di-n-octyl phthalate (DNOP)	117-84-0	19	Di-iso-hexylphthalate (DIHxP)	71850-09-4
8	1,2-Benzenedicarboxylic acid, di-C6-8- branched alkyl esters, C7-rich (DIHP)	71888-89-6	20	Di-n-propylphthalate (DPrP)	131-16-8
9	Di-isopentylphthalate (DIPP)	605-50-5	21	Diethyl phthalate (DEP)	84-66-2
10	Di-n-pentyl phthalate (DPP)	131-18-0	22	Dimethyl phthalate (DMP)	131-11-3
11	Bis(2-methoxyethyl) phthalate (DMEP)	117-82-8	23	Di-iso-octyl phthalate (DIOP)	27554-26-3
12	Di-n-hexyl phthalate (DnHP)	84-75-3	24	Di-n-nonyl phthalate (DNP)	84-76-4

List of Polynuclear Aromatic Hydrocarbons:

Name of Analytes	CAS-No.	No.	Name of Analytes	CAS-No.
Benzo (a) pyrene	50-32-8	13	Phenanthrene	85-01-8
Benzo (e) pyrene	192-97-2	14	Antracene	120-12-7
Benzo (a) anthracene	56-55-3	15	Fluoranthene	206-44-0
Chrysene	218-01-9	16	Pyrene	129-00-0
Benzo (b) fluoranthene	205-99-2	17	Indeno (1,2,3-cd) pyrene	193-39-5
Benzo (j) fluoranthene	205-82-3	18	Benzo (g,h,i) perylene	191-24-2
Benzo (k) fluoranthene	207-08-9	19	1-Methylpyrene	2381-21-7
Dibenzo (a,h) anthracene	53-70-3	20	Dibenzo[a,l]pyrene	191-30-0
Naphthalene	91-20-3	21	Dibenzo[a,i]pyrene	189-55-9
Acenaphthylene	208-96-8	22	Dibenzo[a,h]pyrene	189-64-0
Acenaphthene	83-32-9	23	Dibenzo[a,e]pyrene	192-65-4
Fluorene	86-73-7	24	Cyclopenta[c,d]pyrene	27208-37-3

List of Azo-amines and Arylamine salts:

No.	Name of Analytes	CAS-No.	No.	Name of Analytes	CAS-No.
1	4-Aminodiphenyl	92-67-1	15	4,4'-Methylene-bis-(2-chloroaniline)	101-14-4
2	Benzidine	92-87-5	16	4,4'-Oxydianiline	101-80-4
3	4-Chloro-o-toluidine	95-69-2	17	4,4'-Thiodianiline	139-65-1
4	2-Naphthylamine	91-59-8	18	o-Toluidine	95-53-4
5	o-Aminoazotoluene	97-56-3	19	4-Methyl-m-phenylenediamine (2,4-Toluenediamine)	95-80-7
6	5-nitro-o-toluidine (2-Amino-4-nitrotoluene)	99-55-8	20	2,4,5-Trimethylaniline	137-17-7
7	4-Chloroaniline (p-Chloroaniline)	106-47-8	21	o-Anisidine	90-04-0
8	4-Methoxy-m-phenylenediamine (2,4-Diaminoanisole)	615-05-4	22	4-Aminoazobenzene (p-Aminoazobenzene)	60-09-3
9	4,4'-Diaminodiphenylmethane (4,4'-Methylenedianiline)	101-77-9	23	2,4-Xylidine	95-68-1
10	3,3'-Dichlorobenzidine	91-94-1	24	2,6-Xylidine	87-62-7
11	3,3'-Dimethoxybenzidine (o-Dianisidine)	119-90-4	25	4-chloro-o-toluidinium chloride	3165-93-3
12	3,3'-Dimethylbenzidine (4,4'-Bi-o-tolidine)	119-93-7	26	2-Naphthylammoniumacetate	553-00-4
13	4,4'-Methylenedi-o-toluidine (3,3'-Dimethyl-4,4'-diaminodiphenylmethane)	838-88-0	27	4-methoxy-m-phenylene diammonium sulphate; 2,4-diaminoanisole sulphate	39156-41-7
14	p-Cresidine	120-71-8	28	2,4,5-trimethylaniline hydrochloride	21436-97-5

-END OF REPORT