


annealing T at $p_{\text{H}_2} = 1\text{e-}09$ bar

824 K



The headline. (a) The equilibrium habit evolves with hydrogen chemical potential: as $\Delta\mu_{\text{H}}$ grows the $-100''$ area fraction rises at the expense of $-111''$. (b) Because (100) is the one facet whose net surface stress is TENSILE in the continuum convention -- $f = -\tau$, so its τ 'mean of -2.00 N/m is $f = +2.00$ N/m -- while (110) and (111) are compressive, that change drives the interior from tension into compression and through zero at $\Delta\mu_{\text{H}} = 1.295$ eV, which at $p_{\text{H}_2} = 1\text{e-}09$ bar (a realistic residual vacuum) is 824 K uncorrected and 708 K once zero-point energy is included. The 116 K ZPE shift is the dominant systematic on this number and is drawn rather than footnoted. At the crossing the sign of every strain-induced NV shift reverses, which is a sharper experimental signature than any magnitude here because it needs no coupling constant and no absolute τ . Epistemic level L1; the H-poor side is unbounded while the dehydrogenation ceiling is uncomputed (see F2).