

Mehul Electro insulating industries

2610/A, Ph-4, G.I.D.C., Vata, Ahmedabad 382 445

Phone : 2584 2331/2, Fax: 2584 0356

Raw Materials Required For Grinding

Batch No :4526		Batch Start :11/24/2016 9:02:11 PM	Batch Qty :400
Allocated To :Ranchood			
Process	Product	Qty	
Grinding	CALCIUM OCT 3%	0.800	
Grinding	ZINC NAPHTHENATE 6%	1.200	
Grinding	XYLINE	12.000	
Grinding	SDI PASTE	8.000	
Grinding	ALUMINIUM PASTE NON L 0030	26.000	
Grinding	MEDIUM FATY 70%	260.000	
Thining	XYLINE	77.600	
Thining	BYK 306	0.800	
Thining	BARIUM OCT 6%	2.480	
Thining	COBALT OCT 6%	1.520	
Thining	ZIRCONIUM OCTOATE 6%	9.200	
Thining	NS	0.400	

Packing Details

Name	Qty
20 LTR	10

Grinding Information

Has Hymenguage?	Yes
Reading 1	
Reading 2	
Has Pigment Dispersion?	Yes

Shade Matching Type

Type :	Master Panel
Panel Number :	008
Rack Number :	08