

Secondary woodiness

1

0

-4

0

4

PC2

