



ALS USA Inc.
4977 Energy Way
Reno NV 89502
Phone: +1 775 356 5395 Fax: +1 775 355 0179
www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC
1712 CAREY AVENUE
SUITE 100
CHEYENNE WY 82001

Page: 1
Total # Pages: 3 (A - E)
Plus Appendix Pages
Finalized Date: 12-MAY-2021
Account: KEERRG

CERTIFICATE RE21096417

This report is for 52 samples of Rock submitted to our lab in Reno, NV, USA on 19-APR-2021.

The following have access to data associated with this certificate:

STEPHAN FINCH

LARRY MCMASTER

CHARLES REDDIEN

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
CRU-QC	Crushing QC Test
PUL-QC	Pulverizing QC Test
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize up to 250g 85% <75 um
CRU-21	Crush entire sample

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-MS61r	4A multi-element ICP-MS + REE	
Hq-MS42	Trace Hg by ICPMS	ICP-MS
PGM-ICP23	Pt, Pd, Au 30g FA ICP	ICP-AES
Rh-MS25	Rh 30g FA ICP-MS	ICP-MS
Aq-AA45	Trace Ag - aqua regia/AAS	AAS

The results of this assay were based solely upon the content of the sample submitted. Any decision to invest should be made only after the potential investment value of the claim 'or deposit has been determined based on the results of assays of multiple samples of geological materials collected by the prospective investor or by a qualified person selected by him/her and based on an evaluation of all engineering data which is available concerning any proposed project. Statement required by Nevada State Law NRS 519

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

***** See Appendix Page for comments regarding this certificate *****

Signature:

Saa Traxler, General Manager, North Vancouver



ALS USA Inc.

4977 Energy Way

Reno NV 89502

Phone: +1 775 356 5395 Fax: +1 775 355 0179

www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC

1712 CAREY AVENUE

SUITE 100

CHEYENNE WY 82001

Page: 2 - A

Total # Pages: 3 (A - E)

Plus Appendix Pages

Finalized Date: 12-MAY-2021

Account: KEERRR

CERTIFICATE OF ANALYSIS RE21096417

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	Ag-AA45 Ag ppm 0.2	ME-MS61r Ag ppm 0.01	ME-MS61r Al % 0.01	ME-MS61r As ppm 0.2	ME-MS61r Ba ppm 10	ME-MS61r Be ppm 0.05	ME-MS61r Bi ppm 0.01	ME-MS61r Ca % 0.01	ME-MS61r Cd ppm 0.02	ME-MS61r Ce ppm 0.01	ME-MS61r Co ppm 0.1	ME-MS61r Cr ppm 1	ME-MS61r Cs ppm 0.05	ME-MS61r Cu ppm 0.2
WF-1		2.08	<0.2	0.28	0.29	2.1	30	0.08	0.07	0.24	0.04	8.60	0.3	47	0.14	4.8
WF-2		1.02	<0.2	0.20	6.85	223	730	1.69	0.22	4.96	0.16	52.1	12.5	60	4.93	25.9
WF-3		0.11	1.4	1.48	3.94	19.3	540	2.35	0.06	0.46	0.10	24.1	1.1	19	3.24	7.5
WF-4		0.16	<0.2	0.22	6.08	80.5	310	2.66	0.35	0.34	0.22	40.5	0.5	8	1.53	14.4
WF-6		0.57	<0.2	0.04	6.67	1.7	2740	0.82	0.02	1.13	0.04	12.65	0.5	9	0.48	3.0
WF-7		1.68	0.3	0.42	6.46	1.3	2020	0.85	0.02	1.26	0.06	14.05	0.6	17	0.38	3.5
WF-9		0.53	<0.2	0.17	6.85	86.4	1000	1.89	0.15	0.74	0.07	20.6	1.4	11	1.63	4.1
WF-10		1.81	<0.2	0.10	6.99	52.5	1100	1.45	0.06	1.24	0.04	25.4	2.0	10	0.99	4.7
WF-12		0.47	<0.2	0.21	6.89	16.7	330	2.74	0.32	0.26	0.06	29.2	1.1	5	2.92	4.1
WF-13		0.60	<0.2	0.10	6.99	24.7	590	2.05	0.16	0.73	0.04	34.3	1.7	7	2.04	4.6
WF-15		0.31	<0.2	0.07	7.12	27.7	830	2.28	0.08	1.71	0.08	25.3	1.4	9	1.07	4.7
WF-16		1.09	<0.2	0.14	7.55	18.7	1010	1.40	0.04	2.01	0.07	23.9	1.4	7	0.67	5.9
WF-18		0.04	<0.2	0.11	7.63	27.0	1190	1.69	0.07	1.95	0.08	47.4	4.8	8	1.41	7.5
WF-19		0.37	<0.2	0.07	7.34	21.0	1080	1.56	0.06	2.42	0.07	46.6	3.4	9	0.61	9.9
WF-21		1.57	<0.2	0.12	7.57	21.7	600	3.30	0.32	0.90	0.08	49.9	3.7	11	3.35	9.4
WF-22		0.69	<0.2	0.14	7.52	22.1	610	2.60	0.28	1.73	0.12	61.0	4.6	11	3.22	12.5
WF-24		0.04	<0.2	0.17	5.93	12.6	820	2.14	0.08	0.73	0.09	33.4	1.6	7	1.97	4.9
WF-25		0.17	<0.2	0.13	6.18	9.0	1420	1.46	0.07	0.85	0.04	25.5	1.0	7	1.36	3.9
WF-27		0.33	<0.2	0.13	6.90	31.2	540	2.98	0.42	0.69	0.05	50.0	1.7	7	3.02	6.6
WF-28		0.55	<0.2	0.08	6.84	17.3	1390	2.02	0.13	1.16	0.05	37.9	1.3	7	2.04	4.0
WF-30		0.08	<0.2	0.17	6.79	17.2	410	2.72	0.18	0.52	0.05	29.4	1.0	4	2.92	2.8
WF-31		0.18	<0.2	0.10	6.24	12.8	1100	1.30	0.07	1.00	0.04	51.6	0.9	8	0.88	3.4
WF-32		1.65	<0.2	0.24	9.36	37.9	670	3.03	0.42	1.81	0.37	73.8	16.0	31	7.91	51.3
WF-33		0.15	<0.2	0.12	7.44	41.3	980	2.83	0.18	0.82	0.10	85.2	2.9	9	4.57	9.6
WF-34		0.48	<0.2	0.12	6.13	16.6	1230	1.67	0.12	1.44	0.06	32.8	1.2	6	1.93	4.2
WF-36		0.09	<0.2	0.10	7.11	14.4	1080	2.52	0.15	0.99	0.05	78.5	2.2	4	3.97	5.6
WF-37		0.52	<0.2	0.08	6.49	4.0	1440	1.67	0.10	1.25	0.04	26.5	0.9	5	1.90	3.1
WF-39		0.22	<0.2	0.07	6.35	1.7	1840	1.30	0.06	0.98	0.04	24.2	0.8	7	1.26	3.1
WF-41		0.05	<0.2	0.05	5.51	5.2	490	2.24	0.06	2.13	0.07	28.3	3.3	6	3.77	10.6
WF-42		0.42	<0.2	0.07	6.95	4.7	1260	1.71	0.07	2.25	0.06	33.8	2.5	8	1.93	6.0
WF-44		0.21	<0.2	0.06	6.68	24.9	880	2.77	0.13	0.67	0.09	76.4	1.4	5	5.89	6.4
WF-45		0.15	<0.2	0.05	7.22	10.9	1110	2.22	0.04	1.29	0.09	69.0	1.5	5	4.60	5.1
WF-47		0.05	<0.2	0.07	6.90	15.7	520	2.79	0.06	0.70	0.07	62.7	1.1	2	5.65	4.8
WF-48		0.81	<0.2	0.05	6.53	2.5	1140	1.67	0.04	1.61	0.03	24.4	0.7	6	1.15	2.2
WF-50		0.07	<0.2	0.11	6.68	8.4	1150	1.55	0.07	3.51	0.11	29.3	5.2	13	1.16	8.0
WF-51		0.28	<0.2	0.10	7.32	17.3	1040	1.97	0.08	2.32	0.09	41.0	4.5	14	2.09	8.8
WF-53		0.77	<0.2	0.07	8.07	3.4	1540	1.62	0.05	3.32	0.14	48.2	8.5	20	0.63	10.2
WF-54		0.37	<0.2	0.06	7.97	5.1	1320	1.73	0.08	3.34	0.09	50.0	8.7	22	1.64	12.5
WF-56		0.45	<0.2	0.08	8.04	3.2	1510	1.73	0.07	3.19	0.19	52.5	8.8	22	0.90	10.9
WF-57		0.17	<0.2	0.08	8.18	4.9	1350	1.64	0.08	2.78	0.14	52.0	8.2	24	1.60	10.9



ALS USA Inc.

4977 Energy Way

Reno NV 89502

Phone: +1 775 356 5395 Fax: +1 775 355 0179

www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC

1712 CAREY AVENUE

SUITE 100

CHEYENNE WY 82001

Page: 2 - B

Total # Pages: 3 (A - E)

Plus Appendix Pages

Finalized Date: 12-MAY-2021

Account: KEERRG

CERTIFICATE OF ANALYSIS RE21096417

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P
		%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
		0.01	0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01	0.1	0.2	10
WF-1		0.48	0.89	0.08	0.4	0.007	0.15	3.8	2.1	0.02	52	3.58	0.01	0.6	1.4	30
WF-2		3.63	16.50	0.13	0.9	0.049	2.20	26.2	139.5	2.16	721	2.60	2.89	10.8	41.4	920
WF-3		0.76	11.20	0.14	0.7	0.010	2.74	14.4	67.5	0.12	119	1.51	0.95	12.9	4.3	450
WF-4		1.19	19.90	0.18	2.0	0.023	3.05	18.9	8.0	0.04	81	0.90	2.50	21.6	3.0	140
WF-6		0.69	13.65	0.13	<0.1	0.006	2.50	6.9	4.6	0.04	342	0.83	2.95	1.4	0.8	160
WF-7		0.68	13.10	0.13	0.1	0.007	1.86	7.5	5.2	0.06	306	1.41	3.07	1.5	1.1	180
WF-9		0.87	16.45	0.14	1.2	0.017	2.32	11.9	10.7	0.14	202	0.95	2.83	11.6	1.9	300
WF-10		0.94	14.85	0.14	0.5	0.013	1.80	13.6	9.6	0.20	217	0.78	2.95	5.2	2.2	270
WF-12		0.95	21.7	0.16	2.9	0.030	3.16	16.7	17.0	0.08	253	0.87	2.10	24.9	1.7	540
WF-13		1.12	17.40	0.16	1.6	0.023	2.38	18.9	14.6	0.17	240	0.76	2.42	15.3	2.2	520
WF-15		1.15	16.15	0.15	0.7	0.013	1.74	13.8	9.7	0.12	233	0.78	2.96	8.0	1.1	340
WF-16		0.99	15.45	0.13	0.3	0.011	1.57	13.2	7.1	0.12	197	0.48	3.24	3.8	1.1	290
WF-18		2.18	15.70	0.12	0.5	0.030	2.13	25.6	12.0	0.62	371	0.51	2.52	8.4	2.9	580
WF-19		1.56	15.05	0.12	0.2	0.024	1.63	24.5	8.3	0.37	289	0.61	2.73	5.1	2.3	460
WF-21		1.78	21.8	0.16	1.7	0.037	3.29	28.4	21.2	0.37	355	0.80	2.57	21.3	4.0	710
WF-22		2.07	20.2	0.16	1.5	0.039	2.91	34.7	23.2	0.54	417	0.43	2.25	15.6	5.5	680
WF-24		1.27	15.60	0.16	2.0	0.019	3.05	18.7	23.2	0.11	184	0.77	2.23	9.6	1.7	250
WF-25		0.97	13.45	0.15	0.8	0.013	3.45	14.4	12.1	0.08	131	0.71	2.06	6.5	1.2	270
WF-27		1.40	19.80	0.18	3.1	0.028	3.90	28.6	23.0	0.12	186	1.00	2.30	17.9	1.7	400
WF-28		1.15	15.80	0.16	1.7	0.020	4.13	21.0	18.9	0.10	150	0.85	2.23	10.9	1.2	360
WF-30		1.01	20.1	0.16	2.1	0.033	3.69	17.1	14.8	0.08	179	0.57	2.02	17.6	1.0	210
WF-31		1.03	13.15	0.15	0.6	0.012	2.11	28.6	9.5	0.08	183	0.67	2.48	5.8	1.3	310
WF-32		5.05	28.1	0.18	1.9	0.086	2.69	36.9	76.3	1.80	1060	0.86	0.99	18.0	21.7	1280
WF-33		2.01	22.0	0.21	4.5	0.050	4.39	51.9	35.6	0.26	257	1.69	2.15	23.1	3.8	660
WF-34		1.11	14.00	0.16	1.8	0.020	3.80	19.1	15.7	0.10	153	0.85	1.97	9.9	1.5	410
WF-36		1.15	18.80	0.20	3.2	0.035	4.25	41.5	24.7	0.17	368	0.99	2.41	15.8	1.5	630
WF-37		0.86	14.35	0.17	0.8	0.012	3.99	15.1	11.0	0.08	118	0.71	2.08	6.7	0.9	370
WF-39		0.80	12.75	0.18	0.4	0.010	4.44	13.8	9.2	0.05	121	0.86	1.83	4.3	1.2	460
WF-41		1.55	14.55	0.17	1.7	0.022	3.53	16.4	27.7	0.14	238	0.70	1.97	9.6	2.8	840
WF-42		1.50	14.10	0.17	0.9	0.018	3.43	18.5	19.1	0.21	378	1.03	2.11	7.8	2.6	650
WF-44		1.46	18.05	0.21	3.4	0.033	3.90	43.1	35.3	0.12	127	1.21	2.10	13.9	2.0	870
WF-45		1.18	17.75	0.21	2.3	0.022	3.86	41.5	30.0	0.14	135	0.99	2.40	11.2	2.0	1140
WF-47		0.98	19.55	0.20	3.8	0.039	4.21	35.7	41.4	0.09	134	0.92	2.18	16.5	1.4	1020
WF-48		0.82	14.75	0.15	0.5	0.009	2.91	13.9	11.8	0.05	89	0.67	2.39	4.6	1.0	420
WF-50		1.85	16.90	0.14	2.5	0.021	2.41	17.3	26.8	0.50	364	0.66	2.46	6.5	9.7	1650
WF-51		1.68	17.75	0.17	1.3	0.022	2.82	21.0	21.7	0.40	309	0.96	2.35	7.8	7.8	720
WF-53		2.54	20.5	0.17	3.7	0.032	2.04	25.6	23.1	0.74	518	0.64	3.29	7.4	14.0	2080
WF-54		2.68	19.70	0.18	3.2	0.032	2.05	26.4	27.8	0.86	442	0.73	2.90	8.5	16.0	1490
WF-56		2.56	20.6	0.18	3.7	0.031	2.04	27.5	22.0	0.84	519	0.72	3.19	7.4	15.7	2540
WF-57		2.68	19.45	0.18	3.2	0.032	2.08	27.3	23.4	0.78	511	0.65	3.01	8.2	15.7	1640



ALS USA Inc.

4977 Energy Way

Reno NV 89502

Phone: +1 775 356 5395 Fax: +1 775 355 0179

www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC

1712 CAREY AVENUE

SUITE 100

CHEYENNE WY 82001

Page: 2 - C

Total # Pages: 3 (A - E)

Plus Appendix Pages

Finalized Date: 12-MAY-2021

Account: KEERRG

CERTIFICATE OF ANALYSIS RE21096417

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	U
		ppm 0.5	ppm 0.1	ppm 0.002	% 0.01	ppm 0.05	ppm 0.1	ppm 1	ppm 0.2	ppm 0.2	ppm 0.05	ppm 0.05	ppm 0.01	% 0.005	ppm 0.02
WF-1		20.5	5.8	<0.002	0.01	0.58	0.4	<1	<0.2	6.2	<0.05	0.06	1.15	0.023	0.04
WF-2		23.3	90.6	<0.002	0.09	10.30	9.5	1	2.2	617	0.69	<0.05	7.92	0.326	0.48
WF-3		339	128.0	<0.002	0.01	15.45	1.7	1	1.4	75.2	1.32	<0.05	6.08	0.070	0.65
WF-4		30.4	109.5	<0.002	<0.01	5.77	0.3	<1	0.9	51.6	1.58	<0.05	14.65	0.030	0.42
WF-6		21.0	55.9	<0.002	<0.01	0.21	0.6	<1	0.2	515	0.09	<0.05	1.79	0.023	0.26
WF-7		107.5	38.7	<0.002	0.01	1.18	0.7	<1	0.2	497	0.08	<0.05	1.81	0.028	0.17
WF-9		38.3	90.3	<0.002	<0.01	1.49	1.3	<1	2.8	311	0.98	<0.05	5.77	0.068	0.46
WF-10		22.1	58.0	<0.002	0.01	1.02	1.8	<1	1.1	443	0.43	<0.05	4.11	0.080	0.30
WF-12		44.2	163.0	<0.002	<0.01	1.48	0.7	<1	6.5	65.6	2.25	<0.05	13.45	0.034	0.83
WF-13		17.7	107.0	<0.002	0.01	1.04	1.5	<1	3.8	228	1.33	<0.05	8.16	0.089	0.54
WF-15		12.0	56.8	<0.002	<0.01	1.14	1.2	<1	1.9	487	0.61	<0.05	4.19	0.067	0.29
WF-16		26.9	38.1	<0.002	<0.01	0.64	1.2	<1	0.7	597	0.30	<0.05	2.60	0.062	0.21
WF-18		18.2	72.2	<0.002	<0.01	0.73	5.3	<1	1.7	433	0.51	<0.05	5.60	0.189	0.33
WF-19		9.6	41.7	<0.002	<0.01	0.45	4.2	<1	1.0	560	0.27	<0.05	4.83	0.143	0.21
WF-21		26.5	156.5	<0.002	0.03	0.91	3.4	<1	4.8	147.5	1.90	<0.05	14.80	0.142	0.76
WF-22		173.5	127.5	<0.002	0.01	9.69	4.7	<1	3.6	239	1.28	<0.05	15.35	0.176	0.64
WF-24		33.0	118.0	<0.002	<0.01	1.09	1.6	<1	2.1	133.0	0.78	<0.05	18.05	0.053	0.55
WF-25		24.5	112.5	<0.002	<0.01	0.76	1.0	<1	1.3	354	0.54	<0.05	5.09	0.062	0.53
WF-27		20.8	171.5	<0.002	0.01	1.89	2.1	<1	4.0	114.5	1.53	<0.05	17.30	0.083	0.87
WF-28		19.3	146.0	<0.002	<0.01	1.10	1.5	<1	2.2	338	0.87	<0.05	9.55	0.081	0.71
WF-30		20.2	160.5	<0.002	<0.01	1.19	1.6	<1	4.6	103.5	1.62	<0.05	13.95	0.040	0.82
WF-31		13.6	65.1	<0.002	<0.01	0.72	1.0	<1	1.5	411	0.49	<0.05	5.71	0.064	0.35
WF-32		22.7	137.0	0.002	0.01	2.18	14.1	<1	3.7	242	1.15	<0.05	15.35	0.438	0.76
WF-33		25.8	177.0	0.002	0.01	3.03	3.6	<1	5.1	132.5	1.79	<0.05	19.00	0.114	0.86
WF-34		19.1	126.5	<0.002	<0.01	1.29	1.4	<1	2.0	278	0.81	<0.05	7.68	0.063	0.62
WF-36		29.3	178.0	0.002	<0.01	1.42	2.6	<1	3.2	207	1.38	<0.05	14.90	0.094	0.90
WF-37		26.0	125.5	<0.002	<0.01	0.61	1.4	<1	1.3	424	0.54	<0.05	5.35	0.085	0.59
WF-39		22.7	128.0	<0.002	<0.01	0.25	0.7	<1	0.7	440	0.30	<0.05	3.88	0.074	0.57
WF-41		21.5	156.0	<0.002	0.01	1.33	1.9	<1	1.9	181.5	0.75	<0.05	8.59	0.093	0.76
WF-42		22.5	106.0	<0.002	<0.01	0.93	2.8	<1	1.2	425	0.67	<0.05	6.28	0.133	0.51
WF-44		20.9	184.0	0.002	0.01	8.74	1.9	<1	4.5	82.2	1.28	<0.05	17.50	0.091	0.81
WF-45		20.4	153.5	<0.002	0.01	3.99	1.7	<1	3.0	285	0.96	<0.05	13.50	0.120	0.66
WF-47		26.0	192.0	<0.002	0.01	5.63	1.4	<1	4.5	54.5	1.44	<0.05	18.15	0.063	0.92
WF-48		16.0	82.0	<0.002	<0.01	0.61	0.7	<1	0.7	556	0.31	<0.05	3.66	0.093	0.35
WF-50		19.1	52.2	<0.002	0.03	2.84	4.3	1	1.1	536	0.45	<0.05	4.90	0.243	0.42
WF-51		20.1	88.9	<0.002	0.03	2.61	3.4	<1	1.1	524	0.49	<0.05	6.17	0.212	0.46
WF-53		19.1	31.2	<0.002	0.01	0.68	5.7	1	1.0	735	0.46	<0.05	2.82	0.359	0.07
WF-54		18.3	42.9	0.002	0.01	1.27	6.4	<1	1.3	636	0.53	<0.05	4.11	0.370	0.15
WF-56		21.2	33.5	0.002	0.01	0.84	6.1	1	1.0	747	0.46	<0.05	3.19	0.362	0.12
WF-57		20.8	41.0	0.002	0.01	1.72	5.9	<1	1.1	685	0.52	<0.05	4.03	0.373	0.18



ALS USA Inc.

4977 Energy Way

Reno NV 89502

Phone: +1 775 356 5395 Fax: +1 775 355 0179

www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC

1712 CAREY AVENUE

SUITE 100

CHEYENNE WY 82001

Page: 2 - D

Total # Pages: 3 (A - E)

Plus Appendix Pages

Finalized Date: 12-MAY-2021

Account: KEERRG

CERTIFICATE OF ANALYSIS RE21096417

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		V	W	Y	Zn	Zr	Dy	Er	Eu	Gd	Ho	Lu	Nd	Pr	Sm
		ppm 1	ppm 0.1	ppm 0.1	ppm 2	ppm 0.5	ppm 0.05	ppm 0.03	ppm 0.03	ppm 0.05	ppm 0.01	ppm 0.01	ppm 0.1	ppm 0.03	ppm 0.03
WF-1		5	0.4	1.6	6	15.4	0.31	0.18	0.10	0.37	0.06	0.04	3.7	0.99	0.62
WF-2		82	14.0	14.3	98	25.6	2.58	1.34	0.94	3.25	0.50	0.19	23.1	6.40	4.20
WF-3		12	4.2	18.2	13	17.2	3.24	1.67	0.35	3.03	0.63	0.19	12.4	3.27	2.90
WF-4		7	24.9	21.8	57	45.4	4.25	2.17	0.34	4.78	0.81	0.27	21.5	5.47	5.62
WF-6		5	0.2	3.5	16	1.0	0.52	0.41	0.39	0.59	0.12	0.11	5.3	1.47	0.83
WF-7		5	0.2	3.3	17	1.4	0.51	0.36	0.39	0.65	0.11	0.09	5.9	1.65	0.95
WF-9		12	1.0	9.0	30	26.4	1.54	0.87	0.44	1.69	0.31	0.14	9.9	2.71	1.99
WF-10		17	0.6	5.8	24	11.9	1.08	0.57	0.48	1.40	0.20	0.09	11.3	3.13	1.97
WF-12		5	1.4	20.4	46	58.9	3.45	1.94	0.39	3.45	0.69	0.29	15.4	4.10	3.67
WF-13		15	1.0	14.7	38	35.3	2.61	1.36	0.56	2.89	0.51	0.19	16.9	4.54	3.40
WF-15		17	0.6	7.7	31	16.1	1.37	0.73	0.56	1.57	0.27	0.11	10.8	3.03	1.94
WF-16		19	0.3	5.2	23	8.6	0.96	0.52	0.56	1.16	0.19	0.08	9.6	2.76	1.56
WF-18		49	1.1	10.9	49	13.3	2.08	1.03	0.98	2.71	0.39	0.14	20.4	5.66	3.56
WF-19		40	0.5	7.7	30	5.7	1.45	0.71	0.79	1.93	0.28	0.10	18.1	5.25	2.80
WF-21		25	1.8	20.5	52	44.2	3.66	1.90	0.73	4.07	0.69	0.25	22.8	6.63	4.64
WF-22		37	1.8	16.9	57	37.2	3.06	1.58	0.86	3.59	0.59	0.22	24.5	7.43	4.27
WF-24		10	0.5	8.1	34	65.3	1.45	0.77	0.44	1.78	0.28	0.12	13.5	3.85	2.39
WF-25		13	0.4	6.7	17	19.8	1.18	0.61	0.43	1.41	0.22	0.09	10.8	3.01	1.84
WF-27		17	1.4	14.9	42	84.6	2.68	1.42	0.61	3.10	0.51	0.22	21.1	6.26	3.83
WF-28		16	0.8	9.7	29	55.1	1.78	0.92	0.57	2.18	0.34	0.13	16.1	4.52	2.82
WF-30		16	1.1	11.2	33	48.5	2.05	1.09	0.38	2.36	0.40	0.16	13.7	3.80	2.83
WF-31		17	0.5	6.1	18	15.6	1.12	0.58	0.52	1.56	0.22	0.09	17.8	5.51	2.41
WF-32		92	3.9	21.6	159	58.7	4.07	2.14	1.15	4.77	0.79	0.30	31.1	9.02	5.78
WF-33		22	2.6	19.8	63	160.5	3.99	1.97	1.04	4.86	0.74	0.26	39.3	11.25	6.56
WF-34		13	1.6	9.4	26	59.4	1.73	0.93	0.54	2.06	0.33	0.13	14.8	4.16	2.66
WF-36		16	1.8	18.6	33	99.2	3.35	1.71	0.78	4.01	0.64	0.24	29.6	8.92	5.11
WF-37		12	0.5	7.9	16	23.1	1.42	0.71	0.52	1.78	0.26	0.10	12.6	3.45	2.26
WF-39		11	0.3	5.6	10	9.3	1.01	0.47	0.47	1.39	0.19	0.07	10.4	2.86	1.78
WF-41		22	1.1	12.4	26	40.0	2.24	1.29	0.41	2.38	0.46	0.21	13.5	3.69	2.60
WF-42		36	0.8	12.2	24	21.9	2.24	1.20	0.70	2.63	0.45	0.18	16.4	4.42	3.01
WF-44		6	2.5	28.5	37	94.8	4.66	2.67	0.60	4.93	0.94	0.40	31.4	9.54	5.80
WF-45		12	2.0	24.2	31	67.3	4.24	2.18	0.83	4.64	0.82	0.31	31.0	9.08	5.51
WF-47		5	2.4	29.0	39	96.0	5.10	2.82	0.56	5.46	1.03	0.40	28.4	8.32	5.88
WF-48		13	0.4	5.1	12	11.8	1.01	0.49	0.51	1.33	0.19	0.07	10.9	2.97	1.82
WF-50		29	0.8	14.3	46	88.0	2.48	1.38	0.72	2.77	0.50	0.20	15.4	3.95	3.09
WF-51		30	0.9	10.0	41	37.8	1.88	0.92	0.81	2.44	0.35	0.12	17.9	4.81	3.31
WF-53		41	0.6	18.3	67	139.0	3.35	1.73	1.14	3.99	0.64	0.23	24.2	6.70	4.80
WF-54		46	1.1	17.9	69	122.5	3.22	1.66	1.13	3.86	0.62	0.23	24.4	6.44	4.80
WF-56		46	0.7	19.5	68	143.0	3.72	1.90	1.24	4.42	0.70	0.25	25.9	6.94	5.15
WF-57		46	1.2	18.2	67	122.5	3.44	1.78	1.20	4.10	0.65	0.24	24.8	6.79	4.81



ALS USA Inc.
4977 Energy Way
Reno NV 89502
Phone: +1 775 356 5395 Fax: +1 775 355 0179
www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC
1712 CAREY AVENUE
SUITE 100
CHEYENNE WY 82001

Page: 2 - E
Total # Pages: 3 (A - E)
Plus Appendix Pages
Finalized Date: 12-MAY-2021
Account: KEERRG

CERTIFICATE OF ANALYSIS RE21096417

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	Hg-MS42	PGM-ICP23	PGM-ICP23	PGM-ICP23	Rh-MS25
		Tm	Yb	Hg	Au	Pt	Pd	Rh
		ppm 0.01	ppm 0.03	ppm 0.005	ppm 0.001	ppm 0.005	ppm 0.001	ppm 0.001
WF-1		0.04	0.25	0.009	0.006	<0.005	<0.001	<0.001
WF-2		0.21	1.27	1.670	0.240	<0.005	0.001	<0.001
WF-3		0.24	1.44	0.177	0.011	<0.005	<0.001	<0.001
WF-4		0.32	1.96	0.047	0.008	<0.005	<0.001	<0.001
WF-6		0.07	0.57	0.013	0.001	<0.005	<0.001	<0.001
WF-7		0.06	0.48	0.012	0.205	3.12	1.415	<0.001
WF-9		0.14	0.92	0.007	0.007	<0.005	<0.001	<0.001
WF-10		0.08	0.56	0.007	0.005	<0.005	<0.001	<0.001
WF-12		0.31	1.99	0.008	0.001	<0.005	<0.001	<0.001
WF-13		0.21	1.33	0.006	0.001	<0.005	<0.001	<0.001
WF-15		0.11	0.71	0.007	0.002	<0.005	<0.001	<0.001
WF-16		0.08	0.52	0.005	0.001	<0.005	<0.001	<0.001
WF-18		0.15	0.92	0.005	0.007	<0.005	0.001	<0.001
WF-19		0.10	0.66	0.026	0.001	<0.005	0.001	<0.001
WF-21		0.29	1.79	0.013	0.002	<0.005	<0.001	<0.001
WF-22		0.24	1.53	0.016	0.003	<0.005	<0.001	<0.001
WF-24		0.11	0.75	0.017	NSS	NSS	NSS	<0.001
WF-25		0.10	0.58	0.009	0.002	<0.005	<0.001	<0.001
WF-27		0.22	1.44	0.010	0.001	<0.005	<0.001	<0.001
WF-28		0.14	0.89	0.015	<0.001	<0.005	<0.001	<0.001
WF-30		0.17	1.09	0.042	0.001	<0.005	<0.001	<0.001
WF-31		0.09	0.56	0.010	0.001	<0.005	<0.001	<0.001
WF-32		0.32	2.04	0.062	0.011	<0.005	0.001	<0.001
WF-33		0.29	1.81	0.028	0.001	<0.005	<0.001	<0.001
WF-34		0.14	0.87	0.024	0.001	<0.005	<0.001	<0.001
WF-36		0.25	1.64	0.040	0.001	<0.005	<0.001	<0.001
WF-37		0.11	0.65	0.018	0.001	<0.005	<0.001	<0.001
WF-39		0.07	0.42	0.005	<0.001	<0.005	<0.001	<0.001
WF-41		0.21	1.36	0.013	0.004	<0.005	<0.001	<0.001
WF-42		0.19	1.21	0.008	0.001	<0.005	<0.001	<0.001
WF-44		0.42	2.63	0.009	<0.001	<0.005	0.001	<0.001
WF-45		0.33	2.09	0.012	<0.001	<0.005	<0.001	<0.001
WF-47		0.44	2.76	0.082	0.010	<0.005	0.004	<0.001
WF-48		0.07	0.45	0.010	0.001	<0.005	<0.001	<0.001
WF-50		0.20	1.27	0.021	0.007	0.008	0.007	<0.001
WF-51		0.13	0.82	0.033	0.002	<0.005	<0.001	<0.001
WF-53		0.24	1.48	0.017	0.001	<0.005	<0.001	<0.001
WF-54		0.23	1.42	0.016	0.001	<0.005	<0.001	<0.001
WF-56		0.26	1.64	0.017	0.003	<0.005	<0.001	<0.001
WF-57		0.25	1.50	0.020	0.030	<0.005	<0.001	<0.001



ALS USA Inc.
4977 Energy Way
Reno NV 89502
Phone: +1 775 356 5395 Fax: +1 775 355 0179
www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC
1712 CAREY AVENUE
SUITE 100
CHEYENNE WY 82001

Page: 3 - A
Total # Pages: 3 (A - E)
Plus Appendix Pages
Finalized Date: 12-MAY-2021
Account: KEERRG

CERTIFICATE OF ANALYSIS RE21096417

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	Ag-AA45 Ag ppm 0.2	ME-MS61r Ag ppm 0.01	ME-MS61r Al % 0.01	ME-MS61r As ppm 0.2	ME-MS61r Ba ppm 10	ME-MS61r Be ppm 0.05	ME-MS61r Bi ppm 0.01	ME-MS61r Ca % 0.01	ME-MS61r Cd ppm 0.02	ME-MS61r Ce ppm 0.01	ME-MS61r Co ppm 0.1	ME-MS61r Cr ppm 1	ME-MS61r Cs ppm 0.05	ME-MS61r Cu ppm 0.2
WF-59		0.07	<0.2	0.15	7.94	8.0	1360	1.57	0.04	1.78	0.09	42.2	7.4	27	2.94	15.3
WF-60		0.20	<0.2	0.17	7.47	13.3	1350	1.45	0.05	1.33	0.08	40.7	5.5	18	3.20	8.9
WF-62		0.26	<0.2	0.17	7.75	11.2	1310	1.61	0.06	1.88	0.06	39.9	5.6	22	2.17	9.4
WF-63		0.51	<0.2	0.15	6.66	15.3	1320	1.65	0.06	1.66	0.07	39.3	5.8	22	2.14	9.7
WF-65		0.18	<0.2	0.10	7.65	5.9	1400	1.68	0.09	2.49	0.11	42.5	6.7	19	1.77	9.7
WF-66		0.32	<0.2	0.09	7.23	6.0	1380	1.65	0.07	2.08	0.06	39.3	4.9	17	2.33	7.7
WF-68		0.51	<0.2	0.10	7.95	6.7	1400	1.71	0.06	2.75	0.07	37.9	6.9	23	3.54	10.3
WF-69		0.66	<0.2	0.10	7.77	12.4	1350	1.69	0.06	2.42	0.06	38.5	5.8	20	2.65	9.5
WF-71		0.08	<0.2	0.09	7.74	4.2	1270	1.77	0.02	2.81	0.09	37.3	7.2	21	1.76	9.5
WF-72		0.35	<0.2	0.08	6.53	5.4	1150	1.46	0.06	1.76	0.06	37.6	3.8	15	1.99	6.4
WF-74		0.13	<0.2	0.13	6.24	10.9	850	1.47	0.06	1.71	0.06	34.3	4.8	19	2.55	8.7
WF-75		0.43	<0.2	0.08	5.24	11.8	880	1.17	0.06	1.15	0.04	31.3	2.3	14	3.31	5.7



ALS USA Inc.
4977 Energy Way
Reno NV 89502
Phone: +1 775 356 5395 Fax: +1 775 355 0179
www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC
1712 CAREY AVENUE
SUITE 100
CHEYENNE WY 82001

Page: 3 - B
Total # Pages: 3 (A - E)
Plus Appendix Pages
Finalized Date: 12-MAY-2021
Account: KEERRG

CERTIFICATE OF ANALYSIS RE21096417

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	
		Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P
		%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
		0.01	0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01	0.1	0.2	10
WF-59		2.31	18.30	0.16	2.2	0.026	2.43	21.8	41.7	0.89	380	0.45	2.56	6.9	22.6	1270
WF-60		2.03	16.70	0.16	2.1	0.024	2.47	23.2	38.9	0.70	316	0.53	2.22	7.0	14.4	1200
WF-62		2.23	17.75	0.17	2.3	0.026	2.52	21.7	31.9	0.69	323	0.66	2.60	7.2	14.5	960
WF-63		2.06	17.40	0.17	2.4	0.025	2.48	21.1	30.4	0.66	313	0.76	2.46	7.7	14.7	980
WF-65		2.29	18.65	0.18	2.7	0.028	2.25	25.5	31.5	0.64	374	0.59	2.70	7.2	14.6	1490
WF-66		1.86	16.25	0.16	2.2	0.025	2.37	21.9	24.8	0.51	309	0.72	2.51	6.8	11.0	1050
WF-68		2.31	18.50	0.17	3.0	0.029	2.25	19.7	34.6	0.85	330	0.48	2.52	6.6	17.5	1050
WF-69		2.23	17.70	0.16	2.9	0.025	2.34	21.4	31.0	0.69	345	0.67	2.54	6.6	14.2	1100
WF-71		2.25	18.30	0.17	2.5	0.030	2.41	19.6	38.3	0.88	393	0.67	2.68	7.4	15.7	1370
WF-72		1.54	14.25	0.16	1.6	0.020	2.36	20.4	26.4	0.42	272	0.79	2.32	8.3	9.0	880
WF-74		1.92	14.85	0.17	1.6	0.022	2.40	18.7	24.5	0.25	478	0.96	2.01	8.9	13.1	950
WF-75		1.33	10.80	0.16	0.8	0.017	2.21	15.7	17.6	0.19	231	0.78	1.75	8.1	5.8	490



ALS USA Inc.
4977 Energy Way
Reno NV 89502
Phone: +1 775 356 5395 Fax: +1 775 355 0179
www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC
1712 CAREY AVENUE
SUITE 100
CHEYENNE WY 82001

Page: 3 - C
Total # Pages: 3 (A - E)
Plus Appendix Pages
Finalized Date: 12-MAY-2021
Account: KEERRR

CERTIFICATE OF ANALYSIS RE21096417

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl
		ppm 0.5	ppm 0.1	ppm 0.002	% 0.01	ppm 0.05	ppm 0.1	ppm 1	ppm 0.2	ppm 0.2	ppm 0.05	ppm 0.05	ppm 0.01	% 0.005	ppm 0.02
WF-59		15.0	64.2	0.002	<0.01	2.92	5.4	<1	1.0	541	0.44	<0.05	2.62	0.328	0.35
WF-60		14.8	71.5	<0.002	<0.01	3.76	4.8	<1	1.0	422	0.47	<0.05	2.71	0.295	0.40
WF-62		16.4	63.9	<0.002	0.01	1.98	5.2	<1	1.2	528	0.50	<0.05	3.18	0.310	0.40
WF-63		15.1	64.1	<0.002	0.01	2.50	4.9	<1	1.2	455	0.51	<0.05	3.25	0.315	0.40
WF-65		18.5	49.3	<0.002	0.01	3.23	5.4	<1	1.3	647	0.49	<0.05	3.54	0.299	0.28
WF-66		121.0	62.3	0.002	<0.01	3.23	4.2	<1	1.1	581	0.50	<0.05	3.78	0.252	0.33
WF-68		18.7	51.1	0.002	<0.01	1.80	6.0	<1	1.0	768	0.41	<0.05	2.78	0.324	0.28
WF-69		20.2	56.6	0.003	0.01	2.30	5.0	<1	1.0	692	0.44	<0.05	3.53	0.295	0.29
WF-71		17.4	54.9	<0.002	<0.01	2.01	5.3	<1	1.2	671	0.51	<0.05	3.99	0.309	0.30
WF-72		13.3	70.1	0.002	<0.01	3.72	3.4	<1	1.0	469	0.70	<0.05	4.56	0.208	0.35
WF-74		17.6	77.1	<0.002	<0.01	5.02	4.0	<1	1.4	361	0.84	<0.05	5.24	0.185	0.32
WF-75		29.4	80.4	<0.002	<0.01	5.35	2.4	<1	1.0	288	0.70	<0.05	4.79	0.157	0.40



ALS USA Inc.
 4977 Energy Way
 Reno NV 89502
 Phone: +1 775 356 5395 Fax: +1 775 355 0179
 www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC
 1712 CAREY AVENUE
 SUITE 100
 CHEYENNE WY 82001

Page: 3 - D
 Total # Pages: 3 (A - E)
 Plus Appendix Pages
 Finalized Date: 12-MAY-2021
 Account: KEERRG

CERTIFICATE OF ANALYSIS RE21096417

Sample Description	Method Analyte Units LOD	ME-MS61r V ppm 1	ME-MS61r W ppm 0.1	ME-MS61r Y ppm 0.1	ME-MS61r Zn ppm 2	ME-MS61r Zr ppm 0.5	ME-MS61r Dy ppm 0.05	ME-MS61r Er ppm 0.03	ME-MS61r Eu ppm 0.03	ME-MS61r Gd ppm 0.05	ME-MS61r Ho ppm 0.01	ME-MS61r Lu ppm 0.01	ME-MS61r Nd ppm 0.1	ME-MS61r Pr ppm 0.03	ME-MS61r Sm ppm 0.03	ME-MS61r Tb ppm 0.01
WF-59		46	0.9	10.7	65	79.2	2.00	0.92	0.81	2.70	0.36	0.12	19.2	5.12	3.53	0.38
WF-60		42	1.2	12.1	53	72.1	2.17	1.03	0.80	2.84	0.41	0.13	19.9	5.30	3.67	0.39
WF-62		50	0.9	11.0	57	79.9	2.17	1.03	0.83	2.74	0.39	0.13	19.3	5.11	3.57	0.38
WF-63		43	1.1	11.9	56	87.0	2.17	1.08	0.81	2.72	0.40	0.15	18.9	5.02	3.60	0.38
WF-65		45	1.5	18.1	55	97.3	3.30	1.69	1.11	3.86	0.63	0.22	23.8	6.34	4.64	0.56
WF-66		37	1.5	13.6	44	78.4	2.44	1.19	0.88	2.95	0.46	0.16	19.6	5.15	3.69	0.42
WF-68		52	1.0	12.2	60	111.5	2.22	1.16	0.90	2.74	0.42	0.15	18.6	4.84	3.46	0.40
WF-69		47	1.3	12.7	55	108.5	2.38	1.22	0.93	3.00	0.46	0.16	19.4	5.06	3.66	0.42
WF-71		45	1.4	13.8	59	88.3	2.53	1.32	0.92	3.05	0.49	0.18	19.0	4.88	3.75	0.44
WF-72		30	2.0	10.7	35	58.1	1.94	0.94	0.76	2.48	0.36	0.13	17.2	4.61	3.19	0.35
WF-74		27	2.6	14.5	31	52.1	2.45	1.37	0.73	2.73	0.49	0.18	16.7	4.40	3.24	0.41
WF-75		27	3.4	8.4	21	21.9	1.60	0.79	0.59	2.01	0.29	0.11	14.0	3.69	2.65	0.29



ALS USA Inc.
4977 Energy Way
Reno NV 89502
Phone: +1 775 356 5395 Fax: +1 775 355 0179
www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC
1712 CAREY AVENUE
SUITE 100
CHEYENNE WY 82001

Page: 3 - E
Total # Pages: 3 (A - E)
Plus Appendix Pages
Finalized Date: 12-MAY-2021
Account: KEERRG

CERTIFICATE OF ANALYSIS RE21096417

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	Hg-MS42	PGM-ICP23	PGM-ICP23	PGM-ICP23	Rh-MS25
		Tm	Yb	Hg	Au	Pt	Pd	Rh
		ppm 0.01	ppm 0.03	ppm 0.005	ppm 0.001	ppm 0.005	ppm 0.001	ppm 0.001
WF-59		0.13	0.77	0.016	0.015	<0.005	<0.001	<0.001
WF-60		0.14	0.87	0.042	0.001	<0.005	<0.001	<0.001
WF-62		0.14	0.85	0.011	0.001	<0.005	<0.001	<0.001
WF-63		0.15	0.92	0.020	0.001	<0.005	<0.001	<0.001
WF-65		0.23	1.44	0.050	0.006	<0.005	<0.001	<0.001
WF-66		0.17	1.04	0.038	0.002	<0.005	<0.001	<0.001
WF-68		0.16	1.02	0.070	0.002	<0.005	<0.001	<0.001
WF-69		0.17	0.99	0.058	0.003	<0.005	<0.001	<0.001
WF-71		0.19	1.16	0.039	0.002	<0.005	<0.001	<0.001
WF-72		0.13	0.83	0.034	0.002	<0.005	<0.001	<0.001
WF-74		0.19	1.20	0.022	0.005	<0.005	<0.001	<0.001
WF-75		0.11	0.73	0.044	0.425	<0.005	0.001	<0.001



ALS USA Inc.
4977 Energy Way
Reno NV 89502
Phone: +1 775 356 5395 Fax: +1 775 355 0179
www.alsglobal.com/geochemistry

To: RED RIVER CREEK MINING GROUP LLC
1712 CAREY AVENUE
SUITE 100
CHEYENNE WY 82001

Page: Appendix 1
Total # Appendix Pages: 1
Finalized Date: 12-MAY-2021
Account: KEERRG

CERTIFICATE OF ANALYSIS RE21096417

CERTIFICATE COMMENTS

ANALYTICAL COMMENTS

Applies to Method: NSS is non-sufficient sample.
ALL METHODS

Applies to Method: REEs may not be totally soluble in this method.
ME-MS61r

LABORATORY ADDRESSES

Processed at ALS Reno located at 4977 Energy Way, Reno, NV, USA.
Applies to Method: CRU-21 CRU-31 CRU-QC LOG-22
PUL-31 PUL-QC SPL-21 WEI-21

Processed at ALS Vancouver located at 2103 Dollarton Hwy, North Vancouver, BC, Canada.
Applies to Method: Ag-AA45 Hg-MS42 ME-MS61r PGM-ICP23
Rh-MS25