TR558A

Injection Molding

Description

- Transparency, General Purpose

Applications

- Electric & Electronic Products

Properties	Method	Unit	TR558A
Physical			
Specific Gravity , 23℃	ISO 1183		1.11
Mold Shrinkage , 23℃, 3.2mm , 23℃	ISO 294-4	%	0.4 ~ 0.6
Melt Volume Rate , 220℃, 10kg	ISO 1133	cm^3/10min	24
Mechanical			
Tensile Strength at Yield , 23℃, 50mm/min, 4mm	ISO 527	MPa	55
Tensile Elongation at Break , 23℃, 50mm/min, 4mm	ISO 527	%, (Min)	15
Tensile Modulus , 23℃,1mm/min, 4mm	ISO 527	MPa	2400
Flexural Strength , 23℃, 2mm/min, 4mm	ISO 178	MPa	79
Flexural Modulus , 23℃, 2mm/min, 4mm	ISO 178	MPa	2500
Izod Impact Strength , Notched, 4mm, 23℃	ISO 180/1A	kJ/m^2	12
Izod Impact Strength , Notched, 4mm, -30℃	ISO 180/1A	kJ/m^2	5
Charpy Impact Strength , 4mm, 23℃	ISO 179/1eA	kJ/m^2	12
Charpy Impact Strength , 4mm, -30℃	ISO 179/1eA	kJ/m^2	5
Rockwell Hardness , R-Scale	ISO 2039		112
Thermal			
HDT , Flatwise, 1.8MPa, 4mm, Unannealed	ISO 75	℃	71
VICAT , 50N, 50℃/h	ISO 306	℃	91
RTI , Electrical	UL 746B	℃	50
RTI , Mechanical with Impact	UL 746B	℃	50
RTI , Mechanical without Impact	UL 746B	℃	50
Flammability, 1.5mm	UL 94		HB
Flammability, 3.0mm	UL 94		HB
Optical			
Haze	ASTM D1003	%	1.9
Luminous Transmittance ,3.2mm	ASTM D1003	%	90

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.Values given should not be interpreted as specification and not be used for designing part or tool.All properties, except melt flow rate are measured by injection molded specimens after 48 hours storage at 23℃, 50% relative humidity.

Updated Date : 12-Sep-17 Issued Date : 8-Jun-21

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

TR558A

Injection Molding

Description

- Transparency, General Purpose

Applications

- Electric & Electronic Products

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	℃	80 ~ 90
Drying Time	hrs	2 ~ 4
Moisture Content	%	0.1 ~
Melt Temperature	℃	190 ~ 220
Nozzle Temperature	℃	200 ~ 250
Mold Temperature	℃	40 ~ 80
Back Pressure, Hydraulic Type	kg/㎠	30 ~ 60
Screw Speed	rpm	30 ~ 60

Note

Back Pressure & Measuring Speed are only mentioned as general guidelines.These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

Updated Date : 12-Sep-17 Issued Date : 8-Jun-21

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.