

FRACMATH: A fast and vectorized MATLAB framework for continuum damage mechanics with crack-band regularization

Jaykumar Mavani¹ and Madura Pathirage¹

¹ Gerald May Department of Civil, Construction, and Environmental Engineering, University of New Mexico, Albuquerque, NM, USA  Corresponding author

DOI: [10.xxxxxx/draft](https://doi.org/10.xxxxxx/draft)

Software

- [Review](#) 
- [Repository](#) 
- [Archive](#) 

Editor: [Open Journals](#) 

Reviewers:

- [@openjournals](#)

Submitted: 01 January 1970

Published: unpublished

License

Authors of papers retain copyright and release the work under a Creative Commons Attribution 4.0 International License ([CC BY 4.0](https://creativecommons.org/licenses/by/4.0/)).

Summary

FRACMATH is an open-source MATLAB framework for finite-element simulation of crack-band-regularized continuum damage mechanics (CDM) in quasi-brittle materials. The code uses a scalar isotropic damage variable, the modified von Mises equivalent strain (Vree et al., 1995), exponential softening, and Oliver’s direction-dependent projected crack-band length (Bažant & Oh, 1983; Oliver, 1989). It keeps the solver, plotting, and constitutive update inside MATLAB, with no MATLAB executable (MEX) files, compiled extensions, or separate build system.

The package includes a two-dimensional (2D) notched three-point bending (3PB) benchmark checked against Abaqus/Standard through an Oliver-matched user material subroutine (UMAT), plus two three-dimensional (3D) MATLAB demonstrations: the Nooru-Mohamed mixed-mode test and Brokenshire’s notched beam torsion test. The repository stores source code, input decks, results, plotting scripts, and a theory manual at <https://github.com/Jaykumar9033/FRACMATH> under the MIT license.

Statement of need

Open-source finite-element tools already cover many research needs, including OOFEM in C++ (Patzák & Bittnar, 2001), FEniCS for Python/C++ workflows (Logg et al., 2012), Akantu for high-performance fracture simulations (Richart et al., 2024), and CALFEM as a MATLAB teaching toolbox (Austrell et al., 2004). These projects are valuable, but extending them for a new damage formulation can require learning a larger architecture, templated interface, wrapper layer, or compiled user-material workflow. Commercial tools such as Abaqus/Standard are also powerful, but custom CDM models generally require user-material subroutines, such as UMAT for Abaqus/Standard or VUMAT for Abaqus/Explicit, plus careful state-variable handling (Dassault Systèmes Simulia Corp., 2023).

MATLAB remains useful in engineering research because students already know its matrix syntax, plotting tools, debugger, profiler, and sparse linear algebra. This matters for fracture modeling, where a user often needs to inspect element-level strain histories, change a softening law, compare crack-band lengths, and immediately visualize the damage field. FRACMATH uses that accessibility to provide a transparent CDM reference implementation rather than a general-purpose finite-element platform.

The closest recent Journal of Open Source Software (JOSS) comparison is Parallel-CDM by Eldababy et al. (Eldababy et al., 2025), which provides a MATLAB implementation of 2D local and nonlocal CDM with parallel assembly. FRACMATH is complementary: its emphasis is direction-dependent Oliver crack-band scaling, the same bandwidth formula in MATLAB and

40 Abaqus, a direct UMAT cross-check on an identical 3PB mesh, and reuse of the scalar damage
41 routine for 3D mixed-mode and torsion-driven crack paths.

42 Software design

43 The material model follows standard scalar CDM, where damage variables and equivalent-strain
44 histories are used to represent stiffness degradation in quasi-brittle fracture (Bažant & Planas,
45 1998; Vree et al., 1995). Damage degrades the undamaged stiffness as

$$\sigma = (1 - \omega)C_0 : \varepsilon, \quad (1)$$

46 where $\omega \in [0, 1]$ is the damage variable. A history variable stores the maximum equivalent
47 strain so damage cannot heal. Exponential softening is scaled element by element so the
48 dissipated fracture energy matches G_F after crack-band regularization (Bažant & Oh, 1983).
49 Instead of using a fixed mesh length, FRACMATH computes Oliver's projected characteristic
50 length from the element geometry and the current maximum-principal-strain direction (Oliver,
51 1989). For a three-node triangular finite element (T3),

$$h(\mathbf{n}) = \frac{2}{\sum_{a=1}^3 |\nabla N_a \cdot \mathbf{n}|}. \quad (2)$$

52 The same idea is used for tetrahedra in 3D. In the Abaqus comparison, a preprocessing script
53 writes the T3 shape-function gradients to `oliver_t3_gradN.dat`; the UMAT then recomputes
54 Equation 2 from the current principal strain direction. This avoids using Abaqus's built-in
55 characteristic element length variable, `CELENT`, as a fixed crack-band length and keeps the
56 regularization consistent with Oliver's characteristic-length construction (Oliver, 1989).

57 The quasistatic solver uses displacement control with a fixed-secant modified Newton iteration
58 in each increment. The secant stiffness is assembled and factored once, displacement residuals
59 are iterated with that fixed matrix, and damage is updated after the displacement solve.
60 Element strains, equivalent strain, history variables, damage, and crack-band lengths are
61 updated with vectorized MATLAB operations, including pageant times; sparse linear systems use
62 MATLAB's backslash interface, which dispatches to UMFPACK (Davis, 2004). This design
63 favors readable vectorized kernels, direct plotting, and reviewer-side inspection over a larger
64 compiled framework.

65 For the Abaqus comparison, FRACMATH includes the input deck, the Fortran UMAT, the Oliver-
66 gradient table generator, and extraction scripts for load-CMOD curves, where CMOD is
67 crack-mouth-opening displacement, and damage fields. The MATLAB and Abaqus paths
68 therefore share the same mesh, boundary conditions, fracture energy, tensile strength, and
69 crack-band bandwidth formula. Differences in the plotted response are primarily solver and
70 implementation differences, not changes in the continuum model.

71 Benchmarks

72 The main quantitative benchmark is the Gregoire notched 3PB beam (Grégoire et al., 2013),
73 modeled with the same refined mesh, material constants, loading, scalar damage law, and
74 Oliver crack-band formula in MATLAB and Abaqus. The 2D mesh uses Abaqus CPS3 elements,
75 where CPS3 denotes a three-node plane-stress triangular element. MATLAB predicts a peak
76 load of 3.63982 kN at CMOD 0.022811 mm; Abaqus predicts 3.60913 kN at CMOD 0.022485
77 mm. Both simulations localize damage upward from the notch, which is the expected opening-
78 mode (mode-I) crack path for this geometry (Grégoire et al., 2013). The Abaqus UMAT
79 independently evaluates the same damage law and Oliver bandwidth inside a commercial
80 finite-element environment (Dassault Systèmes Simulia Corp., 2023; Oliver, 1989).

On the test workstation, an Intel Core Ultra 9 285K central processing unit (CPU) with 64 GB random-access memory (RAM) and a 1 TB non-volatile memory express solid-state drive (NVMe SSD), MATLAB R2024a used one thread and Abaqus/Standard 2023 used four threads. The MATLAB solver wall-clock time was 547.58 s, while the Abaqus submit-to-completion time was 1996.25 s. MATLAB time was dominated by stiffness assembly, not by the sparse solve. The timing should not be read as a universal speed claim, because solver settings, output requests, hardware, and Abaqus licensing can all change wall-clock time.

Table 1: Updated 2D 3PB comparison using the same mesh, material law, and Oliver T3 crack-band bandwidth.

Quantity	MATLAB	Abaqus + UMAT
Peak load (N)	3639.82	3609.13
CMOD at peak (mm)	0.022811	0.022485
Solver/submit wall-clock (s)	547.58	1996.25
End-to-end/internal time (s)	590.54	1968.00




Figure 1: 3PB mesh and damage fields: (a) CPS3 mesh and support/load layout; (b) Abaqus UMAT final fully damaged elements; (c) MATLAB damage field at peak load; (d) MATLAB post-peak damage field.




Figure 2: 3PB response and timing: (a) MATLAB and Abaqus load-CMOD response; (b) wall-clock comparison and MATLAB timing breakdown.

The Nooru-Mohamed benchmark checks mixed-mode 3D cracking in a double-edge-notched

concrete panel under combined tension and shear (Nooru-Mohamed, 1992). The same scalar CDM routine uses four-node linear tetrahedral (TET4) elements and Oliver crack-band scaling (Oliver, 1989). The simulated damage bands initiate at the two notch tips and coalesce across the ligament, matching the qualitative experimental crack-path pattern.




Figure 3: Nooru-Mohamed mixed-mode benchmark: (a) boundary conditions with experimental crack-path inset; (b) 3D mesh.

This example is included because mixed-mode response is a common failure point for simplified fracture implementations. In the simulation, the crack-band direction changes as the principal strain field evolves, so the projected bandwidth is recomputed rather than assigned from a constant element size. The resulting localization band does not remain a straight mode-I notch extension; it bends across the ligament in the same qualitative direction as the reported experimental crack path.




Figure 4: Nooru-Mohamed damage evolution from first localization to coalescence in a 3-by-3 sequence.

Brokenshire's torsion benchmark tests whether the same formulation can recover a curved 3D

fracture surface in a notched plain concrete beam (Jefferson et al., 2004). The model uses a prescribed twist, TET4 elements, and the same damage update. The computed band nucleates at the notch front and rotates toward the loaded corner, consistent with the experimentally recovered fracture surface.




Figure 5: Brokenshire torsion benchmark: geometry and experimental fractured specimen from Jefferson et al. (Jefferson et al., 2004).

The torsion case is deliberately different from the 3PB validation: it contains out-of-plane cracking, a nonuniform stress state, and a visibly curved fracture surface. The 3D examples are intended as qualitative crack-path demonstrations; only the 2D 3PB case is quantitatively cross-checked against Abaqus.




Figure 6: Torsion damage evolution over the imposed twist history.

Software availability

The repository contains MATLAB source code, Abaqus UMAT files, benchmark input decks, plotting scripts, updated results, a theory manual, LICENSE, CITATION.cff, CONTRIBUTING.md, and reproducibility instructions. Reviewers can run the smoke tests from the repository root with `matlab -batch "addpath('tests'); run_smoke_checks"`. The test suite has been checked on MATLAB R2022a, R2023a, and R2024a across Linux, macOS, and Windows. A release

archive digital object identifier (DOI) should be added before final JOSS acceptance.

Limitations

FRACMATH is quasistatic and does not include inertia, rate effects, contact, plasticity, or unilateral crack closure. Damage is isotropic and scalar, so anisotropic stiffness recovery and cyclic loading are outside the current scope. Crack-band scaling controls mesh-objective energy dissipation but does not introduce a physical material length scale.

Acknowledgements

The authors acknowledge support from the National Aeronautics and Space Administration, the New Mexico Space Grant Consortium under grant 80NSSC22M0044, and the New Mexico Department of Finance and Administration under grant ZI5044-MG25-109. The opinions and conclusions are those of the authors and do not necessarily reflect the views of the sponsors.

References

- Austrell, P.-E., Dahlblom, O., Lindemann, J., Olsson, A., Olsson, K.-G., Persson, K., Petersson, H., Ristinmaa, M., Sandberg, G., & Wernberg, P.-A. (2004). *CALFEM — a finite element toolbox, version 3.4*. Lund University.
- Bažant, Z. P., & Oh, B. H. (1983). Crack band theory for fracture of concrete. *Matériaux Et Construction*, 16(3), 155–177. <https://doi.org/10.1007/BF02486267>
- Bažant, Z. P., & Planas, J. (1998). *Fracture and size effect in concrete and other quasibrittle materials*. CRC Press.
- Dassault Systèmes Simulia Corp. (2023). *Abaqus/standard user's manual, version 2023*.
- Davis, T. A. (2004). Algorithm 832: UMFPACK V4.3 — an unsymmetric-pattern multifrontal method. *ACM Transactions on Mathematical Software*, 30(2), 196–199. <https://doi.org/10.1145/992200.992206>
- Eldababy, H., Saji, R. P., Pantidis, P., & Mobasher, M. (2025). Parallel-CDM: Parallel implementation of continuum damage mechanics simulations using FEM and MATLAB. *Journal of Open Source Software*, 10(112), 7610. <https://doi.org/10.21105/joss.07610>
- Grégoire, D., Rojas-Solano, L. B., & Pijaudier-Cabot, G. (2013). Failure and size effect for notched and unnotched concrete beams. *International Journal for Numerical and Analytical Methods in Geomechanics*, 37(10), 1434–1452. <https://doi.org/10.1002/nag.2180>
- Jefferson, A. D., Bennett, T., & Hee, S. C. (2004). Three-dimensional finite element simulations of fracture tests using the Craft concrete model. *Computers and Concrete*, 1(3), 261–284. <https://doi.org/10.12989/cac.2004.1.3.261>
- Logg, A., Mardal, K.-A., & Wells, G. N. (Eds.). (2012). *Automated solution of differential equations by the finite element method: The FEniCS book*. Springer. <https://doi.org/10.1007/978-3-642-23099-8>
- Nooru-Mohamed, M. B. (1992). *Mixed-mode fracture of concrete: An experimental approach* [PhD thesis]. Delft University of Technology.
- Oliver, J. (1989). A consistent characteristic length for smeared cracking models. *International Journal for Numerical Methods in Engineering*, 28(2), 461–474. <https://doi.org/10.1002/nme.1620280214>
- Patzák, B., & Bittnar, Z. (2001). Design of object-oriented finite element code. *Advances*

155 in *Engineering Software*, 32(10–11), 759–767. [https://doi.org/10.1016/S0965-9978\(01\)](https://doi.org/10.1016/S0965-9978(01)00027-8)
156 [00027-8](https://doi.org/10.1016/S0965-9978(01)00027-8)

157 Richart, N., Anciaux, G., Gallyamov, E., Frérot, L., Kammer, D., Pundir, M., Vocialta,
158 M., Ramos, A. C., Corrado, M., Müller, P., Barras, F., Zhang, S., Ferry, R., Durussel,
159 V., & Molinari, J.-F. (2024). Akantu: An HPC finite-element library for contact and
160 dynamic fracture simulations. *Journal of Open Source Software*, 9(94), 5253. <https://doi.org/10.21105/joss.05253>
161

162 Vree, J. H. P. de, Brekelmans, W. A. M., & Gils, M. A. J. van. (1995). Comparison of nonlocal
163 approaches in continuum damage mechanics. *Computers & Structures*, 55(4), 581–588.
164 [https://doi.org/10.1016/0045-7949\(94\)00501-S](https://doi.org/10.1016/0045-7949(94)00501-S)

DRAFT